

Influence of Anion Substitution on the Lithium Diffusivity in Hexagonal $\text{Li}_x\text{TiS}_{2-y}\text{Se}_y$

Benjamin Ruprecht,¹ Jessica Heine,^{*1} Martin Wilkening,¹ Sylvio Indris,^{1†} Joseph Wontcheu,²
Wolfgang Bensch,² Thomas Bredow,³ Paul Heitjans¹

¹ Leibniz Universität Hannover, Institut für Physikalische Chemie und Elektrochemie,
Callinstraße 3a, 30167 Hannover, Germany

² Christian-Albrechts-Universität zu Kiel, Institut für Anorganische Chemie,
Olshausenstr. 40 (Otto-Hahn-Platz 6/7), 24098 Kiel, Germany

³ Universität Bonn, Lehrstuhl für Theoretische Chemie, Wegelerstr. 12, 53115 Bonn, Germany

[†] present address: Forschungszentrum Karlsruhe, Institut für Nanotechnologie, Hermann-von-Helmholtz-Platz 1, 76344 Eggenstein-Leopoldshafen, Germany

E-Mail: heine@pci.uni-hannover.de

*Presented at the Bunsen Colloquium: Spectroscopic Methods in Solid State Diffusion and Reactions
September 24th – 25th, 2009, Leibniz University Hannover, Germany*

Diffusion processes play a crucial role in the design of new components for, *e.g.*, rechargeable batteries, electrochemical sensors and electrochromic devices [1]. In order to systematically develop suitable materials for these applications, the diffusion properties of ion conductors have to be well understood. Among manifold aspects, the influence of dimensionality as well as substitution effects on ionic motion have to be taken into account when promising materials are tailored further in order to improve their transport properties.

Layered Li_xTiS_2 turned out to be an excellent model system in order to study the elementary steps of Li self-diffusion within the van-der-Waals gap between the TiS_2 layers [2,3] where Li diffusion is strictly confined to two dimensions [2,3].

The present work tries to go one step further and is concerned with the question what kind of influence the substitution of S^{2-} with Se^{2-} in Li_xTiS_2 has on the Li diffusivity. Layered $\text{Li}_x\text{TiS}_y\text{Se}_{2-y}$ ($0 \leq y \leq 2$) is single phase and shows the same crystal structure as the end members Li_xTiS_2 and Li_xTiSe_2 which is $P\bar{3}m1$. Here, we have restricted our measurements to samples with a Li content x of $x = 0.7$. Li diffusivity was studied from a microscopic point of view by rotating-frame spin-lattice relaxation (SLR) NMR measurements at moderate temperatures ranging from 150 to 500 K. Details of the technique are described in, *e.g.*, Refs. [5,6]. When plotted as a function of the inverse temperature, the diffusion-induced NMR relaxation rate $T_{1\rho}^{-1}$, which can be recorded by the well-known spin-lock technique, see, *e.g.*, Ref. [6], passes through a characteristic maximum when $\omega_1\tau \approx 0.5$ is fulfilled. While τ denotes the correlation time, ω_1 is the angular locking frequency, which is of the order of a few kHz. In the present study we have recorded $T_{1\rho}^{-1}$ rates at about 14 kHz by using an MSL 100 spectrometer (Bruker) in combination with a field-variable Oxford cryomagnet of a nominal external magnetic field of 4.7 T. This corresponds to a resonance frequency of 77.7 MHz.

In Fig. 1 Arrhenius representations of the SLR NMR rates $T_{1\rho}^{-1}$ of Li_xTiSe_2 as well as $\text{Li}_{0.7}\text{TiS}_{0.4}\text{Se}_{1.6}$ are shown. In both cases the diffusion-induced rate peak is clearly detected. As an

example, for Li_xTiSe_2 the maximum shows up at $T_{\text{max},\rho} = 322$ K. Using the above mentioned maximum condition this leads to an Li jump rate of approximately $1.8 \times 10^5 \text{ s}^{-1}$. For comparison, the corresponding jump rate of the sulfide analogue is $2 \times 10^6 \text{ s}^{-1}$ at this temperature [3]. Obviously, Li diffusion in Li_xTiS_2 is by more than one order of magnitude faster than in Li intercalated titanium diselenide. Substitution of Se^{2-} for S^{2-} shifts the maxima of the rate peaks to lower temperatures. For example, the SLR NMR rate maximum of $\text{Li}_x\text{TiS}_{0.4}\text{Se}_{1.6}$ appears, when recorded at the same locking frequency of 14 kHz, at $T = 280$ K.




Fig. 1 ^7Li NMR spin-lattice relaxation rates $1/T_{1\rho}$ of polycrystalline, $\text{Li}_{0.7}\text{TiSe}_2$ and $\text{Li}_{0.7}\text{TiS}_{0.4}\text{Se}_{1.6}$ plotted as $\log_{10}(1/T_{1\rho})$ vs. $1000/T$. Data were recorded at $\omega_0/2\pi = 77.7$ MHz and $\omega_1/2\pi \approx 14$ kHz. β denotes the frequency dependence of the relaxation rates on the low- T flanks of the diffusion-induced rate peaks (see text).

Whereas the slope of the high- T flank, reflecting long-range Li diffusion, is nearly independent of the composition y , that of the low- T side of the diffusion induced rate peak is reduced by more than a factor of two. The corresponding (low- T) activation energy decreases from about 0.37 eV ($y = 2$) to values of approximately 0.15 eV ($y \approx 1$).

Solid lines in Fig. 1 show fits based on Richards' modified expression for the spectral density function $J(\omega, \tau)$ of a 2D ionic conductor, $J(\omega, \tau) \propto \tau \cdot \ln(1 + (\omega\tau)^{-\beta})$, incorporating a logarithmic frequency dependence of the rate $T_{1\rho}^{-1}$ in the limit $\omega\tau \ll 1$ [5] as well as a non-BPP-type frequency dependence on the low- T flank being expressed by $1 < \beta < 2$ [4,6]. The latter takes into account correlation effects such as structural disorder and Coulomb interactions, see, e.g., Refs. [6,8,9]. The so obtained activation energy, which characterizes long-range Li transport, is about 0.4 eV and does not change much with composition. However, the β -values pass through a maximum located at $y = 1.0$, i.e., at the composition which produces the highest degree of mixing in the anion sublattice.

The activation energies probed when just the low- T flank is analyzed (see above) are in good agreement with those obtained from calculations using the density-functional-Hartree-Fock one-parameter hybrid method PW1PW (see [10] and Refs. therein), which were performed on samples with the composition $y = 1$. Such small values are found when an Li ion can jump from an octahedron with mixed anions to another one composed of S^{2-} anions, only.

Acknowledgement. Financial support by the DFG in the frame of SPP 1136 is gratefully acknowledged.

References

- [1] J. Maier, *Nature Mater.* 4 (2005) 805.
- [2] M. Wilkening, W. Kuchler, P. Heitjans, *Phys. Rev. Lett.* 97 (2006) 065901.
- [3] M. Wilkening, P. Heitjans, *Phys. Rev. B* 77 (2008) 024311.
- [4] W. Kuchler, P. Heitjans, A. Payer, R. Schöllhorn, *Solid State Ion.* 70-71 (1994) 434.
- [5] E. Fukushima R. Roeder, *Experimental Pulse NMR*, Addison Wesley, London 1981.
- [6] P. Heitjans, A. Schirmer, S. Indris, in: *Diffusion in Condensed Matter – Methods, Materials, Models*, P. Heitjans, J. Kärger (Eds.), Springer, Berlin/Heidelberg 2005.
- [7] P. M. Richards, *Solid State Commun.* 25 (1978) 1019.
- [8] K. Funke, *Progr. Solid State Chem.* 22 (1993) 111.

- [9] A. Bunde, W. Dieterich, P. Maass, M. Meyer, in: *Diffusion in Condensed Matter – Methods, Materials, Models*, P. Heitjans, J. Kärger (Eds.), Springer, Berlin/Heidelberg 2005.
- [10] M. M. Islam, T. Bredow, S. Indris, P. Heitjans, *Phys. Rev. Lett.* 99 (2007) 145502.