

Evaluation of CO₂ diffusion on aluminum based metal organic frameworks

Deniz Angı¹, Alev Güneş Yeresikli², Fehime Çakıcıoğlu Özkan^{2*}

¹Izmir Institute of Technology, Dept. of Materials Sci. and Eng., Izmir, TURKEY

²Izmir Institute of Technology, Dept. of Chemical Eng., Izmir, TURKEY

*Corresponding author (fehimeozkan@iyte.edu.tr)

Metal-organic frameworks(MOFs), highly porous crystalline materials, are composed of metal clusters connected by organic linkers. As they have high porosity, large surface area and large pore volume, a considerable amount of specific gases can be adsorbed onto these pores. Hydrogen, a clean energy fuel can be produced by Steam Methane Reformer (SMR) processes. Steam methane reformer off-gas, gas produced by steam methane reformer contains mainly H₂ besides to CO₂, (10-25%v/v), CH₄ (1.3-8%v/v), CO (0.25-10%v/v) as impurities. It is critical to remove CO₂ from the gas mixture not only for up-grading of SMR-off gas but also natural gas to obtain high purity H₂ or CH₄, respectively. MOFs are considered as a potential adsorbent material to be used in gas purification and separation. Zero Length Column (ZLC) technique was conducted to measure the intraparticle diffusion properties of porous adsorbents. The response curve, yielded from quadrupole mass spectrometer, is used to determine adsorption parameters such as Henry's constant and diffusion coefficient. The adsorption kinetics of CO₂, on aluminum based organic framework was studied at 30 °C. The flow rates of inert carrier gas Helium will be changed as 30, 50, 70 and 100 ml/min in order to determine whether the system will be favored by equilibrium or kinetic control. CO₂ adsorption kinetics of aluminum based organic framework synthesized were compared with the commercial one (MIL-53(Al)). The results show that the calculated diffusivity values are weakly dependent on purge flow rate. The study reveals that transport is controlled by intracrystalline diffusion. The study shows that the ZLC method is an effective tool to investigate the diffusion kinetics of CO₂ gas in MIL 53 (Al).

