**DEVELOPMENT OF A PAT MONITORED FLUID BED
GRANULATION PROCESS USING THE EXAMPLE OF A
LOW DOSE STEROID HORMONE**

Von der Fakultät für Lebenswissenschaften
der Universität Leipzig

genehmigte

D I S S E R T A T I O N

zur Erlangung des akademischen Grades

Doctor rerum naturalium

Dr. rer. nat.

vorgelegt

von

Apothekerin und Diplom-Pharmazeutin Katrin Roßteuscher-Carl,

geb. Roßteuscher

geboren am 22.06.1981 in Suhl

Dekan: Prof. Dr. T. Pompe

Gutachter: Prof. Dr. M. Schulz-Siegmund

Prof. Dr. Dr. h.c. P. Kleinebudde

Tag der Verteidigung 30.11.2018

BIBLIOGRAPHISCHE DARSTELLUNG

Katrin Roßteuscher-Carl

DEVELOPMENT OF A PAT MONITORED FLUID BED GRANULATION PROCESS USING THE EXAMPLE OF A LOW DOSE STEROID HORMONE

Fakultät für Lebenswissenschaften

Universität Leipzig

Dissertation

167 Seiten, 147 Literaturangaben, 38 Abbildungen, 17 Tabellen

---

According to ICH Q8 process analytic technology (PAT) should be established to monitor critical quality attributes (CQAs) during manufacturing processes. Ethinylestradiol (EE) is a highly active and low dosed steroid hormone that is prone to oxidative degradation. The stability of this compound is therefore a critical quality attribute that has to be considered during drug formulation development. Beside the stability of EE, granule particle size and moisture are CQAs influencing the tableting ability of the resulting granules and the stability of EE. Both CQAs should be monitored during the production process.

The investigations described in this thesis evaluate the implementation of in-line-sensors for monitoring of particle size (spatial filtering technology, SFT) and granule moisture (microwave resonance technology, MRT) during the fluid bed granulation process and the influence of process-variations on the stability of EE. The aim of these investigations was to develop an effective and mild fluid bed granulation process for a new model formulation based on microcrystalline cellulose as replacement for lactose as main filler excipient. The EE degradation products 6- α -hydroxy-EE, 6- β -hydroxy-EE, 9(11)-dehydro-EE and 6-oxo-EE were quantified as an index for the stability of EE.

It could be demonstrated that the surface of the filler substance influences the stability of EE due to the impact of water molecules. Hence, spraying sequence was determined to be a useful tool to improve the stability of EE. Correlations could be established for 6-oxo-EE with granule moisture and thermic parameters. The implementation of the SFT-sensor in the granulation process was successful. Measurement with the MRT-sensor for monitoring of granule moisture has to be improved.

Table of Contents

Chapter I	1
1 Introduction	
Chapter II	41
2 Materials and Methods	
Chapter III	54
3 In-line Monitoring of Particle Size in a Fluid Bed Granulator: investigations concerning positioning and configuration of the sensor	
Chapter IV	72
4 Influence of in line monitored fluid bed granulation process parameters on the stability of Ethinylestradiol	
Chapter V	90
5 Influence of filler excipients on stability of EE	
Chapter VI	105
6 Discussion and Conclusion	
Chapter VII	131
7 Summary	
Chapter VIII	138
8 Zusammenfassung	
Reference List	146
Appendix	158

Chapter I

---

1 Introduction

1.1 General introduction

Ethinylestradiol (EE) is the most commonly used estrogen substance in oral contraceptives¹. Homogenous drug distribution and stability of the compound in the formulation must be in focus during development of formulations containing this highly active and low dosed compound. EE is prone to oxidative degradation accelerated by temperature or photocatalysis. In the past, dosages of 0.05 mg EE were dispensed; nowadays the dose could be reduced to 0.015 mg. However, the advantage of lower doses of EE regarding the side effects and safety of patients is coupled with the problems regarding content uniformity and stability of EE in the pharmaceutical formulation. The most frequently used dosage forms for application of oral contraceptives are film coated and sugar coated tablets. Granulation is an important process step during the production of these dosage forms to improve the flow ability and tableting ability of pharmaceutical powders. Within the granulation technologies fluid bed granulation is frequently applied due to ability to perform the three granulation steps mixing, granulating and drying in one container. Further important but uncritical process steps during manufacturing of coated tablets is the tableting process and the coating process. Standard formulations for tablets containing EE are based on lactose as main filler excipient.

Within the fluid bed granulation process the unstable drug substance EE is exposed to high moisture during granulation and high temperatures during drying. The water added during the manufacturing process might influence the stability of drug substances due to acceleration of degradation reactions. Furthermore the moisture in granules might influence tensile strength and disintegration time of tablets manufactured from these granules. Consequently, increased moisture contents result on the one hand in accelerated degradation of EE and on the other hand hard tablets whereas dry granules cause enhanced stability of EE but lead to tablets of unsatisfying hardness. Regarding the moisture in the granules, a compromise has to be found to assure an acceptable hardness of tablets with as low as possible influences on the stability of EE.

The particle size of the resulting granules influences the flow ability and the homogeneity of the granules as well as the properties of the resulting tablets like hardness, friability and disintegration.

Due to the influence of granule moisture, particle size and stability of EE on the final dosage form these granule attributes are defined as critical quality attributes².

Fluid bed granulation is therefore a complex, multifactorial process where particle size and moisture of the granules are critical quality attributes. Their control during the process (in-line-monitoring) is an important element in process development and optimization (ICH Q8) as well as for monitoring in routine operation^{3,4}. An optimization of the process time might be possible which is important in particular for unstable drug substances like EE leading to a reduction of thermal stress.

According to the initiatives of the FDA and ICH³⁻⁵ current scientific methods should be applied to improve the quality of the drug product and efficacy of the production process. The use of process analytic technologies (PAT) for measurement of critical quality attributes during the process is important to assure the quality of the final product. PAT tools comprise chemical, physical, microbial and mathematical methods as well as methods for risk analysis³. They should ideally already be implemented during product development of a drug product⁶.

1.2 Definition of PAT

The FDA-initiative „Pharmaceutical cGMPs for the 21st Century: a Risk-Based Approach“ from 2002⁷ provided first of all an official definition of PAT. The targets of the FDA- initiative were:

- pushing the implementation of new technologies
- facilitating modern quality systems and management tools
- facilitating the utilization of risk based analysis for critical process steps

One result of this initiative was the publishing of the FDA-Guideline „PAT- A Framework for Innovative Pharmaceutical Manufacturing and Quality Assurance“³. Within this guideline PAT is defined as system for design, analysis and control of manufacturing by measurement of critical quality and performance attributes of raw material, in-process-material as well as processes for assurance of end-product-quality. Aim of this guidance is therefore the development of extensively analyzed processes to obtain a pre-defined quality of the manufacturing process. PAT includes the following tools³:

- multivariate tools for design, data acquisition and analysis
- Process analyzers (in-line, at-line or on-line measurement of biological, physical or chemical material attributes)
- Process control tools (should be established during product design and process development) include the following steps:
  - Identification and measurement of critical material and process attributes relating to product quality
  - Real-time monitoring of all critical attributes
  - Process controls to ensure control of all critical attributes
  - Development of mathematical relationships between product quality attributes and measurements of critical attributes
- Continuous improvement and knowledge management (data collection and data analysis over life cycle of a product)

Measurements should be installed for monitoring trends during the process to show individual process steps and changes within the process. They can be used for process monitoring, control and end-point determination³.

ICH Q8⁴ defines the concept of PAT as well. PAT-tools for in-line, at-line or off-line monitoring are integrated as elements of the control strategy in the Quality-by-design approach. The overall concept of ICH Q8⁴, ICH Q9⁵ and ICH Q10⁸ shows that PAT is a risk based approach for keeping the end-product quality. It includes methods of systemic development of formulation and process as well as process optimization and chemometric methods for multivariate data analysis.

Therefore PAT provides the possibility of continuous quality assurance, process validation and further development by using the gained correlations between process variables and product attributes⁹.

Figure 1-1 provides an overview on the regulatory requirements on PAT.

Figure 1-1: Regulatory roots of PAT according to⁹

1.3 Fluid bed granulation

1.3.1 Description

During fluid bed granulation powder particles are fluidized by air flow through the powder bed. Binder solution is sprayed on the fluidized powder bed using one or several nozzles. Within the process the powder particles are agglomerated resulting in granules of larger particle size¹⁰. The fluid bed granulation process is therefore classified as granule growth process resulting in single rounded agglomerates. The process steps mixing, granulating of the powder with binder solution and drying of the resulting granules are carried out in one pot making the process fast and efficient. Compared to mixer agglomeration the resulting granules are more porous which is advantageous for tableting of the granules and their dissolution.

Figure 1-2 presents the construction of a conventional fluid bed granulator. The fan mounted in the exhaust air pipes generates a suction that fluidizes the powder and brings each particle in a state of suspense where the gravity of each particle corresponds to the force resulting from the air suction on every single particle¹⁰. The particles are therefore freely agile and the powder bed turns to a state similar to liquid- the so called 'fluidisation'. The resulting appearance of the fluidized powder bed is like a boiling fluid¹⁰. Miscellaneous types of fluid bed granulators are available. A positioning of sensors for in-line measurement depends on the type of the used granulator. The experiments described in this thesis were performed using a Glatt GPCG 3.1. The principle of operation is comparable to the granulator depicted in Figure 1-2.

Figure 1-2: construction of a fluid bed granulator¹¹: 1 inlet air; 2 inlet air regulation; 3 filter; 4 heater; 5 sieve bottom; 6 product container; 7 deceleration zone; 8 spray nozzle; 9 fine filter; 10 shaker; 11 fan; 12 exhaust air

The fluid bed granulation process can be subdivided to the following process phases:

1. Mixing and warming: homogenizing of the raw materials by rising bubbles, increase of temperature in the powder bed due to heated inlet air. No change or slight decrease in product humidity.
2. Addition of API (Active pharmaceutical ingredients): Substances which are not inserted with raw materials in the product container can be sprayed on the heated powder bed as solution.
3. Agglomeration: Spraying of binder solution and therefore building of the granule particles initiated by formation of nuclei that are fixed by pendular or funicular bridges. Further growth results from coalescence or agglomerates, redistribution of broken fragments, abrasion transfer or snowballing¹². The spraying of water containing binder solution results in low product and exhaust air temperatures.
4. Drying of the granules: The resulting granules are dried in the warmed air stream until the defined granule moisture is reached. The product and exhaust air temperatures rise to the value of the inlet air.

The process of fluid bed granulation has several disadvantages, for example:

- The huge throughput of conditioned inlet air results in high energy consumption

- An increased risk of explosion due to electrostatic force – therefore additional protective precautions are necessary
- The fluidization due to the high air throughput might lead to increased decomposition of unstable substances

1.3.2 Granule attributes

This chapter reviews the properties of granules and summarizes their influence on the further processing. The particle size and particle size distribution as well as the granule moisture as CQAs investigated in this thesis are discussed in detail in chapter 1.6 and 1.7. By comparison granules manufactured in fluid bed granulation process are generally more loosely aggregated and more irregular in shape and appear therefore more porous, bulkier and more compressible than those produced using the high shear granulator¹³.

- Particle size and particle size distribution (see chapter 1.6):
The particle size influences further granule properties like bulk and tapped density, flow ability, specific surface, dissolution behavior. Demixing of granules can be eliminated due to a tight particle size distribution and fixing of small API-particles at larger particles of granules. The risk of contamination is reduced due to enlargement of particle size and therefore reduction of dust formation.
- Particle shape:
Granules produced in fluid bed are spherical shaped. The particle shape influences the flow ability.
- Porosity:
Granule particles are agglomerates of agglutinated powder particles. Air cells are incorporated within the powder particles. The porosity ε is defined as relation of pore (cell-) volume and total volume and is calculated from the corresponding densities. The porosity within the granule particles is defined as intraparticle porosity and is influenced by the properties of powder particles and the manufacturing process. The porosity is important for further processing of the granules (tableting). Less porous granules or larger bulk density are formed at higher rates of binder solution addition¹⁴.
- Particle surface:
The formation of agglomerates changes the particle surface and therefore influences the tableting behavior of the granules as follows^{10;11;15}:
  - Optimization of the surface, the wettability, the porosity, the solubility and the dissolution behavior

- Improvement of plastic deformability as requirement for tableting
- Improvement of mechanical stability of resulting tablets: the rough surface of granule particles results in hard tablets due to adhesion and friction of the particles upon compression
- Density (Bulk and tapped density):
The determination of density depends on the measurement of volume. The densities differ according to
  - a) Particle density/true density - cavities and intraparticle pores are considered as open space, measurement e.g.: helium-pycnometry
  - b) Apparent density - includes intraparticle pores and cavities, measurement e.g.: mercury-pycnometry
  - c) Bulk and tapped density - characterization of granules as bulk, properties as particle size, particle shape and interparticle connections are considered

Bulk and tapped density describe the ability of the granules to flow. They are used for calculation of Carr-index and Hausner-factor. Murakami et al¹⁶ show that the tensile strength of tablets is increased when granules have a loose bulk density. Increased average granule size reduces the particulate interactions due to a lower surface-to-mass ratio. Hence the granulation void spaces are reduced with a higher bulk density value. Increased product moisture due to increased rates of binder addition and lower inlet air temperatures leads to denser granules¹⁴. The defined flow ability due to an increased bulk density results in an improvement of dosing.

- Mechanical properties (tensile strength of granule particle, friability):
A sufficient mechanical stability is essential for further processing of the granules. Otherwise the stability should be moderate for tableting purposes. The friability of granules is decreased with increased rates of addition of the binder solution¹⁴. Less friable granules are formed by augmenting the wetting and penetration capabilities of the binder solution¹⁴.
- Flow ability:
Adequate flow ability is necessary for further processing of the granules. It depends on the particle size, the particle size distribution, the particle shape, the particle surface, the moisture and electrostatic charge. In general, fine powders (< 50 µm) appear to be cohesive with decreased flow ability whereas granules (> 300 µm) are free flowing. Beside direct measurement of the flow ability (e.g. angle of repose), the Carr-index and

the Hausner-factor determined from bulk and tapped densities also provide an indication for flow ability.

- Moisture (see also chapter 1.7):

The residual moisture in granules might on the one hand influence the stability of APIs and the further processing of the granules (e.g. sticking on tableting equipment and capping of tablets)¹⁰. Low moisture content might be responsible for insufficient mechanical stability of tablets. Hence the moisture determination in process as well as in the end product can be regarded as an important process control.

- Homogeneity:

The API should be distributed homogeneously in the bulk. An inhomogeneous distribution of the API across the particle size fractions might lead to demixing at further processing and transport.

1.3.3 Controlling of fluid bed granulation

Fluid bed granulation is a complex process where numerous variables interact and influence the attributes of the final granules. Below only some examples can be discussed. Due to the definition of particle size and granule moisture as critical quality attributes investigated in this thesis, these attributes are focused in the present section.

During granulation process the particle size and moisture of the resulting granules are mainly influenced by the droplet size of the sprayed binder solution, the product moisture and the product temperature during the granulation process^{10;17}. These process variables result from the input-variables spray rate, spray pressure of the vaporizing air, amount of inlet air and inlet air temperature. Davies and Gloor¹⁴ show furthermore that the position of the spray nozzle in proportion to the fluid bed has an influence. Further variables are listed in Table 1-1. During the drying phase the product moisture is decreased due to the continuous moisture delivery with the air stream. The drying process is therefore influenced by the inlet air temperature and the inlet air humidity.

Table 1-1 Variables influencing the fluid bed granulation and attributes of the resulting granules (modified from¹⁷ and¹⁰)

Attributes of raw materials	Variables granulation process	Variables drying process	Attributes of granules
• Particle size distribution • Wettability of the solid by the liquid • Solubility and degree of swelling in the binder solution • Binder concentration and viscosity	• Droplet size at spraying of binder solution • Pressure of vaporizing air • Spraying rate • Quantity of solvent • Air flow rate/ Bed fluidity • Inlet air temperature and Humidity • Equilibrium moisture and temperature in bed • Process time • Position of spray nozzle • Amount of powder in fluid bed granulator	• Inlet air temperature and humidity • Air flow rate • Process time	• Particle size distribution • Bulk density and porosity • Moisture content • Drug content uniformity across particle size distribution • Granule strength/friability

Schæfer and Wørts did extensive research concerning control of fluid bed granulation process^{12;18-21}. They found that the particle size in granules is influenced by droplet size and flow rate of the binder and is large at low inlet air temperature. An increased amount of binder resulted in a tight particle size distribution. The droplet size is the result of the mass balance between the spray air and the amount of binder in the spray nozzle. A small droplet size can be adjusted with a high spray pressure or a low spray rate¹⁰. The decrease in the average granule size with its corresponding increase in granule friability is attributed to the finer spray droplet formation of the binder solution as a result of increasing the proportion of

air to liquid in the atomization process. Furthermore, Davies and Gloor¹⁴ showed that the bulkiness of the granules manufactured at little air pressure is decreased.

An increased spray rate causes a larger droplet size of the binder¹³ and an increased free moisture in the product^{10;14;22} resulting in a larger particle size in the granules.

At defined spray rate, inlet air rate, relative inlet air humidity and the inlet air temperature influences the free moisture of the product during granulation: An increased inlet air temperature causes an increased removal of moisture within the exhaust air and therefore low moisture content during the granulation process. Free moisture during building up of the granules influences decisively the particle size of the product^{12;20;23}. A higher inlet air temperature during granule formation produces smaller, more friable granules¹⁴. On the other hand, granulation at room temperature may cause premature agglomeration of the powders due to over wetting by the binder solution¹⁴. An increase of inlet air temperature causes an increased product temperature when free moisture is removed from the granules and may result in a thermic decomposition of unstable APIs.

The more porous granules obtained at higher inlet air temperatures are due to the larger quantities of unprocessed material in the fluid bed that causes bulkiness of the products¹⁴. Granule size enlargement due to increased wetting capabilities of the binder solution results in denser granules while larger average size granules obtained through increased binder concentration result in less dense granules. Larger and denser granules formed at lower inlet air temperatures showed better flow properties¹⁴.

1.3.4 Implementation of PAT in the fluid bed granulation process

Due to the high number of process variables influencing the end product and regarding the requirements of the PAT initiative several studies focusing the optimization of fluid bed granulating process were performed using in-line sensors for measurement of particle size distribution and granule moisture as critical quality attributes. Laurencio et al²⁴ describe an entire quality by design experiment under variation of binder rate, inlet air temperature and inlet air rate during the process. For screening and optimization tests in pilot scale a Parsum-SFT-sensor was used for inline particle size measurement. In production scale additionally a MRT-sensor for inline moisture measurement was used. Herdling and Lochmann²⁵ describe the implementation of PAT in the production of solids. Their focus is set on the measurement of product moisture using NIR and MWR as well as particle size. Burggraeve presents an

overview on PAT in fluid bed granulation focusing on NIR methods for determination of PSD and moisture during granulation, acoustical methods and spatial filtering technology²⁶.

In the commonly used fluid bed granulation process PAT is already implemented by measuring process parameters like inlet and outlet air temperature as well as the product temperature. These parameters can be used for indirect measurement of granule moisture in terms of the Delta T method (section 1.7). Product moisture and particle size are potential quality attributes of the granules².

Investigations described in this thesis focus on the implementation of spatial filtering technology (SFT) and microwave resonance technology (MRT) in the fluid bed granulator for continuous in-line measurement of particle size and granule moisture during the fluid bed granulation process.

1.4 Model formulation

The formulations used in this thesis are based on microcrystalline cellulose with Ethinylestradiol as active substance. Table 1-2 provides an overview on the composition of the model formulation. The solvents used during granulation (water, ethanol) are not listed due to their removal from the granules during processing. Due to a possible lactose-intolerance of patients lactose was replaced by microcrystalline cellulose in this new formulation. The focus of this work was set on the implementation of in-line sensors for process monitoring during manufacturing of granules with this new formulation process with special consideration of the stability of EE. Hence, the following chapters depict the properties of EE and MCC.

Table 1-2: Composition of the model formulation

Substance	Functions in the formulation
Ethinylestradiol (EE, micronized)	active pharmaceutical ingredient (API) (see chapter 1.4.1)
Microcrystalline cellulose (MCC, Vivapur 101)	filler, binder, disintegrant (see chapter 1.4.2)
Maize starch	filler, binder, disintegrant
Pregelatinized starch (Starch 1500)	binder, disintegrant
Maltodextrine	binder
Magnesiumstearate	lubricant

1.4.1 Ethinylestradiol (EE)

1.4.1.1 Characteristics

EE (*19-Nor-17 α -pregna-1,3,5(10)-trien-20-in-3,17-diol*, $C_{20}H_{24}O_2$), developed in 1938 by Schering AG, is the estrogen substance most commonly used in oral hormonal contraceptives¹. EE is well characterized. Much knowledge on the substance is available in the pharmaceutical industry which is not published and therefore not accessible at all. EE has a molecular mass of 296.4 g/mol. Its pharmacological effect is akin to that of estrogen produced naturally in the body. Chemically, EE differs from estrogen concerning the ethinyl-side-chain in ring D of the steroid-structure (Figure 1-3).

EE is used in oral contraceptives and hormonal replacement therapy in concentrations of 20 µg / day to 50 µg / day at which 30 µg / day as single dose is most frequently prescribed. The most important effect is ascribed to the repression of ovulation¹. The lowest effective dose per day (15 µg) is used for repression of bone absorption in therapy of osteoporosis¹.

Figure 1-3: Structure of Ethinylestradiol (EE)

In development of formulations containing the high active and low dosed compound EE special attention must be paid on the homogeneity and stability of the drug substance. According to ICH Q1A degradation products must be analyzed and characterized in formulations.

1.4.1.2 Stability of EE

To date, published data on EE mainly addressed environmental questions e.g. removal from wastewater whereas little data is available on the stability of EE in pharmaceuticals.

The degradation of EE is an oxidation mechanism auto catalyzed by peroxide radicals. The main points of action for this autoxidation reaction are unsaturated bondings and highly condensed polymers like dienes and double bondings^{27;28}. For EE the degradation is autocatalyzed via the phenyl ring nearby the benzyl ring in the steroid structure²⁷. The leading degradation products are 6- α -hydroxy-EE, 6- β -hydroxy-EE, 9(11)-dehydro (DH)-EE, 6-oxo-EE²⁹⁻³¹ (Figure 4-1, Chapter 4.1, page 73). Due to the amount of degradation product below the identification limit of ICH Q3B³² in the registered products no qualification studies including clinically relevant adverse effects characterization were performed on the impurities. The degradation of EE is directly linked to atmospheric oxygen: Ekhato et al³³ demonstrated that the degradation in oxygen atmosphere is increased compared to degradation in argon atmosphere. Further studies on forced degradation of EE in acid and

alkaline as well as hydrogen peroxide (4 h at 80 °C, in the dark) showed that the highest degradation rate of 56.8 % was found in hydrogen peroxide followed by alkaline medium³⁴.

Beside the induction via oxygen as described above, thermally³¹ and photo catalyzed^{35;36} induction are possible as well.

The photocatalyzed degradation of EE continues slowly and with a small amount of degradation products corresponding to quinone methide and 1,2-quinone derivatives, ring-monohydroxylation photoproducts and photoproduct arising from hydroxylation onto the saturated ring linked to the aromatic one³⁷. Sedee and van Henegouwen³⁶ dedicated hydroperoxides. EE was found to be stable in sunlight at 280-780 nm³⁶. However in tablets formulated with dyes these organic colorants might act as photosensitizer absorbing energy and transferring it to the EE molecules. With the presence of oxygen a photodynamic process starts. EE reacts to peroxides that catalyze the further degradation progress²⁷. Due to the photosensitive effect of organic colorants they were replaced by iron oxides in the formulations³⁶. Furthermore, the photocatalyzed degradation might be clinically relevant concerning photo-allergic reactions: photo-oxidation of phenolic steroid structure leads to irreversible binding to protein or other endogenous molecules³⁶.

In this thesis the stability of EE in pharmaceutical solids (granules and tablets) as a function of granulation process parameters is investigated by storage of the formulation in climatic chambers with conditions corresponding to the regulatory background according to ICH Q 1A (i.e. 25 °C/60 % r. h. and 40 °C/75 % r. h.). After storage the main degradation products are quantified using HPLC.

1.4.1.3 Influence of water on the API stability in solid dosage forms

As already mentioned granule moisture is an important CQA that might influence the stability of APIs. This section therefore examines the interactions of water with compounds. The following mechanisms catalyze the degradation of active substances in solid dosage forms:

- Amorphous fractions: A low percentage of amorphous regions in drugs might be generated mechanical. These regions have greater mobility and lack crystal lattice stabilization energy. As a result oxygen permeability and solubility will be higher. Greater mobility and higher oxygen concentrations present in amorphous drugs also facilitate electron transfer to oxygen. The amorphous form of a compound is higher in

energy; hence, the rate of reaction will be faster³⁸. Such amorphous regions can be produced by spraying the drug substance in the fluid bed³⁹.

- Solid solution: Excipients can potentially solvate the drug either by bringing in low levels of moisture or keeping water around the API. This can result in amorphous regions of the API respectively in deprotonating and therefore an increased reactivity^{38;40}.
- Reactivity of the excipients: Excipients might be a source of oxidants and metals. Furthermore they can be involved in generating mobile oxidative species such as peroxy radicals, superoxide and hydroxyl radicals³⁸. Furthermore Mahajan et al³⁹ found that the oxidative degradation is increased at low concentrations of drug substance due to a high interaction rate of drug substance with excipients that could deal as reactant.

This thesis focuses on water contained in the formulation as critical material attribute. Hence, the influence of water on the stability of drug substances will be subject of the following remarks.

Ahlneck and Zografi⁴¹ discussed the molecular interactions between water and solids: Amorphous structures respectively amorphous layers at particle surfaces adsorb small amounts of water ("hot spots"). The water decreases as plasticizer the glass transition temperature. Consequently the molecular mobility of these structures and correspondingly the chemical reactivity are significantly increased. Therefore water can act as both chemical reacting agent (hydrolysis and oxidation) and plasticizer.

The Leeson-Mattocks-Modell⁴⁰ describes water existing as a layer around the particles containing the drug substance in a saturated solution. This solution increases the mobility and reactivity of the drug substance. Therefore the total degradation rate is affected by the degradation of the solvated part of the drug substance. Each degraded API-molecule is substituted by a new one.

Summarizing, water in the formulation affects the stability of drug substance as follows:

- Water acts as reactant by hydroxylation of the drug substance and increasing its reactivity³⁸
- Water acts as plasticizer by mobilization of small amounts of drug substance in the water layer on the particle surface hence increasing the reactivity of drug substance^{39;40;42}

1.4.2 Microcrystalline Cellulose

1.4.2.1 Characteristics

Microcrystalline celluloses (MCC) were developed in the 1950s⁴³. MCCs are inert and stable excipients used as flow regulator, binder and disintegrant. MCC provides optimal characteristics for tableting purposes and is therefore the mostly used binder for direct tableting. The structure is presented in Figure 1-4. MCC is described as a white fine or granular powder, practically insoluble in water, in acetone, in ethanol, in dilute acids and in a 50 g/l solution of sodium hydroxide with a loss on drying of the powder of maximum 7 %⁴⁴. During tableting MCC undergoes a plastic deformation⁴⁵ but also acts in an elastic manner⁴⁶.

Figure 1-4: Structure of microcrystalline cellulose

MCC is produced from purified alpha-cellulose extracted from wood⁴⁵. The amorphous structures normally connecting the naturally existing microcrystalline structures of cellulose are split by acid hydrolysis. This process results in cellulose with a so called “level-off degree of polymerization” (DP) of 200 to 300- meaning 200 to 300 monomeric units in a polymer. The microcrystals (diameter of 1 μm -10 μm) existing in a fibrous and packed structure run out of this structure by mechanic shear in a dilute suspension and are dried using spray drying or in air stream. Partly the microcrystals form agglomerates. By variation of the hydrolysis, shear and drying conditions particle size and moisture of the product can be adjusted. Hence different qualities are available. Differences between the MCC products available have been examined and discussed in several studies. It could be demonstrated with Emcocel® of different process steps and raw material sources that the source of the

original cellulose has a larger effect on the crystallinity than the manufacturing process⁴⁷. The study also showed that the crystallinity has no influence on compressibility and flow ability.

Beside the manufacturing parameters the quality of the wood used for manufacturing influences the quality of MCC: A further study⁴⁸ investigated the influence of sources from different countries on the characteristics of MCC by means of chemical investigations (amount of lignin and cellulose), crystallographic investigations (XRPD, NIR, Raman), physical investigation (PSD, SEM, flow ability) as well as tableting behavior (direct tableting, compressibility, dissolution). Differences within the used type of wood (hardwood/softwood) influenced the amount of lignin. Only small differences were found for the equilibrium moisture content that influenced heavily the mean yield pressure due to the particle deformation as dominant densification mechanism for MCC. Indeed, it was demonstrated that the sample with the largest crystallinity showed the smallest equilibrium moisture. Significant differences were measured for compressibility. In view of the close correlation with mean surface diameter, these differences in compressibility were attributed to the variation in particle size. Correspondingly the MCC with the smallest PSD showed poorer flow ability than the other brands. Ardizzone et al⁴⁹ showed for two samples of Avicel PH102 from different countries of origin in SEM pictures that the particle morphology differed. One sample depicted large aggregates of almost spherical geometry whereas the other sample consisted of finely subdivided particles with irregular geometry.

In this thesis predominantly MCC of type Vivapur 101 was used as excipient for wet granulation processes. Table 1-3 provides an overview on the properties of MCC-qualities used in this thesis.

Table 1-3: Characteristics of MCC (Source: <http://www.jrspharma.com>, <http://www.fmcbiopolymer.com>)

Name	Manu-facturing (type of drying)	Average particle size (µm)	Particle size determination	Bulk density (g/cm³)
VIVAPUR® 101	Air stream	65	Laser diffraction	0.26 - 0.31
VIVAPUR® 105	Air stream	25	Laser diffraction	max. 0.26
VIVAPUR® 12	Air stream	180	Laser diffraction	0.30 – 0.36
Avicel PH 102	Spray drying	100	Not remarked	0.28 – 0.33

Haware et al⁵⁰ compared Avicel and Vivapur MCC qualities as well, certainly with declaration of the used types. For this reason a direct comparison between Avicel PH 102, Avicel PH 101 and Vivapur 101 can be done. They analyzed PSD, SEM, densities, flow ability and tablet ability. SEM-pictures (Figure 1-5) of Vivapur 101 and Avicel PH 102 showed that the particles are similar by size, however the particles of Vivapur 101 are more fibrous. Vivapur 101 showed low porosity throughout the entire compression cycle and made slightly stronger tablets compared to Avicel PH 101⁵⁰.

Avicel PH 102

Vivapur 101

Figure 1-5: SEM pictures of Avicel PH 102 (magnification x 270) and Vivapur 101 (magnification x 250)⁵⁰

1.4.2.2 Influence of water on properties of MCC

During fluid bed granulation MCC is getting in close contact to water. Water in the formulation is an issue that has to be considered regarding tableting properties and the stability of the formulation (see section 1.7). The knowledge about the state and amount of water is important to estimate how much water exchanges from gas phase or capillary phase and may influence the drug substance stability. Hence the following chapter discusses the interactions between MCC and water from molecular and macromolecular point of view as well as the influence on the tableting behavior.

Water vapor sorption by MCC appears in different states⁵¹. It could be demonstrated by means of water-sorption isotherms that water penetrates in the polymer structure of MCC⁵². The following general model was presented for celluloses and starches⁵¹:

- At low relative pressures water is bound directly to available anhydroglucose units in amorphous regions of cellulose with a stoichiometry of one water molecule per anhydroglucose unit.
- At intermediate relative pressures (up to 0.6) polymer-polymer hydrogen bonds are crushed resulting in an increase in primary binding sites available and allowing water to begin to bind to other water molecules already bound to anhydroglucose units
- At higher relative pressures more primary binding sites become available; water can now also bind to other water molecules including those not bound to primary sites.

In this model therefore at least two distinct thermodynamic states of water can exist 1) water directly bound to one hydroxyl group per anhydroglucose unit and 2) water bound to other water molecules (like bulk water)⁵¹. There is clear evidence that water also exists in intermediate states or states involving water not bound to the primary site but still influenced by the chemical structure of the anhydroglucose unit. This intermediate state water can be up to three times the value of water bound to the polymer. Furthermore some water molecules may be associated with starch or cellulose in metastable states relative to pure water or trapped in the polymer matrix⁵¹. Faroonsarng and Peck⁵³ showed furthermore that water exists as a monolayer on the surface of MCC and reacts there with the so called “active sites” at anhydroglucose molecules.

Most of water bound to MCC is situated within the porous structures of the particle⁵⁴. These internal structures represent 95 % of the surface of MCC that may react to water. The water that reacts to the amorphous structures, causes a decrease of the glass transition temperature and hence, an improvement in deformation⁵³⁻⁵⁵. The sorption sites on the surfaces exist in the glassy state (amorphous surfaces). By adsorption of water and therefore the decrease of glass transition temperature these areas are transferred into the rubbery state⁵³. Investigations by means of NMR with Avicel PH 101 showed that at high moisture content (50 % r.h.) the crystallinity increases⁵⁶.

Khan et al⁵⁷ discussed the water adsorption to MCC (Avicel PH 101) from macromolecular point of view. The cellulose microcrystals are packed together in form of cylindrical micro fibrils where the cellulose chains are oriented axially and tightly packed in the crystalline core. They are more loosely packed in the outer sheath that contains more amorphous cellulose. Up to moisture of 3 wt. % water has practically no effect on the specific volume of MCC, indicating that the water molecules are being accommodated in the spaces between cellulose chains. By moisture above 3 wt. % a swelling of micro fibril causing an increase in

volume could be shown. This could also be demonstrated in the tablets with MCC of different moisture content: the micro fibrils align in the cavity during the tableting process. Therefore an increase in the height of tablets was determined.

1.5 α -Lactose Monohydrate

In the past, α -lactose-monohydrate (lactose) was the most frequently used main filler excipient for tablets made from granules manufactured in fluid bed granulation processes⁵⁸. Due to frequently appearing lactose intolerance the lactose should be replaced in the standard-formulation. In this thesis the granulation process for a new model formulation based on MCC as replacement for lactose is investigated. For comparison with the new main filler excipient (MCC) lactose was used in different tests. Therefore this section introduces the main properties of lactose.

In α -lactose-monohydrate the galactose and glucose moieties are connected together through $\beta(1,4)$ -glucosidic linkage (O- β -D-galactopyranosyl-(1-4)- α -D-glucopyranose). The structure is presented in Figure 1-6. The crystals are available in the so called Tomahawk structure. Lactose is produced from bovine milk and milk products. It is a white, crystalline powder that is easily soluble in water and practically insoluble in ethanol. It is stable in the presence of air. The water uptake from air is negligible. Milled lactose was used for the present tests. It could be demonstrated that the milling of lactose causes approximately 1 % amorphous structures on the surface of the crystals⁵⁹⁻⁶¹. These amorphous structures recrystallize at a relative humidity of more than 20 %⁵⁹. Crystals from lactose are hardly deformable and show therefore less ability for binding in tablets⁵⁸. This makes the use of a binder necessary.

Figure 1-6: Structure of α -lactose monohydrate

In the standard formulation for tablets containing EE Pharmatose 200 M was used as filler excipient. The tests described in this thesis should investigate the stability of EE in connection to the contact with the common main filler excipient (lactose) and the new main filler excipient (MCC). For this purpose binary mixtures were produced containing two grades of lactose (Pharmatose 450 M and Pharmatose 130 M). These grades were chosen to

ensure a range of different particle size distributions around the standard lactose (Pharmatose 200 M): one lactose with a smaller particle size distribution (Pharmatose 450 M) and one lactose with a larger particle size distribution (Pharmatose 130 M). Table 1-4 provides an overview on the particle size of the used lactose qualities. Due to the different particle size distributions of the used lactose grades the particle surface and therefore the contact area with EE should vary. For comparison purposes, the standard lactose Pharmatose 200 M is listed in the table as well. Particle sizes from laser diffraction determined during tests in this thesis will be presented in the results of this thesis.

Table 1-4: Particle size distribution of the used lactose –grades⁶²⁻⁶⁴

Lactose grade	Testing method	Particle size distribution
Pharmatose 130 M	Sonic sifter	<75 µm: max 50 % <180 µm: 80-90%
Pharmatose 200 M (Standard)	Air jet sieve	<45 µm: 50-65 % <100 µm: min 98 % <150 µm: 96 % <250 µm: 99-100 %
Pharmatose 450 M	Air jet sieve	<45µm: min 90 % <63µm: min 98 % <150µm: 100 %

1.6 Particle size determination in granules

As stated by Yu² and already discussed in this thesis particle size is a critical quality attribute during fluid bed and drying granulation process. Particle size influences flow properties, homogeneity and tableting behavior like tensile strength, uniformity of mass and friability in a crucial degree^{17;65-67}. Small particles cause an increase in tensile strength in tablets, work of compression and Hausner-Factor⁵⁰.

Ph. Eur. specifies the classification of powder fines in two paragraphs: Ph. Eur. 2.9.12⁶⁸ classification based on sieve analysis and Ph. Eur. 2.9.35⁶⁹ cumulative distribution with volumetric basis. This paragraph⁶⁹ furthermore includes a definition of parameters describing a particle size distribution (e.g. x_{10} , x_{50} , x_{90}) and a definition of types of cumulative distributions (number, length, area, volume). The granules produced during the investigations for this thesis can be classified according to Ph. Eur. as very fine to fine powder.

Several methods for determination of particle size were described in literature⁷⁰. The measurement methods differ according to counting and quantity measuring methods. Quantity measuring methods are e.g. sieve analysis and laser diffraction. Counting methods are e.g. microscopic and coulter counter analysis

According to Ph. Eur. sieve analysis is the standard procedure and is therefore described in Ph. Eur. 2.09.38⁷¹ and ICH Q4B Annex 12⁷². Sieve analysis is intended for use where at least 80 % of the particles are larger than 75 μm ⁷¹. Beside sieve analysis, Ph. Eur. describes optical microscopy (Ph. Eur. 2.9.37) and laser diffraction (2.9.31) as well. Laser diffraction was used as off-line particle size determination in this thesis.

With regard to the PAT-initiatives and the possibility of real-time-release of granules concerning the particle size distribution several methods for continuous in-line particle size measurement were investigated. Beside Spatial filtering technology described in chapter 1.6.1 of this thesis the methods listed in Table 1-5 are mentioned in literature.

Table 1-5: In-line technologies for measurement of particle size distribution

Method	Measuring principle	Citations
Focused Beam Reflectance Measurement (FBRM)	Determination of particle size from chord length by analysis of the light reflected from particles	73-75

Method	Measuring principle	Citations
Acoustic emission	Measurement and analysis of acoustic signals on the basis of unstable fluidization of spherical particles (determination of particle size and granule moisture)	76-79
Image Processing Systems (CCD), SAY-3D	In-line evaluation of digital pictures of granule particles in the fluid bed	80;81
NIR	Analysis of light scattering from particles: increased scattering parameter and decreasing penetration depth at decreasing particle size. Due to the decreased penetration depth the absorption is reduced and a parallel translation of the spectra referring the intensity results.	82-86
Spatial filtering technology (SFT)	Determination of particle size as chord length from particle velocity in front of an optical array	See section 1.6.1

Tok et al⁸⁷ compared the in-line measured particle size using NIR, FBRM and acoustic measurements. They described that the measuring windows of the NIR as well as the FBRM sensor were blocked. This disadvantage was important especially during measurement with NIR: The determination of the nucleation-phase during granulation was not possible. During drying phase NIR and FBRM depicted advantages compared with the acoustic measurement. Summarizing, they could show that only FBRM measurement was independent from granule moisture.

1.6.1 Spatial filtering technology for in-line particle size determination

The spatial filtering technology (SFT) is based on the determination of the velocity of an object by observing it through a spatial filter in front of a receiver⁸⁸ It was described by Petrak^{88;89}. The measurement is performed by using a sensor for in-line particle size determination which is placed in the fluid bed granulator during the granulation process. During measurement the velocity as well as size of particles passing through the measuring volume is determined (Figure 3-1). The spatial filter consists of a periodic alignment of optical fibers in an array and a “c”-individual fibre. A projection of a moving particle on the optical array occurs when the laser beam in the measuring volume is interrupted. This projection

triggers a signal with the frequency „ f_0 “ on the fiber optic array (spatial filter) and an impulse at the “c”-individual fibre. The particle velocity „ v_p “ is determined from the frequency, the interval of the special filter “g”, as well as the magnification of the imaging system “M” (Equation 1^{88;90}). The chord length of the particle “x” is determined from the impulse time “ Δt ” at the “c” individual fibre, the current particle velocity “ v_p ” and the diameter “d” of the individual fiber (Equation 2). Hence the statistical particle diameter “x” is directly determined as chord length in direction of the optical array⁹¹.

$$v_p = f_0 \times g / M \quad (\text{Equation 1})$$

$$x = v_p \times \Delta t - d \quad (\text{Equation 2})$$

For evaluation of the results the chord lengths are classified by size during measurement. Based on these data the cumulative size distribution $Q_0(x)$ as well as the density distribution $q_0(x)$ can be calculated.

Silva et al⁹² compared several in-line particle size measuring methods like SFT, FBRM, acoustic and optical methods with laser diffraction. They found comparable particle size measured with SFT and laser diffraction for several materials. However, x_{90} particle size measured with SFT was increased compared to laser diffraction. This result was justified with coincidences due to high particle loadings which cause overlapping of particle projections in the in-line sensor. Accordingly, increased particle size affecting x_{90} was measured. This thesis was confirmed by measurements at high and low sensor loading. All experiments were conducted off-line applying the samples with vibration feeder to the SFT-sensor.

An accurate calibration with $R^2 = 0.97$ for off-line SFT-sensor was determined in experiments⁹³. However, differences were detected compared to sieve analysis that could be attributed to variable alignment of particles in the sensor and the different evaluations of the measuring methods (numeric vs. volumetric)⁹³.

SFT was used to evaluate the influences of granule parameters in context of statistical experiments based on multivariate data analysis tools for particle size distribution⁹⁴. Furthermore the use of SFT for optimizing the fluid bed granulation process was described⁹⁵⁻⁹⁹. Incidents during the granulation process (e.g. defects of spray guns) were visible by the use of SFT¹⁰⁰. A control strategy for prediction of granule density could be established by use of SFT in combination with NIR to enable the adjustment of granule density via variation of process parameters during the drying process⁹⁵. A further study established a model for bulk

and tapped density, consequently the Hausner-factor, on the basis of in-line particle size determination with SFT as well as in-line measured product-temperature evaluated by multivariate data analysis¹⁰¹. A review⁹⁰ summarizes applications of SFT in the pharmaceutical industry.

The installation of the SFT-sensor in the fluid bed granulator in the context of qualification of the measurement system is part of this thesis. Hence the literature was surveyed regarding the positioning and installation of the sensor in the fluid bed granulator. The following information could be found:

- GPCG 1; height of 20 cm, 5 cm distance to granulator wall⁹⁶
- WSG 5; height of 45 cm^{93;97}
- Hüttlin HKC 200DJ: installation on product container²⁴

Up to now only Schmidt-Lehr⁹⁹ gave exact information on installation of the sensor in the granulator (angle and sensor adjustment). Hung⁹⁴ remarks that further studies on this issue are necessary. Germer¹⁰² could demonstrate that the installation of the sensor in the granulator has no effect on the granulation process and the properties of the resulting granules.

1.7 Moisture measurement

As already mentioned in previous sections of this thesis moisture is an important parameter influencing the properties of tablets. The interactions of water with MCC as well as the drug substance EE were already discussed in the relevant sections 1.4.1.2 and 1.4.2.2. Schæfer and Wörts²⁰ show that moisture is crucial for granule growing during granulation process. Carstensen⁴⁰ elucidates in a review article the influence of water on formulations. Moisture influences the compressibility of granules and the stability of tablets in the following manner:

a) Effect of moisture on the flow properties of powders:

- On the one hand adsorbed water film lubricates the particles and reduces the frictional force that opposes the relative motion of the particles. On the other hand water increases the cohesion of particles by formation of liquid bridges possibly resulting in formation of a hard cake.⁵⁴

b) Effect of moisture on processing of powders

- Water might accelerate degradation reactions of susceptible drug substances due to hydrolysis⁴⁰, see section 1.4.1.3
- The presence of excessive moisture at moderate to high compression force decreases the compact strength by decreasing the micro irregularities of the particles and by increased elastic recovery after ejection when compressed beyond true density⁵⁴.
- The adsorbed water film decreases the particle surface energy and thus decreases the adhesion of the tablet to the die wall. In addition the water film acts as a low viscosity lubricant. It allows for a greater fraction of the applied force to be transmitted through the compact to the lower punch and reduces therefore the variation of density in the tablet. It results furthermore in a decrease in the ejection forces and a decrease in the forces lost to the die wall⁵⁴.
- The moisture has a solvent effect eliminating surface cracks and irregularities in the crystals. This increases the crystals resistance to fragmentation and decreases the crystal surface energy which therefore decreases adhesion between particles⁵⁴.
- Moisture facilitates plastic deformation of microcrystals to allow close contact and hydrogen bonding between particles. It acts as a plasticizer and reduces the yield point and the elastic recovery during compaction⁵⁴.
- Increased water content reduces the porosity of tablets hence prolonging the dissolution time of tablets⁴².

Malamataris et al¹⁰³ investigated the influence of water with several excipients for direct compression (MCC amongst others). They showed that weakly bound water that exists in monomolecular layers increases interparticular bonding whereas adsorbed bulk water increases the plasticity and impairs interparticular bonding. For this reason tensile strength reaches a maximum and begins to decrease as the moisture content is about double that corresponding to a tightly bound monomolecular layer and therefore becomes bulk water.

This reflection of influence of water on the properties of the formulation shows the necessity to identify and monitor the optimum water content for each formulation.

Different types of water according to bonding strength and type of bonding can be distinguished:

- Adhesive water: existing at the surface of granule particles as well as in large pores and cavities. The vapor pressure corresponds to that of fluid water.
- Capillary water: adhered in capillaries. In hydrophobic substances it corresponds to the vapor pressure of fluid water. In hydrophilic and hygroscopic substances the vapor pressure is reduced.
- Swelling water: is a component of the substance and penetrates it completely. The bonding is relatively tight.
- Constitutional water or crystal water: is the most tightly bound type of water. It can normally not be removed because the degradation of the substance would be connected to it.

The water content in granules can either be determined as loss on drying (LOD) that is according to Ph. Eur. related to the mass of the analysed substance (Equation 3) or as water content that is related to the mass of the dried substance (Equation 4).

$$LOD [\%] = \frac{\text{mass of water in the sample}}{\text{total mass of the sample} \times 100} \quad (\text{Equation 3})$$

$$\text{water content} [\%] = \frac{\text{mass of water in the sample}}{\text{mass of the dried sample} \times 100} \quad (\text{Equation 4})$$

Due to the different types of bound water drying proceeds in different steps: The drying starts on the surface of the material until the adsorbed water there is completely evaporated. The process is sustained in the capillaries because water in the particles diffuses to the surface. Hence the drying front shifts from the surface to the inside of the particles. For this reason the further drying process depends on the thickness of the dried layers as well as their

properties like thermal conductivity and vapor permeability. Drying can therefore be classified according to its chronological progress in three steps (Figure 1-7):

1. 1st section: loosely attached surface water and water from large capillaries evaporates with a high rate
2. 2nd section: residual surface and capillary water evaporates with a decreasing rate
3. 3rd section: drying of moisture from small capillaries and cavities from inside the particles therefore the evaporating rate reaches a minimum

Figure 1-7: Stages of drying in the product¹¹

Drying of granules depends on the following parameters:

- Product temperature (optimum drying temperature 35 °C - 40 °C⁵⁸)
- Relative humidity of inlet air
- Air circulation
- Particle size and layering of the product
- Character of the granules (amorphicity, hygroscopicity, lipophily, aerophily)
- Bonding of water

Several principles can be applied for drying of materials such as convection, contact and radiation. In this thesis drying in fluid bed was used which can be classified as convection drying where heat is applied to the granules by a moving gas. The heat exchange as well as drying occur from outside to inside the product whereas the moving gas absorbs the water

and transports it away from the product. The product temperature on the surface is increased compared to inside. When the granules are dry, inlet as well as outlet air temperature and humidity are equal⁵⁸.

Granule moisture is a critical material attribute influencing crucially further processing of the material as well as the stability in the final product. Hence continuous monitoring of the drying process by direct or indirect determination of granule moisture is an important process control. For indirect determination the inlet or outlet air temperature respectively inlet or outlet air moisture or the product temperature are monitored. One example for indirect measurement is the so called Delta T- method (ΔT - method) already described in literature. Schæfer and Wørts²⁰ describe the measurement of ΔT calculated from temperature of the product at the end of drying and at the end of binder spraying as stop criterion for the drying process. Alden et al¹⁰⁴ and Lipsanen et al¹⁰⁵ modified and improved the method.

Direct measurement methods are for example the determination of loss on drying as thermogravimetric procedure according to Ph. Eur. 2.02.32 or the determination of total water content (including crystal water) by Karl-Fischer-titration as analytical procedure according to Ph. Eur. 2.05.12. Both methods are suitable for in-process-control measurement. Loss on drying was used as in process control used in the investigations for this thesis. A continuous monitoring of the entire process as defined by PAT and Real-time-Release is not possible with these methods due to the testing time needed for each individual analysis.

Near-infrared spectroscopy (NIRS) and acoustic measurement as well as microwave resonance technology (MRT) are useful methods for continuous process monitoring in terms of in-line measurement. Within these three methods NIRS is already well established in the pharmaceutical industry. Reich¹⁰⁶ gives an overview on the measurement principle of NIRS, the approach for analyzing the resulting data and the application in pharmaceutical technology. The measurement with NIRS provides advantages like the non-invasive and non-destructing measurement¹⁰⁷, independence from process variables^{83;108} and the possibility for simultaneous measurement of particle size and granule moisture⁸³. Nevertheless during measurement with NIRS disadvantages as clogging of the measurement window¹⁰⁹, interference of particle size and granule moisture^{83;109} and the complexity of particle properties in the spectrum^{82;110} were depicted. Furthermore a manipulation of the measurement by temperature during the process might occur¹⁰⁸. In terms

of development purposes the necessity of chemometric methods for evaluation of the moisture from NIR signal is complex and therefore detrimental^{111;112}.

Due to the mentioned disadvantages of NIRS for determination of product moisture its use in field of development needs high efforts. For this reason MRT was used during investigations for this thesis as in-line monitoring of product moisture during granulation and drying processes. The following section provides an overview on the basics of this method.

1.7.1 Microwave resonance technology for in-line moisture measurement

Moisture measurement by means of microwave resonance technology (MRT) was already used routinely for several decades in the food as well as the animal feeding industry. Schlemm et al¹¹³ describes moisture measurement after installation in wheat drying equipment within the calibration range of 7 % to 29 % in relation to the moist product.

The measuring principle of MRT is based on the interaction of water molecules according to their great dipole moment with the electromagnetic field. This great dipole moment (Figure 1-8) is generated by the inhomogeneous loading in the water molecule due to the high electronegativity of the oxygen atom compared to the hydrogen atom (oxygen: 3.5, hydrogen: 2.1). The resulting dipole moment is 1.844 Debye. The permittivity of 80.4 (20 °C) is increased compared to other organic-chemical compounds. This high permittivity and the small masses of the water molecules result in their alignment in accordance to the polarity of the changing electromagnetic field at voltage application (e.g. capacitor).

Figure 1-8: Loading in water dipole molecule¹¹⁴

The alignment of the molecules increases proportionally to the frequency of the applied electromagnetic field until the upper limit-frequency of 20 GHz for water molecules¹¹⁵. Above this frequency the water molecules are not able to follow the electromagnetic field. This frequency is therefore named “dipole relaxation frequency”. Each turnaround of the water molecules is associated with a loss of energy which gets disposed from the electromagnetic field and correlates with the total amount of water molecules in the material¹¹¹.

The loading of the microwave resonator system with moist material and application of an electromagnetic field results in an alignment of the water molecules. Compared to an empty resonator the resonance frequency is reduced due to the buffered energy and the band width is broadened due to increased electric loss caused by the uptake of energy for the alignment of the water molecules (Figure 1-9 A)¹¹⁶.

The decrease of frequency Δf as well as the broadening of the band with ΔBW depend on the moisture content ψ and the total mass m_{tot} of the material respectively the density ρ in the field of resonance. However, examinations showed that the ratio $\Delta BW/\Delta f$ is independent from the mass and therefore a function of the moisture^{116;117}.

$$m_{tot} = m_w + m_d \quad (\text{Equation 5})$$

m_w = mass of water in the material

m_d = mass of the dried substance

$$\rho = \frac{m_{tot}}{V} \quad (\text{Equation 6})$$

$$M(\psi) = \frac{\Delta BW(\psi, m_{tot})}{\Delta f(\psi, m_{tot})} \quad (\text{Equation 7})$$

$M(\psi)$ =moisture function

A)

B)

Figure 1-9: Measuring principle of MRT A) Microwave resonance curves: The resonance frequency decreases and the band width increases due to increasing water content (line: empty resonator, dotted line: resonator with material)¹¹⁸ B) Behavior of the resonator at varying moisture contents and mass fractions (ΔBW : change in band width, Δf : change in frequency)¹¹⁶

The moisture function depends on the nature of the measured material. Hence a calibration specifically for each material is necessary. The determination of the material mass via the decrease of the resonance frequency is possible after calculation of the material moisture. This two-parameter measurement of mass and moisture is possible in the moisture range of 0.5 % to 25 %¹¹⁶.

Figure 1-9B depicts the elimination of the connection between the density and the two parameter measurement. Each measurement point (ring) corresponds to the moisture content at different material densities. Therefore the linear slope is independent from the material density. It is therefore characteristic for the corresponding moisture content. The microwave value can be calculated from the linear slope.

The sensor should be installed in the product container in the height of the sampler to assure a constant loading with material^{111;112}.

The microwaves penetrate the material. Therefore a complete measurement of the physically bound water in the product is possible. MRT measures no crystal water¹¹⁸. The penetration depth is increased compared to NIR¹¹⁹ standing for an advantage for the in-line monitoring. The band width for measurement depends on the temperature due to energetic losses on metal walls and surfaces¹¹⁸. The intensities of <10 mW used for measurement have no influence on the stability of the product¹²⁰. The resonance frequency of the sensor is around 2.5 GHz¹¹⁸.

A good correlation to off-line moisture measuring methods like LOD/IR could be found for moisture ranges up to 10 %^{115;121}.

1.8 Aim of the Thesis

Fluid bed granulation has been used for decades for the production of granules. As mentioned before, it is a complex manufacturing process with different key-parameters influencing the critical quality-attributes of the final granules (see Table 1-1). Characterization of the granules quality attributes such as particle size, compressibility and flow ability as well as end-point determination via granule moisture were performed as in-process-controls respectively end-point controls. For in-process- and end-point controls the granulation process has to be stopped for sample drawing meaning an intervention of the process and potentially influencing the product quality attributes. Especially the processing of a low dosed steroid hormone as EE, that is known to be prone to oxidative degradation²⁷, is challenging: firstly the stability and homogeneity of the drug substance in the final dosage form has to be ensured and secondly opening the granulator for sample drawing might lead to a contamination of the employee due to the toxicological status of EE as carcinogen substance. Recent research focussed on the use of in-line continuous technologies for optimization of fluid bed granulation processes²⁶. The in-line measurement is an important part of the PAT - approach of the FDA and ICH^{4;7} to improve quality of pharmaceutical products. One main goal of the implementation of PAT is the real-time-release of the dosage form in the manufacturing process³ making an intervention in the granulation process for sample drawing redundant.

The present thesis aims to develop an effective and mild granulation procedure for the handling of EE as unstable low dosed steroid hormone. To this end the influence of the process variables (key parameters) drying time, drying temperature and spray regime on the critical quality attributes of the granules (stability of EE, particle size and granule moisture) are investigated (Figure 1-10).

Figure 1-10: Key parameters and critical quality attributes discussed in the thesis

The stability of EE in the resulting granules respectively tablets as a function of key parameters is analyzed and evaluated by investigation of its main degradation products. To this end we used a new model formulation based on MCC as main filler substance.

With respect to the requirements of FDA and EMA^{4;7} to use process analyzers for control of material attributes, sensors for continuous in-line monitoring of the critical quality attributes particle size (Spatial filtering technology, SFT) and granule moisture (microwave resonance technology, MRT) during the entire fluid bed granulation process are to be implemented during the investigations for this thesis. PAT-monitoring and later control of the process using the sensors is important in particular for this type of formulation. It is assumed that the current used end-point determination of granule moisture via loss on drying as well as the determination of particle size via sieve analysis can be replaced with real-time-release using the in-line technologies. Furthermore it is hypothesized that by utilization of these in-line monitoring measurements the production of a stable formulation is possible.

To achieve the information on the granulation process and the stability of EE, firstly the in-line sensors are to be installed in the existing fluid bed granulator followed by investigations on variations of the granulation process. Hence, the following investigations will be described in this thesis:

1. Investigations on in-line sensors:

- Investigations on the positioning and configuration of the SFT-sensor for in-line particle size monitoring:

The SFT-sensor for in-line particle size measurement will be tested in different positions and configurations in the granulator. It is hypothesized that the measurement is influenced by the position of the sensor in the granulator and that the sensor might be blocked with substance in single positions. The best position and configuration of the sensor for the following investigations is to be defined.

- Investigations on the calibration of the MRT-sensor for in-line moisture monitoring.

The sensor will be calibrated based on loss on drying. To this end samples will be drawn from granulator during fluid bed granulation of the model formulation. It is assumed that the calibration for the granulation process is independent from external influences and blocking of the sensor. The determined calibration is to be utilized for the following investigations.

2. Investigations on stability of EE as a function of the granulation process:

- Investigations on the influence of thermal stress due to a prolonged drying time on the stability of EE (drying time).

The produced granules will be consciously over dried using the standard inlet air temperature. Therefore the drug substance is exposed to an increased thermal stress. It is hypothesized that the stability of EE is decreased due to a prolonged drying time and increased thermal stress. The in-line measured particle size will be decreased due to mechanical abrasion.

- Investigations on the influence of thermal stress due to variations of inlet air temperature during the drying step of fluid bed granulation on the stability of EE

The inlet air temperature during the drying process will be varied. The inlet air temperature influences the drying time of the granules in combination with an additional thermal stress due to temperature affecting the drug substance. It is assumed that the stability of EE is influenced by the drying temperature. In order to develop an effective but also mild granulation procedure it is important to be aware of the influence of the process parameter drying temperature.

- Investigations on influences of the contact with filler excipients on stability of EE

Firstly binary blends of MCC/EE respectively Lactose Monohydrate/EE will be produced and tested for stability of EE. It is assumed that the stability of EE is influenced by the particle surface of the used filler substance due to the reaction with Oxygen and moisture.

In the second step EE containing granules will be produced using granulation processes with different spraying regimes. These investigations should demonstrate if the surface of MCC can be modified to increase the stability of EE in the formulation. Furthermore a change in the spraying sequence and the corresponding changes in process parameters might influence the stability of EE.

The following chapters present the results of the investigations.

Chapter II

---

2 Materials and Methods

2.1 Materials

The following tables (Table 2-1 and Table 2-2 and Table 2-3) list the materials used for tests evaluated in chapter 5. The tables are assigned to the different investigations. Materials used in chapter 3¹²² and 4¹²³ are described in the corresponding sections of these chapters.

Table 2-1: Composition of model granules

Substance	Type of excipient	Quality	Trade name	Source
Microcrystalline Cellulose	Filler, binder	Ph. Eur.	Vivapur 101®	JRS Pharma, Deutschland
Pregelatinized corn starch	Filler, binder	Ph. Eur.	Starch 1500	Colorcon, USA
Corn starch	Filler, binder, disintegrant	Ph. Eur.	-	Colorcon, USA
Maltodextrine	binder	Ph. Eur.	Lycatab DSH	Roquette, Frankreich
Magnesium stearate	Lubricant	Ph. Eur.	-	Peter Greven, Deutschland
Purified Water	Solvent for binder	Ph. Eur.	-	JPH
Ethanol 96 %	Solvent for drug substance	Ph. Eur.	-	
Ethinylestradiol	Drug substance	Ph. Eur.	-	Bayer AG

Table 2-2: Materials for investigation on stability of EE as a function of matrix material and particle size with binary mixtures

Substance	Quality	Trade name	Source
α -Lactose monohydrate	Ph. Eur.	Pharmatose 450 M	DFE Pharma, Germany
Microcrystalline Cellulose	Ph. Eur.	Vivapur 105 Vivapur 101 Vivapur 12	JRS Pharma, Germany
Ethinylestradiol	Ph. Eur.	-	Bayer AG, Germany

Table 2-3: Materials for HPLC investigations on degradation products of EE

Substance/Material	Quality	Trade name	Source
Acetonitrile	Ph. Eur.	LiChrosolv ®	Merck Millipore
Methanol	Ph. Eur.	LiChrosolv ®	Merck Millipore
Ammoniumacetat	For analysis, Ph. Eur.	EMSURE® ACS	Merck Millipore
Purified water	Ph. Eur.	-	JPH
Filter	0,45µm, hydrophile PTFE,	Millex-LCR Filter	Merck Millipore
Working standard Ethinylestradiol	Ph. Eur.	-	Bayer AG
Working standard Dienogest	Ph. Eur.	-	Bayer AG
Working standard 9(11)-dehydro-EE	Ph. Eur.	-	Bayer AG
Column	RP 18 column with hydrophilic endcapping (250 x 4.6 mm, 4 µm with precolumn)	Synergi 4 µm Hydro- RP 80 Å	Phenomenex

2.2 Methods

The following methods were used for tests evaluated in chapter 5. Methods used for investigations in chapters 3¹²² and 4¹²³ are described in the corresponding sections of these chapters. Comparable methods as described in ¹²² or ¹²³ will be marked in the following sections.

2.2.1 Stability of EE

2.2.1.1 Analytical detection EE- degradation products¹²³

The analytical method for determination of degradation products of EE is a validated method described in a development test procedure of Jenapharm¹²⁴. The test was performed according to Ph. Eur. 2.2.29. The following table provides an overview on the retention times, detection methods and response factors.

Table 2-4: degradation products of EE (RRT= relative retention time = $t_R(\text{substance})/t_R(\text{standard})$)

Substance	t_R (min)	RRT (EE)	Detection	Standard	Response -Faktor F
Ethinylestradiol	23.2	1.00	-	-	-
6 α -hydroxy-EE	6.8	0.29	Fluor. 280/310 nm	EE: 280/310 nm	Fluor. 1.4
6 β -hydroxy-EE	9.2	0.4	Fluor. 280/310 nm	EE: 280/310 nm	Fluor. 1.7
6-oxo-EE	11.8	0.51	UV 220 nm	DNG: UV 220 nm	22
9(11)-dehydro-EE	20.8	0.90	Fluor. 263/343 nm	9(11)-DH-EE 263/343 nm	1.0

Table 2-5: Chromatographic conditions

Parameter	Specification
Column:	RP 18 with hydrophilic Endcapping 250x4.6 mm, 4 μ m with pre-column, column temperature 30 °C (e.g. Phenomenex Synergi 4 μ m Hydro-RP 80 Å)

Flow rate:	1.2 ml/min
Mobile phase and gradient:	A: water
	B: Methanol/Acetonitrile 65/35 (V/V)
	0 min 50 % B
	32 min 70 % B
	37 min 100 % B
	40 min 100 % B
	41 min 5 % B
	44 min 5 % B
	45 min 50 % B
	55 min Stop
Column temperature:	30 C
Detection:	UV 220 nm
	Fluorescence: 280/310 nm and fluorescence 263/343 nm

- Preparation of Solutions

- Standard solution R1 (0.5 % Dienogest, 0.5 % Ethinylestradiol, 0.5 % 9(11)-dehydro-EE)
  - Solution RA1: 8.0 mg Dienogest working standard are weighed in exactly an dissolved in 100.0 ml solvent B
  - Solution RB1: 2.0 mg EE working standard and 2.0 mg 9(11) DH EE working standard are weighed exactly in 100.0 ml solvent B
  - Solution RC1: 3.0 ml solution RB 1 are diluted with solvent B to 50.0 ml
  - Solution R1: 5.0 ml of solution RA1, 5.0 ml of solution RC 1 and 10 ml 0.01 M Ammonium acetate solution are diluted with a mixture of 0.01 M Ammonium acetate solution with solvent B 50/50 (V/V) to 100 ml

Two several standard solutions R1_1 and R 1_2 are to be prepared from individual initial weights.

- Standard solution R2 (0.05 % Dienogest, 0,05 % Ethinylestradiol, 0,05 % 9(11)-dehydro-EE): 2.0 ml of solution R1_1 are diluted with a mixture of 0.01 M ammonium acetate solution with solvent B 50/50 (V/V) to 20 ml
- Sample solution P: The amount of sample according to 8 tablets is dissolved in 10 ml of a mixture of 0.01 M Ammonium acetate solution with solvent B 10/90 (V/V) for 20 min in ultrasonic. After shaking the suspension is spun at 4000 U/min for 10 min. 5.0 ml of the solution is diluted with 5.0 ml of a mixture of 0.01 M Ammonium acetate solution with solvent B 90/10 (V/V). The sample solution is to be filtered with a 0.45 µm PTFE hydrophilic filter.
- Blind solution BL: A mixture of 0.01 M Ammonium acetate solution with solvent B 50/50 (V/V) is to be filtered with a 0.45 µm PTFE hydrophilic filter.
- System suitability test:
  - The coefficient of variation of the peak areas of 6 injections from R1_1 may not exceed 5 % (Chromatograms of Dienogest at 220 nm and EE at 280/310 nm)
  - The coefficient of variation of the retention time may not exceed 1.0 % (from 6 injections of R1_1, Chromatograms of Dienogest at 220 nm and EE at 280/310 nm)
  - The symmetry of peaks must be in between 0.8 and 1.5 (from 6 injections of R1_1, Chromatograms of Dienogest at 220 nm and EE at 280/310 nm)
  - The ratio of signal to noise in the chromatograms of solution R2 for Dienogest (220 nm) may not be less than 75. The EE- peak (280/310 nm) and the 9(11)-dehydro EE-peak (263/343 nm) must have a signal-to-noise ratio of at least 10.
  - The resolution between EE and the 9(11)-dehydro-EE-peak at 280/310 nm of solution R1_1 must be at least $R_s=4$.
- Calibration:
  - Conditions of detection for the standards (single point calibration):
    - Ethinylestradiol: Fluorescence Ex 280 nm/Em 310 nm: solutions R1_1 and R1_2
    - 9(11)-dehydro-EE: Fluorescence Ex 263 nm//Em 343 nm; solutions R1_1 and R1_2

- Dienogest: UV 220 nm; solutions R1_1 and R1_2

The 0.5 % reference peak areas of the standards are calculated according to the following equation:

$$A_R = \left(A_{R1} \times \frac{EW_T}{EW_{R1}} + A_{R2} \times \frac{EW_T}{EW_{R2}} \right) \times \frac{100}{C_s} \times \frac{1}{2}$$

A_R	0,5 % reference peak area
EW_T	target initial weight of standard
A_{R1}, A_{R2}	Mean values of peak areas of the standards in the solutions R1_1 and R1_2
C_s	Content of standard [%]

Determination of specified degradation products of EE

The amount of degradation products of EE (Table 2-4) are calculated according to the following equation. The detection limit is 0.5 %

$$GH_{VU}[\%] = \frac{A_P}{A_R} \times F \times 0,5$$

A_R	0,5 % reference peak area
GH_{VU}	concentration of degradation product [%]
A_P	peak area of the degradation product
F	response factor

The evaluation was performed using Chromeleon Version 6.8 SR 6 Build 2491 (Dionex, Sunnyvale, USA) respectively manually in MS Excel after calculation of peak areas determined from Shimadzu –lab-version –software version 7.3 SP1.

2.2.1.2 Storage conditions for stability tests

To investigate the influence of spraying sequence as well as particle size and type of excipient on the stability of the drug substance samples were drawn and stored in climate chambers at 25 °C/60 % r. h. and 40 °C/75 % r. h. according to Table 2-6.

Table 2-6: Storage conditions for investigations of stability of EE

Test run	Type of samples and packaging	25 °C/60 % r. h.	40 °C/75 % r. h.
1. Investigation on the influence of spraying sequences during granulation process	Tablets, blistered in PVC/Aluminium	4 weeks	1 week
		8 weeks	4 weeks
		12 months	8 weeks
			12 months
2. Investigations on the influence of contact with filler excipient (binary mixtures)	Blends filled in glass vials tightly closed with caps at 25 °C/60 % r. h., open and closed storage at 40 °C /75 % r. h.	24 months	1 week
			4 weeks
			8 weeks
			12 weeks

2.2.2 Fluid bed granulation process of granules^{122;123}

The granulation of the model granules as well as the installation of the sensors was performed in a fluid bed granulation GPCG 3.1 (Glatt, Binzen, Germany) as top spray procedure. EE was sprayed in the granulator as ethanolic solution followed by the aqueous binder solution. The granulation parameters listed in Table 2-7 were used. The product as well as the outlet air temperature was monitored during the entire granulation process. During the granulation process samples were drawn for off-line determination of moisture (LOD) and particle size (Laser diffraction).

Table 2-7: Standard parameters for fluid bed granulation process (GPCG 3.1)

Granulation parameters	Target value
Inlet air temperature	70 °C
Inlet air flow rate	80 m ³ /h
Shaking of filters	Asynchrone, 5 s shaking, 20 s pause
Diameter nozzle	1.2 mm
Spray pressure	2.5 bar
Spray angle	Approx. 24°

Granulation parameters	Target value
Product temperature during ethanolic API-spraying	30 °C ± 5 K
Product temperature during binder spraying	30 °C ± 5 K
Amount of binder and spray rate	68 % of the solution sprayed at a rate of 50 g/min (1 st step) and the residual 32 % sprayed at a rate of 30 g/min (2 nd step)
Amount of ethanolic drug substance solution and spray rate	Approx. 461 g drug substance solution; approx. 50 g/min

The following section provides a description of tests performed in the fluid bed granulator deviating from this standard granulation process.

2.2.3 Manufacturing of binary mixtures with the main filler and EE

The binary mixtures (see chapter 5) from EE and MCC respectively EE and Lactose monohydrate were produced in a scale of 500 g in the fluid bed granulator GPCG 1 (Glatt, Binzen, Germany) as top-spray procedure. In the process the dissolved EE was sprayed on the excipient (MCC or Lactose). The processing parameters described in Table 2-8 were used.

Table 2-8: Standard parameters for EE-solution spraying (GPCG 1)

Granulation parameter	Target value
Inlet air temperature	70 °C
Inlet air flow	10 % position of valve
Spray pressure	2.5 bar
Product temperature during ethanolic API-spraying	30 °C ± 5 K
Spray rate ethanolic drug substance solution	approx. 7 g/min (Lactose-mixture), approx. 11 g/min (MCC-mixture)

2.2.4 Particle size determination

2.2.4.1 *Spatial filtering technology for in-line particle size determination (SFT)*^{122;123}

The in-line particle size determination during fluid bed granulation was performed using the IPP-70Se sensor with dispersing cell D 23 (Parsum- Gesellschaft für Partikel-, Strömungs- und Umweltmesstechnik mbH, Chemnitz, Deutschland). The sensor is specified for particle determination with the range of 50 µm up to 6000 µm. During the fluid bed granulation process the sensor was installed in the deceleration zone of the granulator at a high of 400 mm above the sieve bottom. Data acquisition was carried out with a measurement rate of 5000 single values /s. The ring buffer of the analysis software was set to a size of 10,000 particles. This setting generates an average particle size from at least 10,000 particles every 10 s. Therefore a gliding distribution with permanently actualized data was possible. This means that a single value presented in the following evaluations was determined as a mean value from 10000 single data from the ring buffer. The measured raw data was sent to the PC via A/D converter and stored in ASCII format. Further evaluation of the data was performed using MS Excel.

The dispersing cell D23 allows for a constant measurement in a fluid bed with fluctuating particle densities. The dispersing cell is feed with inlet air via an external pneumatic device and two inlet air supplies: the first inlet air is used for flushing the cell to keep the inlet opening of the cell free for particles (external inlet air, rate: 3 l/min, cleaning impulse: every 30 s). The second inlet air is used for suction and dispersing of particles in the cell (internal inlet air, rate: 20 l/min).

The calibration of the sensor was done every 12 months using the testing device VK1. After fixing the sensor in the device pins of a specified size of 150 µm, 1 mm and 2 mm were passed through the measuring volume. The calibration was aligned with the measurement software. If needed an adjustment was performed. The sensor was installed in the Fluid bed granulator as described in tests on installation¹²².

2.2.4.2 *Off-line particle size determination with laserdiffraction*^{122;123}

The off-line determination of particle size was performed according to Ph. Eur. 2.9.31 with laserdiffraction (Helos 1410, Sympatec GmbH, Clausthal-Zellerfeld, Germany). The samples were dry dispersed with pressurized air using Rhodos/M (Sympatec) as dry dispersing unit in combination with Vibri vibratory feeder (Sympatec). The optical density during measurement

was 5 %. The mathematical evaluation of the data was performed according to Fraunhofer-theory. Each sample was measured three respectively six times. The particular number is mentioned with the results.

2.2.5 Moisture determination

2.2.5.1 MWR technology for in-line moisture determination (MRT)¹²³

In-line moisture determination was carried out using the sensor hydorpharm fbma mini (Döscher & Döscher GmbH, Hamburg). The measuring principle and the construction of the sensor are described in¹¹⁶ and¹²⁵. The sensor is a so called stray field sensor consisting of aluminum oxide (Al_2O_3) with a cylindrical ceramic ring set in metal (Figure 2-1). Resonances are excited if an integer number of full wavelengths fits along the circumference of the ring¹¹⁶. Their electric fields are polarized tangentially to the upper open surface in the radial direction¹¹⁶. The stray fields of the resonances extend into the outer space up to a high of approx. a quarter wavelengths in the dielectric. This means that depending on the used wavelength a sinusoidal distribution arises in the area of the ceramic ring as mentioned in Figure 2-2. The resonator works with a lower frequency of 1 GHz and can be adjusted by the high of the ring.

Influences of temperature on the measurement can be compensated by using Al_2O_3 and the use of a second resonator in the middle of the sensors for monitoring of the temperature¹²⁵. Therefore a temperature calibrating curve can be recorded to eliminate the influences of temperature on the measurement result.

Figure 2-1: Setting of the stray field resonator; a) upper site of the resonator, b) lower site of the resonator c) schematic profile of the sensor¹¹⁶

Figure 2-2: Distribution of the electric field on the resonator. Areas of high field intensity are marked dark¹¹⁶

The sensor has a diameter of 60 mm. The measurement frequency was used at 2.5 GHz. The sensor was installed in the product container of the fluid bed granulator GPCG 3.1 at a high of 120 mm above the sieve bottom in the product container of the granulator (same height as the sampler for *off-line* determinations) and was always covered with product. The measurement was done every 10 s. additionally manually triggered measurement results were collected during sampling for off-line moisture determination (LOD) in order to calibrate the sensor.

The sensor was calibrated during granulation of three test-batches (see chapter 4¹²³). The *off-line* generated data on LOD of these batches were used as reference values.

2.2.5.2 Off-line moisture measurement¹²³

The off-line determination of loss on drying of the samples drawn during the granulation process was performed according to Ph. Eur. 2.2.32 using the halogen dryer HR 73 (Mettler-Toledo GmbH, Gießen, Germany). Each sample ($m_0 = 5$ g) was dried for 10 min at 100 °C. After drying the mass was determined as m_1 . Loss on drying could be calculated according to the following equation:

$$LOD [\%] = \left(1 - \frac{m_1}{m_0}\right) \times 100$$

2.2.6 Tableting¹²³

The tableting of the granules was performed using the rotary tablet press XL 100 (Korsch AG, Berlin, Germany) with a main pressure force of 5 kN and a rotation speed of 40 rpm. The pre-compression force could not be separately adjusted but was monitored as well as the

main pressure force and the ejection force during the process. 12 round dies with a diameter of 5 mm and a convexity radius of 4 mm were used. 50 mg tablets were produced.

2.2.7 Specific surface area determination

The specific surface area was determined according to Ph. Eur. 2.9.26 using MONOSORB (Quantachrome Instruments, Boynton Beach, USA) with the single point method. Nitrogen was used as adsorbate.

2.2.8 Statistical evaluations

The statistical analysis was performed as described in chapter 4¹²³. Results are presented as means $\pm$ standard deviations. Statistical analysis were performed using one way ANOVA analysis followed by Tuckey HSD test using SPSS software (version 21, IBM, Armonk, NY, USA). Values of $p < 0.05$ were considered statistically significant.

Chapter III

---

3 In-line Monitoring of Particle Size in a Fluid Bed Granulator: investigations concerning positioning and configuration of the sensor

Chapter published in: International Journal of Pharmaceutics 466 (2014) 31-37

Authored by:

Katrin Roßteuscher-Carl ^{a,b}, Sabine Fricke ^a, Michael C. Hacker ^b, Michaela Schulz-Siegmund ^b

^a Jenapharm GmbH & Co. KG, Otto-Schott-Str. 15, 07745 Jena, Germany

^b University of Leipzig, Institute of Pharmacy, Eilenburger Str. 15A, 04317 Leipzig, Germany

3.1 Introduction

The implementation of process analytic technology (PAT) is recommended by the ICH Q8 guideline and the PAT-approach by the FDA to establish understanding of the critical process parameters (CPP) of a pharmaceutical manufacturing process. Suitable technologies should be used to monitor critical quality attributes (CQA) for rational process design and process control^{3;4}.

Granulation is a key manufacturing step in the production of tablets. The resulting granule particle size critically influences powder flow rate, blend uniformity and tablet properties such as crushing strength, average mass and friability^{17;65-67}. For these reasons and to optimize energy consumption and process time, the implementation of PAT to monitor particle size during granulation processes is desirable. In the last few years several new in-line technologies have been developed to monitor the particle size as a CQA during the granulation process. In-line particle size measurement became possible by implementation of near infra-red spectroscopy (NIRS) as early as 1996¹¹⁰ but in the past few years some follow-up studies have been published that reveal two major problems of the method^{84;107}. Firstly, a large amount of data is needed to calibrate the sensor and secondly, reflections on particles or granules that adhere to the measuring window may cause measurement failure¹¹¹.

Recently, the spatial filtering technology (SFT) was described as a new in-line particle size analysis method that can be used in the fluid bed granulation process^{93;97;99;126}. The advantage of this method is that no calibration of the sensor with the actual product is necessary. The sensor which analyses particle velocity and impulse in a fiber optic array to calculate particle cord length allows for a direct in-line and real time determination of the particle size distribution (Figure 3-1 A). The manufacturer (Parsum, Chemnitz, Germany) specifies the measurement range from 50 µm to 6000 µm.

Figure 3-1 SFT-Sensor (Parsum). A) Overview of the sensor assembly B) Schematic illustration of the measurement principle of the modified spatial filter technology

In order to validate particle size analysis by SFT, Petrak compared measurement outcomes with off-line results of laser diffraction⁸⁸. He demonstrated that the SFT-sensor provided reasonable particle size data for spherical glass beads with $x_{50} = 100 \mu\text{m}$, but revealed that typically the SFT sensor provided smaller particle size than laser diffraction and coulter counter. In spite of these differences in absolute particle size, the sensor can be used as a tool to reflect relative changes in particle size and hence monitor particle size development during a granulation process^{94;99}.

Several studies already discussed the use of an SFT-sensor for in-line monitoring of particle size during a fluid bed granulation process^{94;96;101}. None of these studies, however, described the effects of sensor position and configuration on the measurement outcome. Schmidt-Lehr mentioned tests for optimization of the sensor position and configuration but no details concerning the instrumental set-up have yet been provided⁹⁹. Burggraeve, however, mentioned that the position of the sensor in the granulator has to be considered due to influences of segregation effects on the measurement results²⁶.

In this study we investigated the influence of sensor position in the fluid bed granulator on particle count rate and average particle size. To this end, we generated two different probe positions in the granulator, one in the conical product container and one in the deceleration

zone below the spraying nozzle. We tested different probe configurations (insertion depth and degree of rotation) in either position (Figure 3-2).

Figure 3-2: Scheme of the GPCG 3.1 granulator and the sensor position and insertion depth during in-line measurement.

In general, installation of the sensor in the deceleration zone involves the risk of overweighing small particle sizes due to possible segregation processes in the fluid bed^{93;127}. On the other hand, measurement in the product container might be influenced by clogging effects of the sensor. To distinguish between these effects, we determined count rates as a measure for particle interactions besides the particles size distributions that were compared to data from laser diffraction. Particle size distributions of two microcrystalline celluloses were investigated; Vivapur 101 with a declared particle size (x_{50}) of 65 μm and Avicel PH102 with an x_{50} of 100 μm . Especially, Vivapur 101 is an excipient of interest as it is increasingly considered as an alternative for lactose in formulations. In order to verify the results of the configuration experiments, a granulation process of a model-placebo-formulation was monitored with the optimized configuration of the probe. The in-line results were compared with off-line laser diffraction data.

3.2 Materials and Methods

3.2.1 Materials

Different specialties of microcrystalline cellulose (MCC) with different particle size characteristics, namely Vivapur® 101 (JRS Pharma, Rosenberg, Germany) and Avicel PH 102 (FMC BioPolymer, Philadelphia, USA), were used in this study. Both MCC grades maintained their average particle size and size distribution during fluidization as confirmed by off-line laser diffraction data.

Corn starch, pregelatinized corn starch, maltodextrin and magnesium stearate were obtained from Colorcon (USA), Roquette (France) and Peter Greven (Germany).

3.2.2 Fluidizing of MCC in the fluid bed granulator

In order to test the sensor position in the granulator 3 kg of MCC were fluidized in a GPCG 3 granulator (Glatt GmbH, Binzen, Germany). The rate of the inlet air flow (v/t) was kept constant at 80 m³/h for all experiments in this study. The inlet air temperature was maintained between 30 °C and 35 °C.

3.2.3 Granulation

In a proof of concept experiment, a mixture (4.5 kg) of MCC (Vivapur 101), corn starch and pregelatinized corn starch was granulated using an aqueous maltodextrin solution. The granulation was monitored with the SFT sensor in the deceleration zone (11 cm, 45° right). The aqueous binder solution was sprayed in phase 1 with a rate of approximately 50 g/min and in phase 2 with a rate of approximately 30 g/min. The air flow was maintained at 80 m³/h and the inlet air temperature at 70 °C. Finally, magnesium stearate was added to the granules.

3.2.4 In-line particle size determination with SFT

The spatial filtering technology is based on the examination of particle velocity and impulse time on a spatial filter (Figure 3-1 B). Particles transported through the array of parallel laser beams in the measuring volume by laminar air flow generate a moving shadow on the fiber optic array (spatial filter) that causes a signal with the frequency (f_0) on the fiber optic array and an impulse on the individual fiber. The particle velocity (v_p) can be calculated from the frequency (f_0), the interval of the spatial filter (g) and the magnification of the imaging system (M), as follows^{88;90}:

$$v_p = f_0 \times g / M \quad (\text{Equation 1})$$

The chord length (x) of the particle can then be determined from the impulse time (Δt) at the individual fiber, the particle velocity (v_p) and the diameter (d) of the optical fiber according to the following equation:

$$x = v_p \times \Delta t - d \quad (\text{Equation 2})$$

In this study, a IPP-70 Se SFT-sensor (Parsum Gesellschaft für Partikel-, Strömungs- und Umweltmesstechnik mbH, Chemnitz, Germany) was utilized in combination with a dispersing cell D23 (Parsum). The ring buffer of the analysis software was set to a size of 10,000 particles. This setting generates an average particle size from at last 10,000 particles every 10 seconds. The measured raw data was sent to a PC via A/D converter and stored in ASCII format for processing with Microsoft Excel.

3.2.5 Investigated configurations of the SFT- sensor

The SFT-sensor was installed in two different positions, the lower sensor position which was located 120 mm above the sieve bottom in the product container and the upper sensor position, which was located 400 mm above the sieve bottom) in the deceleration zone of the granulator as shown in Figure 3-2.

In each of the two positions the sensor was installed at three different insertion depths (measured as the distance between the tip of the probe and the granulator wall in centimeters) (Figure 3-2). As additional parameter, the rotation angle of the probe was varied stepwise in 45° increments, with 0° representing the position with the dispersing cell pointing up and the measuring volume in vertical direction as illustrated in Figure 3-1 A. The combination of three insertion depths and 8 rotation angles resulted in 24 probe configurations for each of the two positions. Table 3-1 decodes the experiment numbers and corresponding configurations.

Table 3-1: Number codes for the different applied configurations of the SFT-sensor

Angle/Direction	Insertion depth		
	5 cm	8cm	11 cm
+135° (right)	1	9	17
+90° (right)	2	10	18
+45° (right)	3	11	19
0° (vertical)	4	12	20
-45° (left)	5	13	21
-90° (left)	6	14	22
-135° (left)	7	15	23
180°	8	16	24

In each configuration, three independent analyses were performed with Vivapur 101. The experiments with Avicel PH 102 were repeated in duplicate. The MCC was replaced prior to each run. In each experiment, the powder was fluidized and particle size was recorded by the SFT-sensor. By means of the particle rate counting, the time until the ring buffer of the SFT-sensor was filled with the data of one configuration was determined. Once the ring buffer was filled with data of the new configuration the measurement started. During measurement, a sample of fluidized MCC was taken via the product sampler (Figure 3-2) for off-line particle size analysis (laser diffraction). In all configurations the dispersing cell D23 was operated at a constant internal air flow of 20 l/min and external air flow of 3 l/min as recommended by the manufacturer

3.2.6 Off-line particle size determination with SFT

Control measurements were performed with the SFT-sensor and the D23-dispersing cell installed in a fitting with an angle of 0° on a laboratory desk. The air-settings in the dispersing cell were adjusted according to the in-line measurements. The material (Vivapur 101 or Avicel PH 102) was fed into the dispersing unit using a vibratory feeder.

3.2.7 Off-line determination of particle size by laser diffraction

The off-line particle size was determined by laser diffraction using a Helos H1410 (Sympatec GmbH, Clausthal-Zellerfeld, Germany). The MCC was dispersed using Rhodos/M (Sympatec) as dry dispersing unit in combination with Vibri vibratory feeder (Sympatec). Each sample was measured six times.

3.2.8 Statistical evaluations

All data were tested for normal distribution using the test of David with a significance level of $\alpha = 0.05$. Statistical analyses were performed using one-factorial ANOVA, t-test and Tukey's test with a significance level of $\alpha = 0.05$.

3.3 Results and discussion

3.3.1 Experiments with Vivapur 101

The particle flow rate in the measuring volume of the SFT-sensor was determined as the main parameter to evaluate the different sensor configurations (Figure 3-3 A). A high flow rate correlates with a high number of particles passing the measurement window and indicates a low number of unwanted events, such as temporary clogging of the sensor or impaired particle flow. Average particle count rate in all measured sensor configurations located in the deceleration zone was comparably high (5790/s; $s_{rel} = 8\%$) and almost independent of the sensor depth and rotation (Figure 3-3 A). The highest particle rate and the smallest variations was found for configurations $+90^\circ$ right to -90° left at an insertion depth of 11 cm. Average particle count rate in the product container (lower position), however, was significantly lower (2898/s; $s_{rel} = 27\%$) (Figure 3-3 A). Furthermore, particle rates determined in different probe angles showed a considerable relative standard deviation and a strong influence on the position angle. Reduced count rate and high standard deviations could be explained by a low or interrupted particle flow through the measuring volume. In the product container particle count rates similar to those found in the upper position were found when the sensor configuration was $+90^\circ$ right (5 cm), -90° to -135° left (5 cm), 180° (5 cm), and $+90^\circ$ right (11 cm).

Particle sizes (Figure 3-3 C) determined in the lower position at increasing rotation angle fluctuated between $70\ \mu\text{m}$ and $83\ \mu\text{m}$ forming a sine-shaped curve. This illustrates that the particle size determined, depended on sensor configuration when the sensor was positioned in the product container (lower position). Particle sizes determined in the upper sensor position, however, were less sensitive to the sensor configuration. We found x_{50} -particle sizes between $73\ \mu\text{m}$ and $77\ \mu\text{m}$ (Tab. 2) with low relative standard deviations within $\pm 2\%$.

For the tested Vivapur 101-model both, particle rate and x_{50} particle size data, pointed towards the upper sensor position in the deceleration zone of the granulator as the preferred position for robust particle size determination.

A)

B)

C)

D)

Figure 3-3: Particle rate (A and B) and average particle size (x_{50}) (C and D) as determined with SFT in the upper and lower position of a fluid bed granulator sensor depending on sensor configuration (rotation angle and insertion depth according to Table 3-1) A) Particle rate of Vivapur 101 in the upper and lower sensor position as a function of insertion depth and rotation (Mean of $n=3$ measurements) B) Particle rate of Avicel PH102 in the upper and lower sensor position as a function of insertion depth and rotation (single data from two different measurements) C) Particle size of Vivapur 101 in the upper and lower sensor position as a function of insertion depth and rotation (Mean of $n=3$ measurements) D) Particle size of Avicel PH102 in the upper and lower sensor position as a function of insertion depth and rotation (single data from two different measurements)

3.3.2 Model Avicel PH 102

Generally, initial particle size may affect the spatial distribution of the fluidized particle bed in the granulator at a given inlet air flow rate. In consequence, the preferred sensor position may also depend on the product particle size. In order to evaluate this parameter, a different MCC specialty, Avicel PH 102, which is characterized by an increased average particle diameter, was tested at the previously applied air flow rate.

Two test runs were performed in the upper and lower sensor position. Individual data from the test runs with the corresponding standard deviations are shown in Figure 3-3 B and Figure 3-3 D. In agreement with the data obtained for Vivapur 101, we found higher particle count rates in the upper (5371/s; $s_{\text{rel}} = 14 \%$ and 6011/s; $s_{\text{rel}} = 11 \%$) than in the lower (1978/s; $s_{\text{rel}} = 37 \%$ and 2233/s; $s_{\text{rel}} = 39 \%$) sensor position. While particle rate in the lower position was rather independent from the sensor angle at 5 cm (approximately 2000/s), variations in particle rate (600/s to 3800/s) were observed with increased sensor distances from the granulator wall.

Figure 3-3 D presents the in-line measured x_{50} particle sizes obtained in the tested sensor positions for Avicel PH 102. Particle size data could be reproduced within narrow ranges. In the upper sensor positions, the particle sizes slightly fluctuated between 68 μm and 72 μm depending on the sensor configuration (depth, rotation). The largest average size was measured in configurations 90° left and 90° right. Similarly, the experiments in the lower sensor position led to consistent results ranging between 80 μm and 86 μm at a sensor depth of 5 cm. Larger variations (70 μm to 85 μm) were obtained when the sensor position was rotated at a sensor depth of 8 cm and 11 cm.

Figure 3-4: Particle size cumulative distributions as determined in the upper and lower sensor position as well as off-line for Vivapur 101 and Avicel PH102. A) In line measured particle size distribution of Vivapur 101 as obtained by SFT-sensor in the upper and lower sensor position B) In line measured particle size distribution of Avicel PH 102 as obtained by SFT-sensor in the upper and lower sensor position C) Off-line measured particle size distribution of Vivapur 101 and Avicel PH 102 as obtained by laser diffraction and SFT-sensor

Particle size data determined for Avicel PH 102 (Figure 3-3 D, Figure 3-4 B) was more dependent on sensor position than for Vivapur 101. Overall, we observed a systematically decreased particle size in the upper sensor position as compared to the lower position. This is indicative of a size-dependent particle segregation in the fluid bed, which has been previously described by others^{128;129}. Segregation of Avicel PH102 in the granulator was allowed as the air inlet rate was not changed between the experiments and visualized by the cumulative particle size distribution recorded in both positions: However, even in the lower position, where no segregation is expected, average particle sizes of Avicel PH 102 differed

from the manufacturer's specification (100 μm). In order to investigate the origin of these deviations in absolute particle size, we determined off-line particle sizes of Avicel PH 102 by laser diffraction and also SFT (Figure 3-4 C). The values obtained by these measurements were in better agreement with the specification. Nevertheless, a difference between the diffraction data and SFT values was apparent, which is attributed to the inability of the SFT probe to analyse particles smaller than 50 μm . At larger particle sizes (above 90 μm), however, the size distribution curves measured by SFT and laser diffraction superimposed. A systematic problem during in-line particle size measurement, such as segregation, can therefore be easily detected by comparing in-line SFT data and off-line laser diffraction data and avoided during setup qualification.

3.3.3 A closer look at the sensor configuration (model Vivapur 101)

We could show that under suitable fluid bed conditions the upper sensor positions are more reliable than the lower sensor positions. Therefore a more detailed investigation and statistical analysis of the sensor configuration with regard to sensor depth and rotation was performed for the upper sensor positions (Figure 3-3, Table 3-2). The average particle sizes determined at a sensor depth of 8 cm and 11 cm were more homogenous at the investigated rotation angles than at a distance of 5 cm (Table 3-2). A one-factorial ANOVA of all configurations at a specific insertion depth revealed no significant differences between the different rotation angles. The average particle sizes at 11 cm and 5 cm differed significantly. The mean value measured at 8 cm was not significantly different from either the value at 5 cm or at 11 cm. Nonetheless, smallest standard deviations were determined at the angles $+45^\circ$, 0° and -45° at the a depth of 11 cm. The vertical position, 0° , however, may be sensitive to gravimetric particle flow and clogging by particle aggregates that sediment on the sensor inlet. The configuration 0° was therefore not considered reliable to analyze granulation processes. We would rather recommend an angle of 45° right (configuration 19). In this setting the fluctuation in particle rate was also fairly small (Figure 3-3 A).

Table 3-2: Particles size mean values (MV single) and standard deviations (SD single) for sensor configurations in the upper sensor position (n=3); particle size ranges, particle size mean values and standard deviations for each depth calculated from MV single- values.

Depth	Angle	MV single	SD single	Range	MV	SD
5 cm	$+135^\circ$ (right)	75.31	1.6	3.9	74.8	1.9
	$+90^\circ$ (right)	76.59	1.12			

Depth	Angle	MV single	SD single	Range	MV	SD
	+45° (right)	73.84	1.04			
	0° (vertical)	73.94	0.94			
	-45° (left)	72.65	0.78			
	-90° (left)	74.3	2.99			
	-135° (left)	75.84	2.31			
	180°	75.99	1.18			
8 cm	+135° (right)	76.14	2.11	2.5	75.3	2.1
	+90° (right)	76.71	2.85			
	+45° (right)	74.44	1.05			
	0° (vertical)	74.88	0.84			
	-45° (left)	74.22	2.15			
	-90° (left)	74.17	3.25			
	-135° (left)	75.78	2.91			
	180°	76.2	1.54			
11 cm	+135° (right)	75.47	1.14	2.5	75.6	1.8
	+90° (right)	76.96	2			
	+45° (right)	74.92	1.42			
	0° (vertical)	75.82	0.81			
	-45° (left)	74.46	1.62			
	-90° (left)	74.84	2.73			
	-135° (left)	76.43	2.41			
	180°	75.57	2.06			

In order to explain why particles size analysis in the upper position is more robust at 11 cm than at 5 cm, air velocities in the different horizontal positions (5 cm to 11 cm) in the fluid bed granulator were determined using a vane anemometer. The design of the granulator generated zones of different inlet air speeds in the granulator. We found high airflow close to the granulator wall which decreased with increasing distance from the granulator wall. While considerable inlet air flow was detected at a depth of 5 cm, no air flow was found at a distance of 6 cm or more in an empty granulator. We assume that inlet airflow close to the granulator wall may have interfered with particle transport in the sensor at this insertion depth.

In summary, in-line particle size measurement in the upper sensor position at a depth of 11 cm was possible for the test substance Vivapur 101 and resulted in reliable results with low variability (Table 3-2, Figure 3-3 A and Figure 3-3 C).

3.3.4 Influence of sensor configuration during a model granulation process

In order to test if the optimized setting would also be appropriate to monitor a granulation process, we compared in-line particle size data with off-line laser diffraction data during a granulation process of a placebo formulation consisting of Vivapur 101. Particle size was monitored by the SFT-sensor positioned in configuration 11 cm, 45° right. Figure 3-5 A shows the results of the in-line monitored x_{50} particle size during the granulation process. The observed profile of our model granulation process can be divided into 4 phases:

Initially the excipients were pre-warmed to product-temperature of 36 °C (measuring points 0 – 100). In the following first granulation phase the binder-solution was sprayed into the granulator using a high spraying rate in order to obtain rapid granule formation and particle growth (measuring points 100 - 200). The subsequent plateau phase (measuring points 200 - 300) was achieved by reducing the spraying rate. This phase is necessary to maintain granule particle sizes but allow for granule size consolidation by drying. In the last step the granules are dried (past measuring point 300).

A)

B)

Figure 3-5: Particle size profile measured during a model granulation process. A) In-line particle size x_{50} obtained at sensor position 11 cm, 45° right (position 19) as a function of the granulation process B) In-line (SFT) and off-line (Laser) measured particle size x_{10} , x_{50} and x_{90} at sensor configuration 11 cm, 45° right (Position 19) as a function of process time

The product temperature was used as stopping criterion for the drying process. Figure 3-5 B compares particle sizes determined in-line and off-line during granulation. It illustrates that particle sizes measured with the Parsum probe met the data determined off-line with laser diffraction concerning x_{50} and x_{90} . This shows that also broader particle size distributions, as found during a granulation process, can be correctly monitored by SFT in the upper position. Due to the detection cutoff of the SFT probe at 50 μm , x_{10} and x_{50} values in the beginning of the granulation process differed significantly from the laser diffraction data. Higher x_{90} values determined by SFT compared to laser diffraction at the end of phase 2 and beginning phase 3 may be attributed to a decrease in humidity when samples are taken and transferred to the off-line LD equipment and are therefore considered as artifact of the off-line process.

In summary, the SFT probe was able to monitor the granulation process in-line. Data of both methods were in very good agreement for x_{50} and x_{90} . This, however, is true for our comparably fine granules. Selected positions need to be revalidated for coarser granules and other equipment.

3.4 Conclusion

We showed that SFT sensor position in a fluid bed granulator as well as insertion depth and rotation angle have a relevant influence on the determined particles size and reliability of in-line particle size measurement. For the tested model Vivapur 101, we could demonstrate that the installation of the sensor in the deceleration zone of a granulator is recommended to gain high particle rates and reproducible data. In the upper position, the optimal sensor configuration (sensor installation depth and rotation angle) was determined by statistical analysis of the particle size data. We showed segregation for a coarser powder, Avicel PH 102, fluidized under the same conditions as Vivapur 101. Segregation led to smaller particle size results in the deceleration zone than in the product container. We therefore strongly recommend validating in-line particles size measurements with off-line laser diffraction when new formulations are involved.

In general, placement of the sensor in the deceleration zone appears to be reasonable as long as a non-sorting fluid bed exists. The results also show that configuration of the Parsum sensor within the fluid bed granulator has to be qualified with care. We were able to follow a model granulation process with the identified sensor configurations in the deceleration zone. Particles sizes determined by the Parsum sensor correlated well with the off-line measurement and laser diffraction data. This study provides a general positioning layout for SFT sensor qualification that can be adapted to each individual model-system with its specific characteristics, such as inlet air-flow pattern, powder bed position as well as particle size and nature of the material to be granulated.

3.5 Acknowledgements

We would like to thank Parsum Gesellschaft fuer Partikel-, Stroemungs- und Umweltmesstechnik mbH for performing the off-line SFT measurements in their lab. We also thank Anke Herling for excellent technical assistance and Ralf Ladwig for helpful discussions.

Chapter IV

---

4 Influence of in line monitored fluid bed granulation process parameters on the stability of Ethinylestradiol

Chapter published in: International Journal of Pharmaceutics 496 (2015) 751-758

Authored by:

Katrin Roßteuscher-Carl ^{a,b}, Sabine Fricke ^a, Michael C. Hacker ^b, Michaela Schulz-Siegmund ^b

^a Jenapharm GmbH & Co. KG, Otto-Schott-Str. 15, 07745 Jena, Germany

^b University of Leipzig, Institute of Pharmacy, Eilenburger Str. 15A, 04317 Leipzig, Germany

4.1 Introduction

Ethinylestradiol (EE) is the most commonly used estrogen substance in hormonal oral contraceptives¹. Homogenous drug distribution and stability in the formulation must be in focus during development of formulations containing the highly active and low dosed compound. EE is prone to oxidative degradation, which is accelerated with temperature³¹ or by photocatalysis³⁶. Autocatalysis activated by the phenyl-ring is assumed as mechanism for the oxidative degradation^{27;35} leading to the main-degradation products 6- α -hydroxy-EE, 6- β -hydroxy-EE, 9(11)-dehydro(DH)-EE, and 6-oxo-EE²⁹⁻³¹ (Figure 4-1). To date, published data on EE stability mainly addressed environmental questions, i.e. removal from wastewater, whereas little data is available on the stability of EE in pharmaceuticals.

Figure 4-1: Main degradation products of EE

The most frequently used dosage forms for application of oral contraceptives are film-coated and sugar-coated tablets. Fluid-bed granulation is an important process-step in the manufacture of such dosage forms. During fluid bed granulation, EE is exposed to high temperature as well as increased humidity, both of which accelerate API degradation in general^{38;40}. Particle size and humidity in the granules are critical quality attributes for the subsequent processing of the granules and drug stability. Particle size of the resulting

granules is another crucial parameter influencing flow rate, blend uniformity as well as tablet properties like crushing strength, average mass, friability and dissolution^{17;66}. Crushing strength and disintegration also depend on granule moisture⁵⁴ that, on the other hand, might negatively influence API stability^{40;42}. Water catalyses the oxidative degradation of API by the formation of water layers around drug crystals and particles that may increase the mobility in the solid state and result in more interactions of the API with oxidation-initiators³⁹.

Control of the key properties granule moisture and particle size during the granulation process, especially when monitored in-line, is therefore an important component of process development and required by the ICH guidelines^{3;4}. Moreover, in comparison to off-line or equilibrium determination of relative humidity over the granules, in-line process control may accelerate the granulation process considerably.

The residual moisture of the granules can be determined in different ways. Currently, a standard procedure for moisture assessment is to draw a sample to determine the loss on drying (LOD) off-line when a pre-defined outlet-air- temperature is reached in the granulator. In order to realize the guidelines, several publications describe the measurement of granule moisture using Near-infrared (NIR)-sensors in combination with multivariate data analysis^{107;109}. The advantages of the NIR-measurement (e.g. measurement independent from process variables) are accompanied by some disadvantages (e.g. complexity of particle properties to the spectrum) as discussed in several publications^{83;108-110}. An alternative in-line moisture-measurement technology is the microwave resonance technology (MRT). This technique has already been described for the in-line monitoring of the granulation^{111;112} and drying process¹¹⁸ using this new method. The technology is based on the alignment of the water-dipole-molecules in the electromagnetic field of a resonator and the measurement of the loss in energy due to the turn-around and alignment of the water-molecules. Due to a calibration without chemometrics and a bulk-density-independent measurement, this technology is a promising tool.

The aim of this study was to investigate the influence of the drying conditions after fluid bed granulation on the stability of EE. To this end, we varied the granulation process parameters 'drying time' and 'process air temperature' in order to adjust the granule moisture (test run 1) and thermal stress (test run 2) during processing (Figure 4-2). We implemented and investigated PAT to monitor the granulation process in-line in order to control the process parameters of fluid bed granulation and hence EE stability according to the ICH guideline Q8. In-line particle size determination was performed using the SFT sensor according to¹²². For

in-line granule moisture assessment a microwave resonance sensor was used and validated by off-line LOD measurements.

Figure 4-2: Fluid bed granulation- varied key-parameters of the drying process and critical quality attributes of the product.

4.2 Materials and methods

4.2.1 Materials

The model-formulation contained EE as API (Bayer, Germany) and microcrystalline cellulose (JRS Pharma, Germany) as filling agent. Corn starch, pregelatinized corn starch, maltodextrin and magnesium stearate were obtained from Colorcon (USA), Roquette (France) and Peter Greven (Germany), respectively.

4.2.2 Methods

4.2.2.1 Granulation process

The granulation process was performed in a fluid bed granulator in batches of 5 kg (GPCG3.1, Glatt, Binzen, Germany). The granulator was equipped with inlet-, outlet and product-temperature sensors as well as in-line sensors for measurement of granule moisture (MRT-Sensor) and granule- particle size (SFT-Sensor).

EE was sprayed in the granulator as ethanolic solution followed by the aqueous binder solution. A portion of 68 % of the solution was sprayed at a rate of 50 g /min (1st step) and the residual 32 % were sprayed at a rate of 30 g/min (2nd step). The inlet-air temperature in the standard-process was set to 70 °C.

In test run 1 the influence of the granule drying time on the stability of EE was investigated. For this test the produced granules were dried up to 30 min in the fluid bed granulator. During the drying process, samples were drawn every 5 minutes to determine loss-on drying (LOD) and the particle size off-line. After 0 min, 15 min and 30 min samples were additionally collected and stored under defined conditions in order to quantify EE degradation products. During this test-run, the granules were consciously over-dried to investigate the influence of extreme manufacturing conditions on the product.

In test run 2 the drying process inlet-air temperature was varied: 3 batches were dried at the standard inlet temperature of 70 °C, 3 batches were dried at 50 °C and 3 more batches at 90 °C inlet-air temperature. The stop-criterion was set at in-line measured granule moisture of 6 %, which correlated with a LOD of 6 to 7 %. Due to the different inlet-air temperatures during the drying process the drying time of the granules varied during the test runs.

Granules were analysed for the main chemical degradation products of EE: 6- α -hydroxy-EE, 6- β -hydroxy-EE, 9(11)-dehydro(DH)-EE, and 6-oxo-EE.

4.2.2.2 In-line-measurement of particle size distribution

The in-line particle size was determined using the SFT-sensor IPP-70 Se (Parsum Gesellschaft für Partikel-, Strömungs- und Umweltmesstechnik mbH, Chemnitz, Germany) according to the settings described previously¹²². The sensor was installed in the deceleration zone of the granulator at a height of 400 mm above

4.2.2.3 In-line-measurement of product moisture

The in-line-measurement of product moisture was carried out using microwave-resonance-technology (MRT, Hydorpharm C32, Döscher&Döscher GmbH, Hamburg, Germany). During test run 1, the sensor system was calibrated on the basis of the in-line measurement of the 3 produced batches. The off-line generated data on LOD of the batches were used as reference values. The MRT sensor was installed 120 mm above the sieve bottom in the product container of the granulator (same height as the sampler for off-line determinations) and was always covered with product.

4.2.2.4 Off-line measurement of particle size distribution

The off-line particle size by laser diffraction was determined using a Helos H1410 (Sympatec GmbH, Clausthal-Zellerfeld, Germany). The samples were dispersed using Rhodos/M (Sympatec) as dry dispersing unit in combination with Vibri vibratory feeder (Sympatec). Each sample was processed at least three times. The mean value of the data was determined for each batch.

4.2.2.5 Off-line determination of granule moisture

The granule moisture was determined as loss on drying using the halogen moisture analyser HR 73 (Mettler-Toledo) with a 5 g sample at 100 °C, 10 min measuring time.

4.2.2.6 Processing of granules:

4.2.2.6.1 Test run 1:

In order to investigate granules taken from one drying process at different times, only small samples sizes, sufficient for off-line determination of particles size, loss of drying (LOD) and for storage in controlled climate to investigate EE stability were drawn. Due to the limited sample size no tableting was performed with these samples. Moreover, the material achieved after 30 min drying time showed extremely low residual moisture and was therefore considered as over dried. Hence, the tableting of this material was not possible.

4.2.2.6.2 Test run 2:

The achieved granules from test run 2 were compressed to 50 mg tablets using a rotary tablet press (Korsch XL 100, Berlin, Germany, Force of pressure 5 kN).

4.2.2.7 Stability tests on Ethinylestradiol

To investigate the influence of the drying time on the stability of the drug substance, samples of the granules were drawn in test run 1 after 0, 15 and 30 minutes during drying process via the sampler of the granulator. 240 mg of these samples were filled in glass-vials, tightly closed with caps and stored at 25 °C/60 % r.h. and 40 °C/75 % r.h.

The produced granules from test-run 2 were tableted. The achieved tablets were blistered in PVC/Aluminium and stored at 25 °C/60 % r.h. and 40 °C/75 % r.h. according to Table 1.

Table 4-1: Storage time at climates

Test run	25 °C/60 % r.h.	40 °C/75 % r.h.
1. Investigation of the influence of drying time	1 week	1 week
	3 weeks	3 weeks
	8 weeks	8 weeks
	24 months	12 weeks
2. Investigation of the influence of inlet-air temperature during the drying process	4 weeks	1 week
	8 weeks	4 weeks
		8 weeks
		12 months

4.2.2.8 Investigation on degradation products of EE

Figure 1 presents the degradation products of EE. The drug substance undergoes mainly oxidative degradation. The main products of this process are 6-oxo-EE, 6 β -hydroxy-EE, 6 α -hydroxy-EE und 9(11)-dehydro-EE²⁹⁻³¹.

These degradation products were quantified in all samples using HPLC (Shimadzu). The HPLC set- up consisted of a RP 18 column with hydrophilic endcapping (250 x 4.6 mm, 4 μ m with precolumn, column temperature 30 °C, e.g. Phenomenex Synergi 4 μ m Hydro-RP 80 Å) and a mobile phase gradient from Water (A) and Methanol/Acetonitrile (B) 65/35 (V/V) at a

flow rate of 1.2 ml/min (0 min: 50 % B; 32 min: 70 % B; 37 min: 100 % B; 40 min: 100 % B; 41 min: 5 % B; 44 min: 5 % B; 45 min: 50 % B; 55 min: Stop). The detection was performed with UV at 220 nm and Fluorescence at 280/310 nm as well as 263/434 nm.

4.2.2.9 Statistical evaluations

Results are presented as means $\pm$ standard deviations. Differences in degradation product formation were analysed for statistical significance by one way ANOVA analysis followed by Tuckey HSD test using SPSS software (version 21, IBM, Armonk, NY, USA). Values of $p < 0.05$ were considered statistically significant.

4.3 Results and Discussion:

We intended to evaluate the influence of humidity and thermal stress during fluid bed granulation on stability and storage stability of EE.

In a first test run, samples at different drying stages were sealed to prevent moisture exchange with the environment.

In the second test run, we investigated the influence of the process temperatures during the drying phase on the stability of EE.

Additionally we evaluated the efficiency of *in-line* particles size and moisture determination using SFT and MRT in both test runs. A successful combination of both *in-line* technologies would allow for control of the most crucial granule parameters for tableting and API stability in real time.

4.3.1 *In-line* particle size determination

4.3.1.1 *Test run 1:*

Figure 4-3 A and Figure 4-3 B show that the individual phases of a typical granulation process could be monitored using in-line and off-line particle size distribution measurement. Particle size measured in-line and off-line remained constant during the pre-warming phase and the spraying of API-Solution. In-line particle size monitoring showed a slight increase in x_{50} and a stronger increase in x_{90} during the first step of binder spraying. During the drying phase, x_{50} and x_{90} moderately decreased with ongoing drying time, probably by mechanical abrasion and shrinkage upon drying. Off-line measured particle size distribution showed a constant increase in particle size during the first and the second step of binder spraying. In-line data only displayed the particle size increase during the first step. In all phases of granulation, off-line measured particle size differed notably from the in-line measured particle size. These differences are due to a known problem of SFT analysis to detect particles smaller than $50\text{ }\mu\text{m}$ ¹³⁰. This error typically affects the data at early stages of the granulation process and becomes negligible towards the end of the granulation process when the fraction of particles below that size is strongly reduced¹²². Both, x_{50} and x_{90} determined in-line by SFT and off-line by laser diffraction, showed remarkable consistence in the determined values in that last phase of the process.

A)

B)

C)

Figure 4-3: A) In-Process-data on granulation process: mean value SFT (in-line)-sensor (black line, SD=grey lines), mean value laser diffraction (off-line method, dotted line with squares), mean value loss- on drying (off-line method, dots); MV= Mean Value (MV over all batches, $n=3$), SFT=Spatial filtering technology, LOD= Loss on drying B) Particle size x_{10} , x_{50} , x_{90} from off-line Determination using Laserdiffraction (LD, filled symbols) and in-line determination using SFT-Sensor (SFT, open symbols), Mean values over all batches ($n=3$) C) x_{50} -Particle size measured in-line (lines) and off-line (dots) during variation of the in-let air temperature in drying process (mean value from $n=3$ batches per drying temperature)

4.3.1.2 Test run 2:

Figure 4-3 C compares x_{50} of in-line and off-line measured particle size distribution as mean values of three batches dried at different inlet air temperatures. We observed strong fluctuations in in-line determined particle size at the end of the drying process that can be explained with the process that was necessary to add the outer phase to the granules for later compression.

Figure 4-3 C shows that variations of the inlet-air temperature had only slight influence on the x_{50} - particle size distribution of the final granules. The largest particle size was measured for the granules dried at 90 °C in-let air temperature, whereas the smallest particle size was found for granules dried at 50 °C. This might be explained by the different drying times that resulted from the different inlet temperatures and led to shorter processing times and lower mechanical stress for higher temperatures. Table 4-2 shows the measured process duration that emphasizes this conclusion.

Table 4-2: Product- temperatures and drying time of the granules

Inlet- air temperature during drying process [°C]	Drying time of granules [min]	Measured product-temperature [°C]
50	26	34
70	16	39
90	15	47

4.3.2 In-line granule moisture determination

4.3.2.1 Test run 1

The samples drawn during granulation and drying for off-line determination of LOD (Figure 4-3 A) were used for the product-related calibration of the MRT sensor applied in the following test run 2 in order to stop the process at a predefined granule moisture. The data set showed a linear correlation with a correlation coefficient of 0.903 (Figure 4-4 A). A separate calibration approach that took into account possible differences in data fitting for spraying and drying phase did not significantly improve the correlation (Figure 4-4 B). Therefore, we defined the stop criterion for the second run as 6 % MRT, which correlated with a LOD range between 6 % and 7 %.

A)

B)

C)

Figure 4-4: A) Calibration data for MWR-sensor from $n=3$ batches during entire granulation process; B) Calibration data for MWR-sensor from $n=3$ batches separated in granulation phase (squares) and drying phase (rhombs) C) Granule moisture (in-line measurement: lines, off-line measurement: dots) during variation of inlet-air temperature during drying process (mean value of $n=3$ batches per temperature)

4.3.2.2 Test run 2

Figure 4-4 C shows the granule moisture monitored in-line with MRT and off-line by LOD. We found differences between in-line and off-line moisture-measurement in the 1st and 2nd step of binder-spraying (Figure 4-4 C) that resulted from the limitation of MRT to measure moisture below 10 %¹¹⁵. The subsequent drying phase could be more appropriately characterized with MRT. At 90 °C inlet-air temperature the measured moisture fell steeply during the drying process compared to the moisture measured at 50 °C. Hence, a fast drying of the granules at 90 °C inlet-air temperature and the slow drying process of granules dried at 50°C inlet-air temperature could be monitored well by MRT. However, MRT mean values

for the intermediate condition (70 °C) could not be as clearly distinguished from the 90 °C batches as by comparison of off-line LOD data. We therefore conclude that granule moisture determination by our MRT equipment was less reliably and sensitive as with the off-line LOD data. Nevertheless, MRT is well suited for an estimation of product moisture during the entire granulation process.

4.3.3 Effects of granule moisture on stability of EE

4.3.3.1 Test run 1

Figure 4-5 A and Figure 4-5 B show the quantitative data on EE impurities in the granules after long term storage in sealed vials at 25 °C/60 % r. h. over 24 months and storage under accelerated conditions (40 °C/ 75 % r. h.) over 12 weeks, respectively. Time of drying (0, 15 or 30 min) did not affect the detected amount of degradation products when analysed directly after granulation. Degradation products increased with ongoing storage time in all groups. Remarkable differences in EE degradation were found between the samples of different initial moisture. After 24 months of storage under long term conditions (25 °C/60 % r. h.) we found a significantly increased content of all investigated degradation products in samples with an LOD of 8.35 % as compared to batches with lower LOD (Figure 4-5 G). This indicates moisture driven degradation of EE in the sealed containers. Affirmative results were obtained under accelerated conditions. After 8 weeks we already found significantly increased amounts of 6- α -hydroxy-EE, 6- β -hydroxy-EE and 9(11)-DH-EE in the granules with 8.35 % as compared to those with 4.88 % and 3.43 % LOD (Figure 4-5 E). The amount of degradation products found after 12 weeks under accelerated conditions corresponded well with the data found after 24 months of long term storage (Figure 4-5 F and Figure 4-5 G). After 12 weeks, we also found significantly increased amounts of 6-oxo-EE in granules with 8.35 % compared to 3.43 % LOD. Thus, we could confirm our hypothesis that granule moisture accelerated EE degradation. Using sealed vials, we could distinguish between effects of the granule moisture and temperature effects of storage conditions. No humidity or drying effects of the storage conditions biased the results of test run 1.

4.3.3.2 Test run 2

In the second experiment we varied process temperatures and dried the granules to LODs of 6-7 % to allow for tableting and blistering. After 8 weeks of storage under accelerated conditions (40 °C/75 % r. h., Figure 4-5 D) we found significant differences for degradation products in samples dried at different temperatures. 6- β -hydroxy-EE, 9(11)-DH-EE and 6-

oxo-EE were significantly increased for processing temperatures of 90 °C as compared to 50 °C and partly to 70 °C.

The difference in drying time and product temperatures of each process are described in Table 4-2. The increased product temperatures (47 °C) during the drying process using 90 °C inlet-air temperature was responsible for the thermal stress on EE in presence of water over a short time. Prolonged process times at 50 °C inlet-air temperature may not have a significant influence on EE stability since this resulted in a low final product temperature of 34 °C for less than 30 min, which is lower than the storage stress under accelerated conditions. Figure 5C shows that the final LOD of the granules differed more or less within the defined limits of 6 to 7 % with samples dried at 90 °C having the lowest LOD with 5.9 %. The increased amounts of degradation products in samples dried at 90 °C indicate that the process temperature has a clear influence on the degradation of EE.

Comparison between degradation data of 6- α -hydroxy-EE and 6- β -hydroxy-EE in the experiments with different granule moisture with that of different granulation processing temperatures revealed a remarkably high amount for these degradation products in all samples of the temperature driven experiment (6- α -hydroxy-EE 0.17 % and 6- β -hydroxy-EE 0.24 % at 50 °C, 8 weeks, Figure 4-5 D). In the experiment on the influence of granule moisture (test run1), however, these two products were only increased for the samples with a LOD of 8.35 % (6- α -hydroxy-EE 0.14 % and 6- β -hydroxy-EE 0.18 %, Figure 4-5 E). This indicates that the increased humidity (75 % r.h.) under accelerated conditions may have a considerable effect on EE stability even through the PVC/aluminium blister. This was confirmed after 12 months of storage under accelerated conditions where we found very high amounts of degradation products that no longer depended on the conditions during the granulation and drying process (Figure 4-5 C). We assume that humidity in combination with temperature stress generated by the accelerated conditions for a very long time of 12 months overruled the observed influence of the drying temperature during granulation.

General differences between the two experiments are probably a consequence of the different storage conditions that were chosen for the two experiments. In the first experiment on the influence of granule moisture on stability, vials were hermetically sealed to preserve the original humidity. In the second experiment on drying temperature the tablets were compressed from the granules and blistered in PVC with an aluminium lid foil. PVC is known to be permeable for water vapour^{131;132}. The described blister material was chosen for the

experiments to gain test-results that are comparable to the stability of marketed EE-containing tablets for which stability of EE is proven under accelerated as well as long term conditions.

A)

B)

C)

D)

E)

F)

G)

Figure 4-5: Stability of EE as mean value of impurities and standard deviations (bars). A) Stability of EE depending on drying time of granules. Impurities after storage in sealed vials at 25 °C/60 % r. h. (bars). Mean and standard deviation of LOD of granules after processing (dots). B) Stability of EE depending on drying time of granules. Impurities after storage in sealed vials at 40 °C/75 % r. h. (bars). Mean and standard deviation of LOD of granules after processing (dots). C) Stability of EE depending on drying temperature during granule processing. Impurities after storage of blistered tablets at 40 °C/75 % r. h. (bars). Mean and standard deviation of LOD of granules after processing (dots). D) Stability of EE in relation to the drying temperature after storage of blistered tablets at 40 °C/75 % r. h. for 8 weeks (bars). Significant differences in impurity contents are indicated by brackets. LOD of samples at different drying temperatures: 7.33 % (50 °C); 7.09 % (70 °C); 5.87 % (90 °C) E) Stability of EE in relation to the drying time of granules after storage of sealed vials at 40 °C/75 % r. h. for 8 weeks (bars). Significant differences in impurity contents are indicated by brackets. F) Stability of EE in relation to the drying time of granules after storage of sealed vials at 40 °C/75 % r. h. for 12 weeks (bars). Significant differences in impurity contents are indicated by brackets. G) Stability of EE in relation to the drying time of granules after storage of sealed vials at 25 °C/60 % r. h. for 24 months (bars). Significant differences in impurity contents are indicated by brackets.

4.4 Conclusion

In-line monitoring of granule size and granule moisture during fluid-bed granulation was applied for the development of a MCC-containing EE model formulation. We investigated the influence of the drying phase during the granulation process concerning heat and remaining granule moisture on the stability of EE. We found that the EE degradation products 6- α -hydroxy-EE, 6- β -hydroxy-EE, 6-oxo-EE and 9(11)-DH-EE were significantly increased by increased granule moisture after long term storage. The combination of increased moisture with an enhanced storage temperature of 40 °C strongly accelerated the humidity driven degradation process.

Enhanced process temperature by increased inlet-air temperature during the drying process had clear effects on EE degradation upon storage. 9(11)-DH-EE and 6-oxo-EE were the main temperature driven degradation products.

The results show that for the development of a robust formulation, the entire granulation process should be well investigated and described. *In-line* technologies offer the possibility to analyse and monitor the process leading finally to a real-time release. Despite some deviations of the *in-line* from the *off-line* data, a detailed description of the drying process as basis for the stability of the model-substance was possible under consideration of the *in-line* sensors.

4.5 Acknowledgements

We would like to thank Anke Herling, Renate Babock and Inge Tarrach for their excellent technical assistance and Ralf Ladwig for helpful discussions.

Chapter V

---

5 Influence of filler excipients on stability of EE

5.1 Introduction

In the past the standard formulation containing EE used lactose monohydrate as main filler substance. Recently lactose monohydrate is frequently replaced due to a possible lactose-intolerance of the patients. Beside this aspect investigations could demonstrate that lactose phosphate, a known intrinsic contaminant in lactose, might enhance the degradation of steroids¹³³. For the model formulation used in this thesis lactose monohydrate was replaced by MCC.

The replacement of lactose monohydrate in the formulation by MCC leads to changed properties of the formulation. This makes investigations concerning the stability of EE and the granulation procedure necessary. As demonstrated in literature MCC is able to bind water molecules on its surface⁵³ and in the polymer structure⁵¹. This water integrated into the MCC structure might influence the stability of drug substances⁴⁰.

As already mentioned in chapter 2.2.1.1 the fluid bed granulation process performed for investigations in this theses consists of two main steps, an ethanolic drug spraying step and an aqueous binder solution spraying step (Figure 5-1, sequence 1). The aqueous binder solution might change the properties of MCC: firstly by incorporation of the water molecules in the MCC polymer structure and secondly by the formation of agglomerates due to the sprayed binder. Sprayed binder therefore changes the surface of the materials.

The investigations described in the following chapter demonstrate the influences of replacing lactose with MCC on the stability of EE considering the following two aspects: firstly the direct contact of the main filler substance with EE by production of binary mixtures and secondly the influence of a covering of the particle surface with binder during granulation process by modelling the spraying sequence:

1. Binary mixtures:

- To investigate the influence of MCC on EE in comparison to the standard filling excipient lactose, binary mixtures of the filler excipients and EE were produced (see chapter 2.2.3). For this purpose ethanolic EE solution was sprayed in the fluid bed granulator GPCG 1 (batch size 500 g) on MCC (Vivapur 101) respectively lactose (Pharmatose 450M and Pharmatose 130M). The mixtures were stored in accelerated conditions (40 °C/75 % r. h., opened glass vials and closed glass vials) and examined for EE impurities.

- The influence of contact area between MCC and EE on the stability of EE was investigated by spraying ethanolic EE-solution in the fluid bed granulator on Vivapur 101, Vivapur 105 and Vivapur 12 (binary mixtures). All MCC-qualities are of different particle size. Vivapur 12 has the largest particle size with $x_{50}=146\text{ }\mu\text{m}$, Vivapur 105 has the smallest particle size with $x_{50}=29\text{ }\mu\text{m}$ (Vivapur 101: $x_{50}=55\text{ }\mu\text{m}$). The binary mixtures were stored at 25 °C/60 % r.h. for up to 24 months in closed glass vials and 40 °C/75 % r.h. open to investigate the relationship of the stability of EE with the surface of MCC.

2. Modelling of spraying sequence during fluid bed granulation process:

In the second step we investigated the influence of the contact of EE and MCC in granules on the stability of EE: In this study, the two-step standard granulation process consisting of an ethanolic drug spraying step and an aqueous binder solution spraying step (Figure 5-1, sequence 1) was modified with the aim to increase EE stability by changing the moisture contact time of EE within the process (Figure 5-1, sequence 3) Furthermore it should be investigated if destabilizing EE interactions with MCC and oxygen were reduced by coating MCC and subsequently EE with binder (Figure 5-1, sequence 2). Three batches were manufactured for each spraying sequence. The resulting granules were compressed and investigated for chemical stability of EE. The end point of the drying process was defined as in-line measured 6 % moisture.

Figure 5-1: Spraying sequences during fluid bed granulation process

The granulation process was monitored with in-line sensors for particle size (SFT) and moisture measurement (MRT) to investigate the influence of changes in spraying sequence on the critical material attributes.

5.2 Results and Discussion

5.2.1 Binary mixtures

5.2.1.1 *Influence of the main filler excipients on the stability of EE*

Figure 5-2 shows a steep increase of all impurities in the opened stored binary mixtures containing MCC whereas the amount of impurities in binary mixtures with lactose monohydrate had only a little change during the open storage (Figure 5-2 A and B). In binary mixtures containing MCC (Vivapur 101) all degradation products increased significantly between all testing points, except for 6- α -hydroxy-EE between 4 and 8 weeks. The steepest increase could be found for 9(11)-dehydro-EE. In binary mixtures containing lactose (Pharmatose 450M) 6- α -hydroxy-EE and 6- β -hydroxy-EE increased significantly except from 1 week to 4 weeks (6- α -hydroxy-EE and 6- β -hydroxy-EE) and 4 to 8 weeks (6- β -hydroxy-EE). No significant increase was determined for 9(11)-dehydro-EE whereas a significant increase could be determined for 6-oxo-EE except from 1 week to 4 weeks. Binary mixtures containing Pharmatose 130M showed significant increases from start to 12 weeks for all impurities, furthermore for 6- α - and 6-oxo-EE from 1 week, 4 and 8 weeks to 12 weeks. For 6- β -hydroxy-EE and 9(11)-hydroxy-EE a significant increase could be identified from start to 8 weeks respectively start to 4 weeks. In a direct comparison between both lactose grades (Pharmatose 450M and Pharmatose 130M) after 12 weeks storage a significant difference could be determined for 9(11)-dehydro-EE (Figure 5-2 B).

Figure 5-2: Degradation products EE in binary mixtures of MCC and Lactose (40 °C/75 % r. h., open), mean values (n=3) with standard deviations; A) comparison of binary mixtures with lactose (Pharmatose 450M and Pharmatose 130M) and MCC (Vivapur 101). Significant differences in impurity contents are indicated by brackets.; B) Zoom to degradation products determined in binary mixtures of lactose Pharmatose 450M and Pharmatose 130M after 12 weeks storage. Significant differences in impurity contents are indicated by brackets.

After storage in closed glass vials (Figure 5-3 A) significant differences were determined in binary mixtures containing lactose Pharmatose 450M and lactose Pharmatose 130M as well as in binary mixtures containing MCC (Vivapur 101). Indeed, the increase was not as steep as in opened stored binary mixtures containing MCC (Vivapur101). Significant increase for all investigated time points could be determined in binary mixtures containing MCC Vivapur 101 for 6- α -hydroxy-EE (except from 4 to 8 weeks), for 6- β -hydroxy-EE (except from 1 week to 4 weeks) and for 6-oxo-EE. For 9(11)-dehydro-EE a significant increase was determined until 4 weeks. Binary mixtures containing lactose Pharmatose 450M showed significant increase for 6- β -hydroxy-EE and 9(11)-dehydro-EE at 4 to 8 and 8 to 12 weeks. 6- α -hydroxy-EE increased significantly from 8 to 12 weeks. 6-oxo-EE increased significantly except from 4 to 8 weeks. In binary mixtures containing lactose Pharmatose 130M all degradation products increased significantly during storage except 6- α -hydroxy-EE from start to 1 week. The highest amount of degradation products were determined in binary mixtures containing lactose Pharmatose 130M.

In the binary mixture with lactose of smaller particle size (Pharmatose 450) as well as in binary mixtures with MCC (Vivapur 101) the impurity profile is dominated by 9(11)-dehydro-EE followed by 6-oxo-EE, 6- β -hydroxy-EE and finally 6- α -hydroxy-EE. In the recent case of binary mixture with Pharmatose 130M the profile after 12 weeks storage in closed

conditions is dominated by 6-beta-hydroxy-EE strictly followed by 9(11)-dehydro-EE and 6-oxo-EE (Figure 5-3 A and B). This profile might provide an indication that an additional factor influenced the degradation of EE. In literature a lactose-impurity was already discussed enhancing degradation of steroids¹³³.

Figure 5-3: Degradation products EE in binary mixtures of MCC and Lactose. A) comparison of binary mixtures with lactose (Pharmatose 450M and Pharmatose 130M) and MCC (Vivapur 101) at (40 °C/75 % r.h., closed), mean values (n=3) with standard deviations. Significant differences in impurity contents are indicated by brackets. **B)** Comparison of degradation products of EE in binary mixtures of MCC and Lactose after 12 weeks at 40 °C/75 % r.h., opened and closed, mean values (n=3) with standard deviations. Significant differences in impurity contents are indicated by brackets.

The increased amount of the degradation products 9(11)-dehydro-EE and 6-oxo-EE after opened storage (Figure 5-3 A) of the binary mixture containing MCC (Vivapur 101) can be attributed to the increased water-uptake of MCC during storage. As already discussed in section 1.4.2.2 MCC acts like a 'molecular sponge'¹³⁴ incorporating water molecules in the spaces between cellulose chains⁵⁷. The water catalyzes degradation reactions (see section 1.4.1.3). During opened storage at 40 °C/75 % r.h. the water-molecules from atmosphere could interact with the structure of MCC and catalyze the degradation of EE. In contrast to this sponge-like behavior of MCC the water- uptake of lactose monohydrate is negligible low, a solvation of EE that leads to an increased degradation can be excluded¹³³. Therefore the amount of degradation products 9(11)-dehydro-EE and 6-oxo-EE in binary mixtures of MCC with EE is increased after opened storage compared to the closed storage (Figure 5-3 B).

5.2.1.2 Influence of MCC contact area on the stability of EE

Figure 5-4 shows that the highest amount of impurities after 24 months was found for Vivapur 105 and the lowest amount was detected for Vivapur 12. After 24 months of storage significant differences could be found for 6-alpha-hydroxy-EE and 6-beta-hydroxy-EE between binary mixtures with Vivapur 105 and Vivapur 101 respectively Vivapur 12. Furthermore the amount of 9(11)-dehydro-EE differed significantly between the binary mixtures of Vivapur 105 and Vivapur 12. No 6-oxo-EE could be determined in the binary blend of Vivapur 12. It is noticeable that linear trends in detected amounts of 6-alpha-hydroxy-EE and 9(11)-dehydro-EE were detected after 24 months storage time with the particle size x_{50} of the different MCC-grades (Figure 5-4 B). R^2 of the linear regressions were determined with 0.82 (6-alpha-hydroxy-EE) respectively 0.95 (9(11)-dehydro-EE). For 6-beta-hydroxy-EE and 6-oxo-EE no linear regression could be established.

In addition we determined the specific surface area of Vivapur 105 and Vivapur 12. As expected Vivapur 105 has a larger specific surface area with $1.5 \text{ m}^2/\text{g}$ compared to Vivapur 12 with $0.8 \text{ m}^2/\text{g}$. Furthermore the residual moisture was determined as LOD in the binary mixtures. The LOD was highest in the binary mixture with Vivapur 105 (LOD=4.5 %). The lowest LOD was determined from the binary mixture with Vivapur 101 (LOD=4.05 %). The LOD determined from the binary mixture with Vivapur 12 showed a value of 4.15 %. The increased moisture content in the binary mixture with Vivapur 105 might have additionally accelerated the degradation of EE. Whereas the increased amount of degradation products found in the binary mixture from Vivapur 101 compared to the mixture with Vivapur 12 might be attributed to the particle surface of MCC.

Figure 5-4: Degradation products EE in binary mixtures of MCC (25 °C, 60 % r.h., closed) mean values ($n=3$) with standard deviations; A) comparison between start and 24 months Significant differences in impurity contents are indicated by brackets.; B) Correlation between

degradation products after 24 months with particle size x_{50} of MCC-qualities; lines are linear regression

Figure 5-5 A presents the results from determination of degradation products in binary mixtures with the different MCC- grades (Vivapur 105, Vivapur 101 and Vivapur 12) after opened storage at 40 °C/75 % r.h.. In the binary mixture with Vivapur 105 all degradation products increased significantly during storage except 6- α -hydroxy-EE and 6-oxo-EE from 1 week to 4 weeks as well as 9(11)-dehydro-EE (significantly increase only from 4 to 12 weeks). In binary mixtures with Vivapur 101 and Vivapur 12 the amount of degradation products increased at each time point significantly. 9(11)-dehydro-EE in binary mixture with Vivapur 12 increased significantly starting by 1 week only.

For direct comparison between all binary mixtures the significant differences were determined for all degradation products at 12 weeks (Figure 5-5 B). It could be demonstrated that only the amount 6- β -hydroxy-EE differs significantly between all 3 binary mixtures. For 6- α -hydroxy-EE, 9(11)-dehydro-EE as well as 6-oxo-EE significant differences were determined from binary mixture with Vivapur 101 compared to the other binary mixtures only. Overall the highest amount of impurities was determined in binary mixture with Vivapur 101 with a particle size distribution of x_{50} = 55 μ m. The amount of degradation products in binary mixtures with the larger particles (Vivapur 12 with x_{50} = 146 μ m) and the binary mixture with smaller particles (Vivapur 105 with x_{50} =29 μ m) did not differ significantly. Therefore during opened storage of the binary mixtures no trend in degradation of EE due to the particle size of the used MCC could be determined.

It is assumed that the high amount of water that is available during opened storage at 40 °C/75 % r.h. overrules the effect of the particle size of MCC on the stability of EE that was observed during closed storage.

Figure 5-5: Degradation products EE in binary mixtures of MCC (40 °C/75 % r. h., open). mean values (n=3) with standard deviations. A) Comparison of binary mixtures during all testing points. Significant differences in impurity contents are indicated by brackets. B) Zoom to degradation products determined in binary mixtures after 12 weeks storage. Significant differences in impurity contents are indicated by brackets.

In conclusion the surface area of MCC as well as the residual moisture from the Vivapur-qualities influenced the stability of EE in the binary mixtures of the Vivapur qualities with EE during closed storage.

In the next step the spraying sequence during granulation of the new model formulation will be investigated regarding a potentially accelerated degradation of EE due to the contact of EE with MCC as main filler excipient.

5.2.2 Fluid bed granulation process- modeling of spraying sequences

The following investigations were performed during the fluid bed granulation process of the model formulation.

5.2.2.1 In-line measurement of particle size and granule moisture

Figure 5-6 shows the results of the in-line determination of granule moisture and particle size. The different sequences (see Figure 5-1, page 92) resulted in fingerprint-like diagrams of particle size and moisture content development. Every individual phase of the granulation process could be monitored using the in-line sensors. For each sequence a decreased particle size as well as a decreased moisture trend could be monitored during ethanolic DS-spraying. With the change to the aqueous binder solution, particle size and moisture increased. The largest particle size of 89 µm during the granulation process could be

measured for sequence 1 at the end of binder spraying (Figure 5-6 A). During spraying of EE the smallest particle size (approx. 28 μm) was found at sequence 1 when EE was sprayed immediately on the MCC-substance. After drying particle size of all three sequences showed particle sizes between 78 and 91 μm . In-line and off-line measured particle size showed the same trend. In-line as well as off-line the strongest increase in particle size could be measured for sequence 3 followed by a decrease after spraying of the binder solution. The same increase of particle size at the beginning of the first binder spraying phase as for sequence 3 could be measured for sequence 2 with both measurement systems. The delay in particle size growth at the beginning of granulation process of sequence 1 could be measured with both systems as well. The discrepancy between in-line and off-line measured particle size was already discussed in the previous sections of this thesis.

Figure 5-6: A) x_{50} particle size during fluid bed granulation process (lines: in-line measured particle size, dots: off-line measured particle size using laser diffraction), Mean values of $n=3$; B) Granule moisture during fluid bed granulation process (in-line measurement: lines, off-line measurement: dots), Mean values of $n=3$ batches per sequence

The product related calibration of the MWR-Sensor for in-line moisture measurement was performed with batches produced for investigation on influences of drying time on stability of EE (see chapter 4 of this thesis). The in-line measured moisture content of sequence 2 and sequence 3 shows a steep increase up to 10 % in the beginning of the granulation process (Figure 5-6 B). Subsequently for sequence 2 the moisture decreases due to ethanolic EE-solution spraying whereas for sequence 3 the moisture level is constant until ethanolic spraying of EE begins after approximately 50 min. During the second phase of binder spraying at sequence 2 the increase in granule moisture is slightly decreased compared to the first binder spraying phase at the beginning of the granulation process. At sequence 1 the increase in granule moisture starts after 26 min with the beginning of binder solution

spraying. The total granule moisture during binder spraying is similar for all 3 sequences between 9 % and 10 %.

By comparison of in-line and off-line measurement strong deviations could be determined between the measured moisture content especially during binder solution spraying at sequence 1 (Figure 5-6 B). During processing of sequence 1 firstly the ethanolic drug solution was sprayed on the excipients. Afterwards the aqueous binder solution spraying step was performed. No literature is available dealing with the influence of ethanol on the properties of MCC during fluid bed granulation process. Literature concerning wet granulation and spheronization processes showed that the use of ethanol instead of water as granulation fluid produces pellets from MCC with different properties regarding the strength, the porosity and the compressibility^{135;136}. It could be demonstrated that no changes in hydrogen bonding occur¹³⁷. A possible explanation could be the reaction of MCC with water as discussed in section 1.4.2.2.: during spraying of aqueous binder solution the contained water reacts with the polymer-structure and penetrates in the MCC⁵². This reaction with the active sites of MCC is not reversible and was already confirmed by NIR¹³⁸. It is assumed that the ethanol sprayed during the fluid bed granulation in sequence 1 influences the surface of the MCC powder. The water added during the following aqueous binder solution spraying step might therefore not penetrate in the deeper structures of MCC. The binding of water molecules would therefore be not as strong as in sequence 2 and sequence 3. In off-line LOD-measurement only delivered water is determined from the sample. Due to the not strongly bound water in granules from sequence 1 the water would be easily removed during the off-line LOD measurements whereas the strongly bound water in granules from sequence 2 and 3 cannot be removed entirely during the LOD measurements. Therefore the LOD values measured for sequence 1 aqueous binder solution spraying step are higher compared to the values determined for sequences 2 and 3. These differences would not be detectable during in-line measurement because with the MRT-method the entire water contained in the formulation is detected. This assumption might also explain lower LOD for sequences 2 and 3 compared to the in-line measured values within the entire granulation process. To measure this strongly bound water another off-line method for detection of water in molecules like Karl-Fischer would be necessary. Correspondingly, the discrepancy between the in-line and the off-line measured values should be removed by calibration of the in-line MRT-measurement method applying the appropriate sequence.

The defined end-point of the drying process with 6 % moisture measured in-line and the discrepancy between in-line and off-line measurement caused variations in the moisture of the end-product between 3.7 % at sequence 3 and 6.6 % at sequence 1. The best fit between in-line and off-line measured moisture content could be found at the end of the drying process for sequence 1 which is the sequence used for the standard granulation process. The calibration of the in-line MRT-sensor was done with this sequence (see chapter 4).

Nevertheless it could be shown that the in-line moisture measurement is a usable tool for characterization of the granulation process even if an end-point determination of the drying process was not possible. It shows reasonable values during the granulation process when the fingerprints for in-line measured moisture are combined to the in-line measured particle size: if the moisture in the granules increases the particle size increases as well and vice versa a decrease in granule moisture can be reflected to a decrease in granule particle size.

5.2.2.2 Effects of spraying sequence on stability of EE

The main issue of the presented study was the improvement of the DS stability. Figure 5-7 shows the measured impurities in the tablets after storage in accelerated conditions. The highest amount of impurities was found for sequence 1, the lowest amount was found for sequence 3. Significant differences between the impurities of the spraying sequences were detected for 4 weeks, 8 weeks and 12 months of storage. The significances for 4 weeks of storage are demonstrated in Figure 5-8 A. The highest influences were found for 9(11)-dehydro-EE that differed significantly between sequence 1 and sequence 2 as well as sequence 3 and furthermore between sequence 2 and sequence 3. After 8 weeks all impurities differ significantly between the sequences. The decrease in amount of impurities from sequence 1 to sequence 3 correlates well with the processing time including EE in the granules. In sequence 1 EE was sprayed at the beginning of the granulation process. In sequence 2 EE was sprayed in the middle of the granulation process and in sequence 3 EE was added at the end of the process. In section 5.2.2.1 the influence of ethanol on the surface of MCC and the possible influence on binding of water molecules in MCC were discussed. This mechanism might as well influence the stability of EE: due to the ethanolic EE-solution spraying step at the beginning of sequence 1 the surface of MCC could be modified by ethanol. Due to this modification the water molecules could not penetrate into the MCC-particles during the following aqueous binder-solution spraying step. The EE fixed on the surface of MCC-excipients was therefore overexposed to the water accelerating its

degradation. During sequence 2 and sequence 3 a part or even the entire aqueous binder solution was already sprayed on the MCC-surface. The water molecules could partly penetrate into the MCC particles. After spraying of EE the amount of free water molecules was reduced. The degradation rate of EE could therefore be decreased during sequence 2 and sequence 3. Another influence might be the contact between EE and MCC filler excipient: in sequence 1 EE is sprayed directly on the large surface of the MCC-powder whereas in sequence 2 EE is sprayed on a decreased surface of partly granulated MCC and furthermore EE is embedded with binder solution. In sequence 3 large MCC granules with a smaller particle surface exist before spraying of EE (Figure 5-6 A). This mechanism would conform to the results from section 5.2.1.2.

In the granules three effects might overlay: in sequence 2 and 3 MCC surface was already coated with binder when DS came into contact with the granules, coating might have protected DS against destabilizing interactions with the MCC surface. On the other hand the time of direct contact of EE with the water in the aqueous binder solution was highest in sequence 1 and lowest in sequence 3. Hence, the amount of free water that acts as accelerator for the degradation process was reduced during sequence 2 and sequence 3. Furthermore the processing time including EE in the granulator decreased from sequence 1 to sequence 3 leading to decreased thermal influences on EE.

Figure 5-7: Degradation products of EE in tablets (40°C/75% r.h., blistered), mean values (n=3) with standard deviations

Figure 5-8: Degradation products of EE in tablets after 4 weeks storage at 40°C/75 %r.h. (blistered), mean values (n=3) with standard deviations, brackets: significant differences between spray sequences for each degradation product

5.3 Conclusion

The investigations with binary mixtures from Lactose (Pharmatose 450M and Pharmatose 130M) respectively MCC (Vivapur 101) depicted that the stability of EE after opened storage at 40 °C/75 % r.h. is decreased in blends from EE and MCC. The increased amount of degradation products is attributed to interactions of water trapped in the molecular structure of MCC with EE. Overall the amount of degradation products determined in binary mixtures after closed storage was decreased compared to the amount of degradation products determined after opened storage. Therefore it can be assumed that the humidity and therefore the water in the atmosphere accelerates the degradation of EE in MCC. A dependency of the stability of EE from the surface of MCC could be demonstrated for the binary mixtures of MCC and EE stored at long term conditions (25 °C, 60 % r.h., closed) under elimination of air humidity. During opened storage under accelerated conditions (40 °C/75 % r. h.) the presence of air humidity overruled the effect of particle size of MCC on the stability of EE.

The investigations demonstrated that a technically feasible change of the spraying sequence might improve the stability of EE. The standard spraying sequence 1 showed the largest amount of impurities and a long processing time, whereas sequence 3 showed the lowest amount of impurities and the shortest processing time. It is assumed that coating with binder, the contact area with MCC and the processing time are lead to differences in the stability of EE in granules from the 3 spraying sequences.

The in-line measurements of particle size and granule moisture are useful tools to describe the granulation processes using the 3 different spraying sequences. By using the sensors fingerprints of the processes could be shown. Furthermore especially the particle size determination was useful to investigate the influences of the granulation process on the stability of EE. The in-line granule moisture measurement was highly influenced from the changes of the spraying sequence. It could be shown that an individual calibration is necessary for each spraying sequence.

An optimization of the granulation process regarding the stability of EE and the process time can be possible.

Chapter VI

---

6 Discussion and Conclusion

The aim of this thesis was the development of a fluid bed granulation process for a new model-formulation based on MCC as replacement for lactose. Ethinylestradiol was used as model API-substance. Process analytical technologies for monitoring of the critical quality attributes were implemented to increase process knowledge and to improve product quality. To this end the fluid bed granulator was equipped with sensors for in-line measurement of particle size (Spatial filtering technology sensor) and granule moisture (Microwave resonance technology-sensor) during fluid bed granulation process. The in-line measurement with these sensors was verified.

The model substance Ethinylestradiol (EE) is an estrogen substance that is prone to oxidative and thermal degradation^{33;31}. During the fluid bed granulation process parameters were varied which were supposed to have a high impact on the stability of EE due to influencing the product moisture and product temperature. The main degradation products of EE were used as indicator for the influence of the variations on the stability of EE.

Furthermore the direct influence of the new filler substance MCC on the stability of EE was investigated. Up to now no literature was published on the interaction of EE with MCC.

The following statements were in focus of this thesis:

1. Investigations on in-line sensors:

- Investigations on the positioning and configuration of the SFT sensor for in-line particle size monitoring:

The SFT-sensor for in-line particle size measurement was tested in different positions and configurations in the granulator. It is hypothesized that the measurement is influenced by the position of the sensor in the granulator and that the sensor might be blocked with substance in single positions. The best position and configuration of the sensor for the following investigations should be defined.

- Investigations on the calibration of the MRT-sensor for in-line moisture monitoring.

The sensor should be calibrated based on the off-line standard method (loss on drying). To this end samples were drawn from the granulator during fluid bed granulation of the model formulation. The granule moisture was determined via loss on drying. These investigations were the basis for the use of the sensor for in-line moisture measurement. It was assumed that the calibration for the granulation process is independent from external influences and blocking of the sensor. The determined calibration should be used for the following investigations.

2. Investigations on stability of EE as a function of the granulation process:

- Investigations on the influence of thermal stress due to a prolonged drying time on the stability of EE (drying time).

The produced granules were consciously over dried using the standard inlet air temperature. Therefore the drug substance was exposed to increased thermal stress. It is hypothesized that the stability of EE is decreased due to a prolonged drying time and increased thermal stress.

- Investigations on the influence of thermal stress due to variations of inlet air temperature during the drying step of fluid bed granulation on the stability of EE

The inlet air temperature during the drying process at the end of the fluid bed granulation process was varied. It is hypothesized that the stability of EE is influenced by the drying temperature due to thermal stress.

- Investigations on influences of the contact with filler excipients on stability of EE

Binary blends of MCC/EE respectively Lactose Monohydrate/EE were produced and tested for stability of EE. It is assumed that the stability of EE is influenced by the particle surface of the used filler substance due to the reaction with oxygen and moisture respectively chemical residuals.

In the second step EE containing granules were produced using granulation processes with different spraying regimes. These investigations should demonstrate whether the surface of MCC can be modified to increase the stability of EE in the formulation. Furthermore a change in the spraying sequence and the corresponding changes in process parameters might influence the stability of EE.

Finally it should be stated if a real time release based on in-line measurement of the parameters granule particle size and granule moisture measured with the SFT-sensor respectively the MRT-sensor is possible and if a new fluid bed granulation process leading to an increased stability of EE could be developed.

6.1 Discussion on sensor for in-line particle size measurement (SFT-sensor)

An SFT-Sensor was installed in the fluid bed granulator for in-line monitoring of particle size during the fluid bed granulation process. The sensor is already described in literature as a useful instrument for characterization of fluid bed granulation processes^{93;127;139}. Prior to in-line measurement of a fluid bed granulation process the sensor has to be qualified for the use in the process. An important step of this qualification process is the determination of the best position in the fluid bed granulator and the definition of the sensor configuration. As discussed in section 1.6.1 literature provides only little information on these issues.

The determination of the sensor-position was performed in connection with the sensor configuration using the model filling substance Microcrystalline Cellulose (MCC, Vivapur 101, see sections 3.3.3 and 3.3.1). It could be demonstrated for the model (Vivapur 101) that the positioning of the sensor in the deceleration zone of the granulator leads to measurement of high particle rates and reproducible data with less influence of the sensor configuration on the measurement results. An optimum position and configuration for the model Vivapur 101 in the deceleration zone was identified.

In a second step the influence of particle size of the model substance on the measurement results was investigated. To this end another MCC speciality (Avicel PH 102, see section 3.3.2) with an increased particle size was tested. In this system the segregation effect in the fluid bed that was already described in literature^{94;140-142} could be monitored: depending on the flow rate, the particle size and the velocity of fluidization¹⁴³ the smaller particles can be found in the upper layer (flotsam) whereas larger particles are found at the bottom (jetsam)¹²⁹. It could therefore be demonstrated that the in-line sensor can be used as a helpful tool to determine the homogeneity of mixtures. On the other hand during granulation of new substances the sensor in combination with off-line particle size determination could easily be utilized to detect segregation and to adjust the fluidization process parameters accordingly. Furthermore with these segregation effects it could be proven that negative influences on the process can be monitored with the in-line SFT sensor.

For verification of the determined in-line measurement position and configuration (model Vivapur 101) a model granulation process for placebo granules was performed (section 3.3.3). The in-line measurement results were compared to off-line measurement results using laser diffraction. Differences between the off-line measured particle size and the in-line

measured particle size could be assigned to the inability of the SFT sensor to measure particles $<50\mu\text{m}$. We showed that the in-line SFT sensor is able to monitor changes in particle size during the whole granulation process and that a fingerprint-like particle size profile is can be achieved for the granulation process.

In the next step the particle size was monitored in-line using the SFT sensor during experiments conducted for this thesis: tests on drying time (section 4.3.1.1), tests on drying temperature (section 4.3.1.1) and tests on spraying sequence (section 5.2.2.1). Figure 6-1 summarizes all in-line measured x_{50} particle size profiles. Results from the standard process (sequence 1/70 °C) were used as comparison for investigations on spraying sequence (section 5.2.2.1) and for drying temperature (section 4.3.1.1).

Figure 6-1: x_{50} Particle size profiles measured in-line during different granulation processes (summary of Figure 3-5 A, Figure 4-3 A and C, Figure 5-6 A)

It can be pointed out that differences between the processing are visible in the particle size profiles. The two profiles for tests on drying temperature (50 °C and 90 °C) are comparable with the standard process sequence 1/70 °C until start of the drying process as already mentioned in section 4.3.1.1. Differences in the spraying sequence over the entire granulation process are visible as well (as discussed in section 5.2.2.1). The profile monitored for the batch for verification of positioning and configuration differs due to the

different manufacturing process: this batch was manufactured as placebo-batch. Therefore no ethanolic spraying step was performed. Furthermore particle size profiles monitored during production of the batches for tests on drying time didn't show a steep particle sizes increase as it was monitored for the standard process. This will be discussed in the next section (see section 6.2).

Finally it could be shown with these data that influences on the fluid bed granulation process can be detected using the SFT-inline sensor. The verification of the measurement method for the recent model granulation process was possible in the determined optimum position and configuration of the sensor. Using the SFT-sensor for monitoring of other formulations and fluid bed granulator models require new investigations on the positioning and configuration of the sensor.

Further tests should be performed to investigate the influence of more process variables on the profile and to establish the finger-print like profile for the standard process. Before installation of the sensor in the granulator only direct process parameters like process temperature and differential pressure could be monitored. They already provided an estimation of the process quality due to process variations but no direct estimation of product quality was possible. Real time monitoring using the SFT sensor allows for a direct characterization of the product and is a helpful tool to detect variations during the granulation process and therefore to increase process quality. Real time release using SFT- sensor as discussed in literature⁹⁰ should be part of the development mind-set for a modern production surrounding. However, real time release is not possible under consideration of the current status of data. Further investigations on influence of process parameters on the fingerprint profile should be considered.

6.2 Discussion on sensor for in-line moisture measurement (MRT-sensor)

During fluid bed granulation the spraying of the granulation liquid induces the formation of liquid bridges and the start of the agglomeration¹⁴⁴. This complex process is influenced by a variety of parameters like liquid flow rate, inlet air humidity and inlet air temperature. The combined result of these parameters is the granule moisture that affects the granules growth rate and particle size. Granule moisture is therefore the best property to measure in order to achieve process control^{107;144}. Beside the influence of granule moisture on the granule structure and particle size, granule moisture furthermore might promote degradation of the API by hydrolysis¹⁴⁵. Hence, the moisture content of granules is a critical quality attribute that has to be determined to characterize the product quality. In the past product moisture was monitored during the granulation process indirectly by means of the product temperature or even the outlet-air temperature^{20;104;105}.

In this thesis the MRT-sensor was embedded directly into the fluid bed granulation process to measure the product moisture from the granules in the product container of the granulator. This position had to be used due to the necessity of covering the sensor with product. Further qualification tests regarding the positioning and configuration could be omitted. The main scope during qualification and for the described investigations was the calibration of the sensor in the granulation process for the model formulation and the verification of the calibration results in further tests.

The calibration was done against loss on drying (LOD/IR) in off-line determination during investigations on drying time of the granules (see section 4.3.2.1). LOD/IR is the standard in-process control for the evaluated fluid bed granulation process. The regression-coefficient was determined with $R^2=0,903$ for the granulation and drying process together. Literature presented regression coefficients of $R^2=0.995$ ¹¹⁹ and $R^2=0.976$ ¹¹⁸. But also these investigations showed that a linear calibration could only be determined for moisture ranges of 1.5 % - 4.5 %¹¹⁹ respectively < 10 %¹¹⁸ and 7.5 %¹¹². To describe the entire granulation process including granulation and drying step during this thesis a moisture range up to 9.5 % was measured and included in the calibration curve. This high moisture content might be responsible for a decreased correlation coefficient and therefore a calibration with less precision.

The verification of the MRT-calibration data-set was performed with batches for testing on influence of drying temperature (section 4.3.2.2) and testing on influence of spraying sequence (section 5.2.2.1). In both tests the granule moisture was determined off-line with LOD/IR during the whole granulation process to evaluate the quality of the MRT-calibration. The resulting graphs from in-line and off-line moisture determination are presented in Figure 6-2 A) and B). During granulation of both test-series differences between in-line and off-line measured granule moisture content were determined. The comparison of in-line and off-line moisture monitoring during tests on influence of drying temperature at 70 °C (equal to sequence 1) shows an off-set between the off-line data and the in-line monitored MRT moisture results (Figure 6-2 A). To investigate the source of this off-set the in-line measured particle size data were compared as well. Figure 6-1 shows different particle size of the granules from the calibration-batches (drying time) and the test-batches (drying temperature and spraying sequence). To determine the root cause for the source of the differences in the particle sizes between these two test-series as well as the off-set of the in-line monitored moisture the in-line monitored product temperature was evaluated as well. As already mentioned this parameter can be used for prediction of changes in granule moisture during the granulation process. The product temperature during the binder spraying step of the calibration-batches (test series on influence of drying time) showed a minimum of 31 °C (Figure 6-2 C) and was therefore increased compared to the other granulation processes (drying temperature and spraying sequence). The reason for this is that the binder solution spraying was performed very slowly within the allowed limits of the granulation process leading to an increased product temperature. This increased minimum product temperature during the calibration batches is an indicator that the granules were less wetted during the binder solution spraying step leading to a smaller increase of particle size during the granulation process as depicted in Figure 6-1. The minimum product temperature during spraying of all other batches during the test-series (influence of spraying sequence and influence of drying temperature) was below 28°C (Figure 6-2 C). The binder spraying step of these granulation processes was performed faster leading to wet granules with a steeper increase in particle size during the granulation process (Figure 6-1). Investigations already pointed out that the particle size influences the MRT-measurement results¹²¹. Therefore it is assumed that the differences in particle size during the granulation step as well as the increased wetting of the MCC-molecules due to the faster binder spraying step influenced the in-line moisture monitoring with the MRT-sensor and caused the off-set to off-line measured granule moisture.

The off-set to off-line measured granule moisture during sequence 2 and sequence 3 to decreased values compared to in-line measured granule moisture with MRT-sensor be assigned to the modification of the surface of MCC with ethanol and was already discussed in section 5.2.2.1.. A verification of the theory on modification of the surface of MCC-particles with ethanol e.g. using x-ray diffractometry would be useful.

Figure 6-2: A) Granule moisture during variation of inlet-air temperature during drying process (in-line measurement: lines, off-line measurement: dots), Mean value of $n=3$ batches per temperature; B) Granule moisture during fluid bed granulation process (in-line measurement: lines, off-line measurement: dots), Mean values of $n=3$ batches per sequence; batches from sequence 1 and tests on 70°C drying temperature are similar C) Minimum of in-line measured product temperature in the fluid bed granulator during spraying of aqueous binder solution for every batch separated according to the individual tests.

Overall it can be concluded that the calibration of the SFT-sensor in the model-fluid bed granulation process is influenced by different aspects:

1. Due to increased product moisture during granulation the precision of the calibration is decreased. This issue was already discussed in literature^{112;118}. Investigations on a

new sensor including 4 wavelengths in the evaluation of data to increase the moisture measurement range were already published¹⁴⁴.

2. Changes in granulation process leading to a stronger wetting of the MCC and to an increased particle size during the granulation process influence the in-line monitoring of the granule moisture.
3. Changes in the granulation sequence influence the in-line monitoring of the granule moisture due to interactions of the MCC with ethanol and the following changed interaction of MCC with water.

These aspects have to be considered when the MRT-sensor for in-line moisture measurement is implemented in the fluid bed granulation process. The off-sets of the in-line and the off-line measured granule moisture might be eliminated by calibrating the sensor for each individual granulation process. The precision of the calibration of the sensor could be improved by using the new 4-wavelength-sensor that should measure linear in a granule moisture range up to 14 %¹⁴⁴.

With the currently available data it can be stated that a real-time release of the model-granules regarding granule moisture utilizing the MRT-sensor calibrated on off-line LOD-measurements is not possible. It could be demonstrated that the MRT-measurement is dependent from different external factors.

Even though it could be shown that a finger-print of the granulation process and changes during the process can be indicated using the sensor.

6.3 Discussion on stability of Ethinylestradiol

The stability of the drug substance is the third critical quality attribute of the granulation product. It can be measured in the granules as well as in the final tablets. The degradation process of Ethinylestradiol (EE) is accelerated by oxygen^{33;27;28} and thermal influences³¹. Water is known to be a catalyst for oxidative degradation processes^{38;40;41}.

6.3.1 Conclusions from investigations on stability of EE

The standard granulation process that was investigated during this thesis consists of different process steps:

1. prewarming of the excipients
2. spraying of ethanolic drug substance solution
3. spraying of aqueous binder solution
4. drying of granules

During this standard fluid bed granulation process Ethinylestradiol is sprayed as ethanolic solution in step 2. It is therefore exposed to oxygen due to large amounts of air passing through the product to keep the fluidized status. In the next step, the spraying of the aqueous binder solution, the product is wetted due to the amount of water sprayed into the granulator. Therefore the drying step leads to an increased product temperature. Summarizing, with each process step the degradation of EE might be accelerated due to factors resulting from the granulation process.

This thesis aimed to investigate the influence of process parameters drying time, drying temperature (thermal stress) and contact with the surface of the filler material on the stability of EE in the model formulation. In this model formulation microcrystalline cellulose was used as main filler substance instead of lactose.

For tests on variation of drying time the model formulation was granulated in the fluid bed granulator and dried up to 30 min. During the drying time samples were drawn for stability testing. It could be demonstrated that the samples with shortest drying (0 min) time and therefore the highest product moisture (8.35 %) present the highest amount of impurities after storage (Figure 4-5 E, F, G). Significant differences were determined for 6- α -hydroxy-EE, 6- β -hydroxy-EE and 9(11)-dehydro-EE after 8 weeks closed storage at

40 °C/75 % r.h. and furthermore for 6-oxo-EE after 12 weeks closed storage at 40 °C/75 % r.h. respectively 24 months closed storage at 25 °C/60 % r.h.. No differences could be detected in the start-samples of all 3 drying times that would be an indicator for thermal influences depending on drying time during the drying process. Therefore it could be stated that the degradation process of EE during the respective experiment was moisture driven. A longer exposure to air oxygen and higher process-temperatures due to a longer drying time (Figure 6-5 A) did not affect the stability of EE in this experiment.

Investigations on influence of thermal stress on the stability of EE were performed by granulating the model formulation in the fluid bed granulator and drying the granules at 50 °C respectively 70 °C or 90 °C inlet air temperature. Significantly increased amounts of 6-beta-hydroxy-EE, 9(11)-dehydro-EE and 6-oxo-EE differences were determined in samples dried at 90 °C inlet air temperature after 8 weeks of storage at 40 °C/75 % r.h. (Figure 4-5 D). This indicates an influence of the thermal stress during the drying process due to the increased drying temperature in the presence of water. The product temperature at the end of drying with inlet-air temperature 90 °C was measured at 47 °C (for inlet-air temperature: 70 °C: 39 °C) Hence, the granules dried at 90°C showed the lowest LOD with 5.9 % compared to granules dried at 50 °C (LOD=7.3 %) and 70 °C (LOD= 7.1 %). At this point the thermal stress due to increased drying temperature overrules the influence of the product moisture in the range of 6 % to 7 % LOD.

For tests on influence of the used filler materials and the contact area of the main excipient MCC on the stability of EE the drug substance was dissolved in ethanol and sprayed on the surface of different lactose-respectively MCC-grades (binary mixtures). Samples of these mixtures were investigated on stability of EE. In these tests it could be demonstrated that during opened storage the amount of all impurities in the lactose-grades was decreased compared to the amount of impurities found for MCC (Figure 5-2). The highest amount of degradation product was determined for 9(11)-dehydro-EE. Between both tested lactose-grades significant differences regarding the impurities could be measured for 9(11)-dehydro-EE as well. The closed storage of the samples showed a completely different picture (Figure 5-3): the highest amount of degradation products was determined for the binary mixture with the largest particle size (Pharmatose 130). In this mixture all impurities were significantly increased after 12 weeks of storage. The amount of impurities in the binary mixture with MCC (Vivapur 101) was comparable with the amount determined in the binary mixture with the lactose of smaller particle size. In the binary mixture with MCC the impurity with the

steepest increase again was 9(11)-dehydro-EE. The increased amount of impurities after opened storage of MCC-containing binary mixtures could be attributed to the sponge-like-behaviour of MCC.

During closed storage at 25 °C/60 % r.h. (24 months) of binary mixtures from different MCC-grades in tests on influence of contact area of EE with the main filler substance MCC it could be shown that the amount of impurities correlates with the particle size of MCC substance: the larger the particle size and therefore the smaller the specific surface area the lesser the amount of impurities that was determined. The highest rate of impurities was determined for binary mixture with Vivapur 105 ($x_{50}=29\text{ }\mu\text{m}$). The lowest rate of impurities was detected for binary mixture with Vivapur 12 ($x_{50}=146\text{ }\mu\text{m}$). The main indicators after 24 months were 6- α -hydroxy-EE and 9(11)-dehydro-EE. For both impurities correlations between particle size of MCC and the amount of degradation product could be determined (*Figure 5-4 B*).

Stability studies for investigations on influence of different spraying sequences (*Figure 5-8*) showed significant differences for all degradation products after 4 weeks storage at 40 °C/75 % r.h.. Sequence 3 (BM-EE) had the smallest amount of impurities. This effect could be explained with a coating of the surface of MCC with ethanol, no contact of EE with aqueous binder solution and the short processing time of EE in the granulator.

6.3.2 Influence of process parameters on stability of Ethinylestradiol

The following section investigates relations between the stability of EE measured as the amount of its degradation products and all tested process parameters with the aim to determine the most important parameters influencing the stability of EE and therefore the main dependency of the individual degradation product from the process. To this end the results for degradation products from all investigations are compared as available for storage time points 8 weeks at 40 °C/75 % r.h. respectively 24 months at 25 °C/60 % r.h.. The following *Figure 6-3* and *Figure 6-4* provide an overview on the results for each degradation product at start of storage and the respective storage time point. *Figure 6-5* presents an overview on factors that are supposed to trigger the degradation of EE: Temperature and drying time are variables of the process that influence as well each other^{10;17}. Both variables influence the product moisture (measured as LOD) which is a CQA of the product that is supposed to influence the stability of EE as well.

A) Start

B) 8 weeks

C) Start

D) 8 weeks

E) Start

F) 8 weeks

G) Start

H) 8 weeks

Figure 6-3: Comparison of degradation products during all investigations at 40 °C/75 % r.h. after start and 8 weeks storage (closed/ opened/ blistered storage)

A) Start

B)

24

months

C)

Start

D)

24

months

E)

Start

F)

24

months

Figure 6-4: Comparison of degradation products during all investigations at 25 °C/60 % r.h. after Start and 24 months storage (closed storage)

By comparison of impurities from tests on influence of granulation process parameters (tests on drying temperature, spraying sequence and drying time, Figure 6-3 and Figure 6-4) it can be clearly seen that the amount of impurities were similar at start of the storage in all tests except for tests on drying time regarding 6-oxo-EE (Figure 6-3 G). This indicates that changes of the process do not influence the stability of EE directly but influence the bonding of the water in the molecules leading to differences in stability of EE during storage of the samples.

The start-values of all degradation products from tests on drying temperature at 70 °C and drying time at 15 min can be directly compared. This is because 70°C is the standard inlet-air temperature usually used for drying and the drying time during the tests on that drying temperature was: 16 min. The results of both test-conditions can therefore be used as bridging point at start. As already mentioned above there is a difference between both test-series: 6-oxo-EE was determined in start samples from test on drying time to the same extend in all three samples (Figure 6-3 G, Figure 6-4 G). This impurity was not detected in samples from tests on influence of drying temperature 70 °C (Figure 6-3 G). Both test series differ regarding product-temperature during granulation process which was increased during tests on drying time as already mentioned in section 6.2, Figure 6-2 C. During the process step 'drying' the product-temperature in the test on drying time was measured at maximum 49 °C and therefore increased compared to tests on influence of inlet-air temperature during process step 'drying' (70 °C drying temperature: 39 °C). This difference in temperature indicates that the degradation of EE forming 6-oxo-EE might be triggered by thermal influences. Further reflexions on the influences of process attributes on the stability of EE will be done in the following section.

6- α -hydroxy-EE as well as 6- β -hydroxy-EE was slightly increased at time point start in samples from tests on influence of product temperature (50 °C, 70 °C, 90 °C), spraying sequence (EE_BM, BM_EE_BM, BM_EE) and drying time (0 min, 15 min, 90 min) (Figure 6-3 A and C, Figure 6-4 A and C). Comparatively small amounts of these degradation products at time point start were determined in samples from binary blends (P450 M, P130M, Viv 101, Viv 105 and Viv 106). This indicates that 6- α -hydroxy-EE and 6- β -hydroxy-EE are formed during the granulation process triggered by process temperature, humidity and process time. 9(11)-dehydro-EE was present in all samples at time point start (Figure 6-3 E, Figure 6-4 E). The formation of this degradation product is therefore supposed to be fast and independent from the primary process.

The amount of all degradation products increased with increasing product moisture in the samples: the highest amount of each degradation product was determined in the sample of opened stored binary blend of MCC (Viv101) (Figure 6-3 B, D, F, H). An extraordinary high amount could be found for 9(11)-dehydro-EE (Figure 6-3 F) after opened storage for 8 weeks at 40 °C/75 % r.h. that could not be detected after closed storage for 24 months at 25 °C/60 % r.h. (Figure 6-4 F). It was already discussed that the sponge-like behaviour of MCC causes an increased bounding of water from the air humidity that catalysed degradation reactions. A trending in the amount of degradation product depending on the particle size of MCC was determined for 6- α -hydroxy-EE and 9(11)-dehydro-EE after 24 months in closed storage at 25 °C/60 % r.h (Figure 6-4 B, F). This trend could be attributed to the increase of particle surface and therefore the increase of the contact area of EE with MCC (section 5.2.1.2).

Influences of product moisture could be determined for all degradation products for the test-series drying time: at 0 min drying time the highest product moisture was measured (8.4 %) showing the highest amount of all degradation products within this series. In the sample of lowest product moisture after 30 min drying time (3.4 %) the smallest amount of all degradation products were determined (Figure 6-3 B, D, F, H and Figure 6-4 B, D, H). Influences of process time were determined for all degradation products for samples on spraying sequence (EE_BM, BM_EE_BM, BM_EE) (Figure 6-3 B, D, F, H): the longest process-time in spraying sequence EE_BM of 55 min (Figure 6-5 C) caused the highest amounts of impurities. Only 6-oxo-EE showed a clear dependency from process temperature in the test series on influence of drying temperature (50 °C, 70 °C, 90 °C): the amount of 6-oxo-EE increased with increasing drying temperature (Figure 6-5 A, Figure 6-3 H).

During all tests 6-oxo-EE displayed the highest extend of increase compared to the other degradation products.

Figure 6-5: Factors influencing degradation of EE for each investigation test series: A) Product temperature measured from fluid bed granulator during process (tests on drying temperature: maximum product temperature during drying; tests on spraying sequence: mean temperature during time EE in process; drying time: temperature measured at sampling; binary mixtures: maximum temperature during time EE in process); B) LOD values from samples; C) Time of EE in process from measured from start spraying ethanolic EE - solution

In the following section the amounts of degradation products measured after 8 weeks storage at 40 °C/75 % r.h. of all test series are correlated against the measured values for the process parameters process time and process temperature as well as the determined CQA LOD to investigate the degree of influence of the parameters on the stability of EE. The source of parameters for correlation is summarized in Figure 6-5. The following diagrams summarize linear correlations with $R^2 > 0.9$ of the investigated parameters with the

degradation products of EE (Figure 6-6 to Figure 6-8). Correlations with $R^2 < 0.9$ are not depicted in the diagrams.

The correlation of the amount of degradation products with LOD showed strong correlation with $R^2 = 0.9977$ for 9 (11)-dehydro-EE, $R^2 = 0.9999$ for 6-oxo-EE and $R^2 = 0.9977$ for 6-alpha-hydroxy-EE in tests on influence of drying time after 8 weeks closed storage at 40 °C/75 % r.h. (Figure 6-6 A). Results from correlations with LOD in investigations on influence of spraying sequence show a weak correlation with $R^2 = 0.9194$ for 9(11)-dehydro-EE (Figure 6-6 B). Strong correlations with $R^2 = 0.9733$ for 6-beta-hydroxy-EE and $R^2 = 0.9987$ for 6-alpha-hydroxy-EE could be determined from investigations on drying temperature (Figure 6-6 C).

Figure 6-6: Correlation of degradation products of EE with LOD: A) Investigations on influence of drying time (40 °C/75 % r.h., 8 weeks storage, closed); B) Investigations on influence of spraying sequence (40 °C/75 % r.h., 8 weeks storage, blistered); C) Investigations on influence of drying temperature (40 °C/75 % r.h., 8 weeks storage, blistered); Lines in diagrams are linear regressions with R^2 as regression coefficient

Correlations of degradation products with drying time showed promising results for 9(11)-dehydro-EE, 6-alpha-hydroxy-EE and 6-oxo-EE (Figure 6-7 A). The correlation with time EE in process (measurement of time started with begin of spraying ethanolic EE-solution, Figure 6-7 D) shows a good correlation with $R^2=0.9886$ for 6-oxo-EE. Comparably weaker correlations were determined for 6-alpha-hydroxy-EE and 6-beta-hydroxy-EE (Figure 6-7 B). Results from investigations on influence of drying temperature show only a weak correlation for 6-oxo-EE with time EE in process (Figure 6-7 C).

Figure 6-7: Correlation of degradation products of EE with time: A) Investigations on influence of drying time, correlation with drying time (40 °C/75 % r.h., 8 weeks storage, closed); B) Investigations on influence of spraying sequence, correlation with Time EE in process (40 °C/75 % r.h., 8 weeks storage, blistered); C) Investigations on influence of drying temperature, correlation with time EE in process from start spraying EE solution (40 °C/75 % r.h., 8 weeks storage, blistered); D) Investigations on influence of spraying sequence, Process time for binder- and API-spraying for every sequence; Lines in diagrams are linear regressions with R^2 as regression coefficient

In tests on influence of drying time strong correlations for all degradation products were determined with product temperature (Figure 6-7 A). The results from all other investigations (influence of spraying sequence and drying temperature) showed a correlation of degradation products with the product temperature respectively drying temperature only with 6-oxo-EE (Figure 6-7 B, C and D).

Figure 6-8: Correlation with Temperature: A) Investigations on influence of drying time, correlation with product temperature (40 °C/75 % r.h., 8 weeks storage, closed); B) Investigations on influence of spraying sequence, correlation with mean product temperature during EE in process (40 °C/75 % r.h., 8 weeks storage, blistered); C) Investigations on influence of drying temperature, correlation with inlet air temperature during drying (40 °C/75 % r.h., 8 weeks storage, blistered); D) Investigations on influence of drying temperature, correlation with maximum product temperature during drying (40 °C/75 % r.h., 8 weeks storage, blistered); Lines in diagrams are linear regressions with R² as regression coefficient

The results from investigations on drying time (Figure 6-6 A, Figure 6-7 A, Figure 6-8 A) show that a long process time ends in a low LOD of the samples and therefore an increased product temperature (no decrease of temperature due to evaporation of residual water). The amount of degradation products and the calculated correlations determined can therefore be

attributed to the amount of water retained in the samples (LOD). The water in process during spraying impacts the degradation of EE to a minor degree. The results from investigations on drying temperature show interactions of the correlated parameters: an increased drying temperature results in a short drying time.

Summarizing the results on correlation of the CQA Loss on drying as well as the process parameter time and temperature it can be assumed that the formation of 6-oxo-EE is to an increased extent thermally controlled whereas the formation of 6- α -hydroxy-EE, 6- β -hydroxy-EE and 9(11)-dehydro-EE is catalysed by moisture.

6.4 Conclusion

This thesis investigated the influence of the variation of key-parameters on the critical quality attributes particle size, granule moisture and stability of EE in a fluidized bed granulation process. Microcrystalline Cellulose was used as main filler substance in the model formulation. According to the PAT-approach of the authorities in-line sensors were installed to monitor the granule particle size and granule moisture during the granulation process and to gain better understanding on the process.

The SFT-sensor for in-line particle size monitoring could be installed successfully. The optimum position and configuration for in-line particle size measurement in the fluid bed granulator for the model formulation could be determined. During granulation of model formulations in different granulation processes it could be demonstrated that a finger-print-like characterization of the granulation process can be observed. Despite of variations of the SFT-sensor from off-line measurement in the first granulation phases (pre-warming and drug substance solution spraying) a good accuracy of the method could be determined for the last granulation phase- the drying process. This granulation phase is of crucial importance for the further processing of the granules^{17;65-67}. During the recent investigations the in-line measured particle size results from SFT-sensor could be used to identify the root cause for deviations in in-line LOD-measurement with MRT-sensor from the off-line measured LOD-results (section 6.2).

The MRT-sensor for in-line moisture monitoring was calibrated by means of the model granulation under variation of the drying time. The regression coefficient was determined. However, deviations to the reference method LOD and strong dependencies from the granulation process were identified. Nevertheless, fingerprint-like charts for granulation processes with variations in the spraying sequence and the drying temperature could be monitored. Further investigations should be done on new sensors measuring with two or more frequencies.

The stability of EE was investigated under consideration of the influence of the thermal stress due to prolonged drying time, variations in in-let air temperature during drying and contacts with the filler excipients. It could be demonstrated that a prolonged drying time increases the stability of EE due to decreasing amount of water in the granules. Increasing drying temperature resulted in a decreased stability of EE due to thermal stress. It could be shown that the surface of the main filler substance influences the stability of EE as well: a

decreasing particle size and therefore increasing surface resulted in a decreased stability of EE. The surface of the main filler substance MCC could be modified by a change of the spraying sequence.

6-oxo-EE was identified as the main degradation product showing the largest increase of its amount during storage and the best correlation with thermal as well as moisture influences. It could be confirmed that the moisture as well as thermal influences impact the stability of EE in the formulation. Up to now no investigations were published discussing these interactions of the stability of EE in a drug substance formulation.

Two approaches could be implemented to improve the fluid bed granulation process regarding control of moisture in the formulation (measured as LOD) and decreasing the thermic influences to improve the stability of EE.

1. Slowly spraying of aqueous binder solution:

The aqueous binder solution could be sprayed slowly in the granulator during the conventional spray regime to avoid a strong wetting of the granules. Besides the in-line moisture control a proper in-line monitoring of the particle size and the product temperature is recommended to control the particle size growth during the process and to prevent the formation of 6-oxo-EE due to high product temperatures. The overall process-time is not influenced by this approach: due to the minor wetting of the granules the drying time can be reduced

2. Change in spraying sequence:

In this thesis different spraying sequences were evaluated. The spraying sequence BM-EE could be shown as beneficial in terms of stability of EE. Furthermore it was the spraying sequence with the shortest process time. A dedicated end-point-control of the drying process can be eliminated due to the drying of the granules during the EE-spraying step.

This conclusion clearly shows that beside the critical quality attributes of the granules economical aspects in terms of limitation of the process time and process resources have to be considered during optimization of a fluid bed granulation process.

The results of this theses showed that an optimization of the fluid bed granulation process regarding the stability of EE is possible. The utilized in-line sensors provided a finger-print of the individual processes and could be helpful tools for optimization of the process. However,

it is not possible to replace the current used off-line end-point controls of the granulation process with the described in-line methods.

Chapter VII

---

7 Summary

Quality initiatives of the FDA and the ICH ask for PAT-approaches as standard during the whole life-cycle of drugs including the development of a formulation. A better understanding of the development and manufacturing process should be gathered to improve and consolidate the quality of the drug product^{3;4;42}. These PAT approaches include amongst others physical methods for characterization and monitoring of manufacturing processes. The methods should be based on predefined process- and formulation dependent critical quality attributes (CQAs) and critical process parameters (CPPs). To this end the implementation of process analyzers for monitoring of these CQAs and CPPs during the manufacturing process should ideally end up in real time release of products.

Ethinylestradiol (EE) is the most commonly used estrogen substance¹ in oral hormonal contraceptives. It is frequently processed in tablets for oral use. EE is highly active and therefore low dosed in the formulation. Furthermore, it is prone to oxidative degradation processes²⁹⁻³¹. During development of a pharmaceutical formulation containing EE the homogenous drug distribution and the stability of the drug must be in focus. In manufacturing of tablets for oral use the granulation procedure can be regarded as an important key-technology to control the quality attributes of the drug product. Therefore it is of crucial importance to understand and control the granulation process.

During development of the new model formulation containing the low dose steroid hormone EE as drug substance and Microcrystalline Cellulose (MCC) as main filling excipient in a film tablet the stability of EE, the particle size of the granules and the granule moisture were identified as critical quality attributes of the product during the process step 'fluid bed granulation'. Due to a possible oxidative degradation of EE the stability should be the leading attribute describing the quality of the entire formulation. Particle size of the granules and granule moisture are important parameters influencing the properties of the tablets as well as the stability of EE^{10;17}.

In context of this thesis formulations containing EE were investigated regarding the applicability of critical process parameters during development as well as their use as release criterion in future manufacturing processes.

The aim of this thesis was the development of an effective and mild fluid bed granulation process of a new model-formulation with EE as drug substance. For this formulation Lactose was replaced by MCC as main filler excipient to meet the expectations of many users for lactose-free tablets. Requirements of the PAT initiatives were included to design a robust

process during development and for the following manufacturing. For this purpose new technologies for in-line monitoring of the critical quality attributes particle size and granule moisture during fluid bed granulation were installed in the granulator. The proper installation and calibration of these in-line sensors as a central point in case of qualification of a measurement system was the basis for further investigations.

In-line particle size measurement was performed using spatial filtering technology. The in-line monitoring with this sensor during fluid bed granulation was described in several studies^{94;96;101} but no details on the effects of sensor positioning and configuration on the measurement were provided. For this reason the influence of the parameters positioning and configuration of the sensor on the measurement results was tested during fluidization of two different MCC grades in the granulator. It could be demonstrated on the basis of the standard MCC-quality Vivapur 101 that the results measured in the deceleration zone are more reliable compared to results measured in the product container. Furthermore influences of the sensor depth as well as the rotation angle on the results were investigated to estimate influences due to accidentally caused variations in measurement set-up. Based on these investigations the optimal sensor configuration (sensor installation depth and rotation angle) was determined by statistical analysis of the particle size data for the standard model MCC (Vivapur 101). Segregation was demonstrated for the coarser MCC-grade (Avicel PH 102) fluidized under the same fluidization conditions as the standard MCC (Vivapur 101) leading to smaller particle size results in the deceleration zone than in the product container. Therefore placement of the sensor in the deceleration zone appears to be reasonable as long as a non-sorting fluid bed exists. The measurement in the position and configuration determined for the standard MCC was verified during a standard granulation process. All process steps were representable in the particle size profile (x_{50} approx. 60 μm to 100 μm). The correlation with the off-line laser diffraction measurement could be shown. The in-line measured particle size in the range of particles below 50 μm showed differences compared to the off-line measured particle size from laser diffraction. In fact, the particle size at the end of the granulation process is of high importance for further processing of the granules. In this process-phase the in-line and off-line measured x_{50} and x_{90} values were comparable. For smaller particles (x_{10}) no accordance could be determined. Hence, variations within the granulation process (e.g. drying temperature or drying time) were detectable. Real time release might be possible in case further investigations on the influence of process parameters on the measurement would be performed. For other test systems (formulations, granulators) the validation of in-line particle size measurement with off-line laser diffraction

as well as the repetition of tests for sensor position for new formulations is strongly recommended.

The MRT (Microwave resonance technology) sensor of in-line measurement of granule moisture was placed in the product container. It was calibrated against standard off-line loss on drying method (LOD/IR) during a standard granulation process. The regression coefficient was determined with 0.903. During the following granulation processes performed for this thesis deviations were detected between in-line and off-line measurement results. These deviations are the results of differences in the granulation process between the batches for calibration and the following granulation processes. Nevertheless, the granule moisture during different fluid bed granulation processes could be monitored. Fingerprints of the processes were presented. However, a replacement of the standard end-point determination using off-line LOD/IR by the MRT-sensor is not possible. Further investigations on MRT-sensors measuring with 2 respectively 4 frequencies instead of one frequency were already described in literature^{146;147}. This should improve the in-line moisture evaluation in fluid bed granulation process.

Beside installation and validation of the in-line sensors for monitoring of the CQA granule particle size and granule moisture the stability EE in the new formulation depending on process variables was investigated. Due to the knowledge on the oxidative degradation of EE, the focus was set on the following three subjects with the aim to develop a mild and effective granulation process:

- Influence of the granule moisture and thermal stress during the drying process by variation of the drying time
- Influence of the thermal stress during drying process by variation of the drying temperature
- Influence of the contact with filler excipients during fluid bed granulation process by investigation of binary mixtures and different spraying sequences of the binder solution

All investigations were performed under consideration of in-line measurement systems to describe variations of the particle size (spatial filtering technology, SFT-sensor) and the granule moisture (Microwave resonance technology, MRT-sensor) during the entire granulation process.

To describe the stability of EE during the tests the leading degradation products of EE (6- α -hydroxy-EE, 6- β -hydroxy-EE, 9(11)-dehydro-EE, 6-oxo-EE²⁹⁻³¹) were quantified and compared.

For investigations on the influence of drying time three batches of the MCC-based model formulation were manufactured and consciously over dried (up to 30 min drying time). Samples were drawn at different drying times (after 0 min, 15 min, 30 min drying time). They were sealed and tested on stability of EE. With these data thermic influences as well as the influence of granule moisture on the stability of EE could be investigated. By evaluation of degradation products determined in the sample from starting point of stability investigations the influence of thermal stress due to a prolonged drying time should be visible in the results. The influence of different granule moisture resulting from different drying times would be detected after closed storage in sealed vials. Directly after granulation the amount of degradation products showed no significant differences in all samples. This indicates that the time of drying and therefore the thermic stress did not influence the stability of EE. Remarkable differences in degradation products were found between the samples of different initial moisture due to drying time with ongoing storage time in all groups: After storage of the samples granules with an LOD of 8.35 % (0 min drying time) for 12 weeks at 40 °C/75 % r.h. all degradation products were significantly increased compared to granules with LOD 3.43 % (30 min drying time). Therefore the hypothesis could be confirmed that granule moisture accelerates EE degradation.

The influence of thermal stress during the drying process was investigated by variation of the drying temperature at 50 °C, 70 °C (standard) and 90 °C. Three batches of the MCC based model-formulation were produced at each temperature. All granules were dried to moisture content of 6-7 % as measured in-line via MRT-sensor. The resulting granules were compressed and investigated on stability of EE. Significantly increased amounts of degradation products were determined after 8 weeks storage at 40 °C/75 % r.h. in samples dried at 90 °C. Therefore it can be concluded that the thermic stress during drying influenced the stability of EE.

In the recent model formulation lactose monohydrate was replaced by MCC as main filler substance. To investigate the influence of the change in the main filler substance on the stability of EE binary mixtures from different grades of lactose monohydrate respectively MCC with EE were produced in the granulator. EE was sprayed as ethanolic solution on each excipient. Samples of these binary blends were stored in opened as well as in closed

glass vials and investigated for degradation products of EE. Significantly increased amounts of degradation products determined in opened stored binary blends of MCC with EE could be assigned to the uptake and inclusion of water in the molecular structure of MCC as already described in literature^{57;134}. The measured amounts of degradation products after closed storage were comparable low for both excipients. These investigations showed that the contact of EE with MCC influences the stability of EE in the presence of water.

In the next step the influence of the contact area of MCC and EE was evaluated by preparing binary blends of EE with different qualities of MCC representing a range of different particle sizes (Vivapur 105, Vivapur 101, Vivapur 12). Samples of the resulting binary blends were stored in closed glass vials to eliminate the influence of external air humidity. The lowest amount of degradation products was detected in binary blends with Vivapur 12 (largest particle size) and the highest amount of degradation products in Vivapur 105 (smallest particle size). Hence, it can be concluded that the decreased particles size distribution and therefore increased specific surface area of the binary blend with Vivapur 105 caused an increased degradation of EE due to increased contact area. This promotes the contact of water included in the molecular structure of MCC with EE and therefore accelerates the degradation of EE.

During fluid bed granulation process EE is in close contact with the MCC-surface. Therefore it was obvious to vary the spraying sequence of aqueous binder solution and ethanolic EE solution to influence the contact time of EE with MCC. During the standard-process firstly the ethanolic EE-solution is sprayed on the prewarmed filler substance (MCC) followed by the binder solution (sequence 1). In the tested sequence 2 the binder solution was split in two similar portions: the first part of the binder solution was sprayed on the prewarmed filler material (MCC) followed by the ethanolic EE-solution and the second portion of the binder solution. Sequence 3 turns the standard procedure vice versa to protect EE: firstly the entire amount of binder solution was sprayed on the prewarmed filler material (MCC) followed by the ethanolic EE- solution. The granulation process was monitored using SFT and MRT for particle size and granule moisture determination. The granules were tableted, blistered in PVC/Aluminium and stored for stability investigations. The highest amounts of degradation products were found for sequence 1, the lowest amount was found for sequence 3. Significant differences were detected between all of these sequences. The off-line as well as the in-line measurement of particle size depict that sequence 3 has the largest particle size and sequence 1 has the smallest particle size prior to spraying of EE-solution. Furthermore

during the entire granulation process of sequence 3 the smallest amount of moisture was detected in-line as well as off-line in the presence of EE. It is assumed that three effects overlay in the granules: on the one hand the covering of the MCC-surface with binder and therefore a decreased contact area between both substances, on the other hand the shorter contact time of EE with water and third the shortened overall processing time of EE in the fluid bed granulator might have caused an increased stability of EE in samples produced with sequence 3.

By cross-evaluation of all results it could be demonstrated that the formation of 6-oxo-EE is mainly thermically controlled whereas the formation of 6- α -hydroxy-EE, 6- β -hydroxy-EE and 9(11)-dehydro-EE is mainly triggered by moisture. Correlations could be determined for 6-oxo-EE from thermal influences as well as granule moisture.

Overall it could be demonstrated that an effective and mild fluid bed granulation process can be developed by changing the granulation sequence to increase the stability of EE. It could be demonstrated that in-line monitoring of particle size using SFT- sensor is a suitable tool to investigate and control the fluid bed granulation process. In-line monitoring of the critical quality attribute granule moisture with the used MRT- sensor is restricted. Discrepancies between in-line and off-line measurement were detected for the granule moisture.

Chapter VIII

---

8 Zusammenfassung

Die amerikanische FDA und die internationale ICH- Organisation fordern die Umsetzung von PAT-Standards für den gesamten Lebenszyklus eines Arzneimittels, also bereits während der Entwicklung. Durch ein besseres Verständnis des Entwicklungs- und Herstellungsprozesses soll die Qualität des Arzneimittels erhöht werden^{3;4;42}. Zu den PAT-Methoden zählen unter anderem physikalische Methoden zur Charakterisierung und Kontrolle des Herstellprozesses. Grundlage bilden dabei vordefinierte prozess- und formulierungsabhängige kritische Qualitätsmerkmale (CQAs) und kritische Prozessparameter (CPPs). Die Kontrolle dieser Qualitätsmerkmale und Prozessparameter ermöglicht im Idealfall eine Produktfreigabe in Echtzeit.

Ethinylestradiol (EE) ist das für die hormonale Kontrazeption am häufigsten verwendete Estrogen¹. Es wird häufig in Tabletten zur oralen Anwendung verabreicht. EE besitzt eine hohe Aktivität und kann somit sehr gering dosiert werden. Der oxidative Abbau des Wirkstoffes²⁹⁻³¹ bedingt eine hohe Instabilität. Aufgrund der niedrigen Dosierung und der Instabilität ist bei der Entwicklung von EE-Formulierungen besondere Aufmerksamkeit auf die homogene Verteilung und die Stabilität des Wirkstoffes zu legen. Während der Herstellung von Tabletten ist die Granulierung ein wichtiger Schlüsselprozess zur Einstellung der Qualitätsmerkmale der Formulierung. Es ist dementsprechend entscheidend, den Granulierprozess zu verstehen und zu beherrschen.

In der Entwicklung der Modellformulierung einer EE-enhaltenden Filmtablette auf Basis von mikrokristalliner Zellulose (MCC) im Rahmen dieser Arbeit wurden die Stabilität von EE, die Partikelgröße der Granulate und die Granulatfeuchte als kritische Qualitätsmerkmale während des Prozessschrittes „Wirbelschichtgranulierung“ identifiziert. Dabei sollte aufgrund des möglichen oxidativen Abbaus von EE während des Prozesses dessen Stabilität als Hauptkriterium für die Qualität der Formulierung im Fokus liegen. Die Partikelgröße des Granulates sowie die Granulatfeuchte sind wichtige Parameter, die die Eigenschaften der aus dem Granulat hergestellten Tabletten sowie die Stabilität von EE beeinflussen^{10;17}.

Im Rahmen dieser Arbeit wurden EE-haltige Formulierungen auf die Anwendbarkeit dieser kritischen Prozessparameter zur Formulierungsentwicklung sowie als Freigabekriterien zukünftiger Herstellprozesse untersucht.

Das Ziel dieser Arbeit war die Entwicklung eines effektiven und schonenden Wirbelschichtgranulierprozesses für eine Modellformulierung mit EE als Wirkstoff. Für die Modellformulierung wurde Lactose durch MCC ersetzt und damit den Wünschen vieler

Anwender nach lactosefreien Tabletten entgegen gekommen. Um den Gesamtprozess in seiner Entwicklung und später in einer laufenden Produktion sicher und effektiv zu gestalten, wurden Anforderungen der PAT-Initiativen berücksichtigt. Zu diesem Zweck wurden neue in-line Messsysteme installiert, die kritischen Qualitätsmerkmale wie Partikelgrößenverteilung und Granulatfeuchte während des Granulierprozesses im Wirbelschichtgranulator kontrollieren sollten. Die korrekte Installation und Kalibrierung dieser in-line Sensoren war ein Kernpunkt in der Qualifizierung der Messsysteme und bildete die Basis für weitere Untersuchungen.

Die in-line Partikelgrößenuntersuchung wurde mittels Spatialfiltertechnologie (SFT) durchgeführt. In-line Kontrollen unter Verwendung eines SFT-Sensors waren bereits Gegenstand verschiedener Studien^{94;96;101}, jedoch wurden keine Einzelheiten zum Einfluss von Position und Einstellung des Sensors auf das Messergebnis angegeben. Im Rahmen dieser Arbeit wurde der Einfluss von Position und Einstellung des Sensors im Granulator auf die Messergebnisse am Beispiel von zwei im Wirbelschichtgranulator verwirbelten MCC-Qualitäten getestet. Anhand der Standard-MCC Vivapur 101 konnte gezeigt werden, dass die Messung in der Entspannungszone des Granulators zuverlässigere Messdaten liefert als die Messung im Produktbehälter. Außerdem wurden die Einflüsse der Tiefe der Sensoreinbringung und des Rotationswinkels auf das Messergebnis dargestellt um mögliche Einflüsse durch unbeabsichtigte Variation im Messaufbau abschätzen zu können. Anhand statistischer Analyse der gemessenen Partikelgrößendaten wurde eine optimale Sensoreinstellung (Tiefe der Sondeneinbringung und Rotationswinkel) für das untersuchte System Vivapur 101 ermittelt. Für die zweite MCC-Qualität mit größerer Partikelgröße (Avicel PH 102) wurde unter Standard-Prozessbedingungen nachgewiesen, dass Entmischungstendenzen auftreten: in der Entspannungszone wurden im Vergleich zum Produktbehälter kleinere Partikelgrößen gefunden. Damit konnte gezeigt werden, dass die Einbringung der Sonde in der Entspannungszone des Granulators nur dann sinnvoll ist, wenn während des Prozesses keine Produkt-Entmischung auftritt. Die für die Standard-MCC ermittelte optimale Sensor-Einstellung wurde anhand einer in-line Partikelgrößen-Messung während eines Standard-Granulierprozesses verifiziert. Dabei konnten alle Prozessschritte im Partikelgrößenprofil (x_{50} : ca. 60 μm bis 100 μm) dargestellt und die Vergleichbarkeit zum off-line Referenzverfahren (Laserdiffraktometrie) gezeigt werden. Im Bereich der Partikelgröße <50 μm traten Abweichungen zur Laserdiffraktometrie auf. Für die weitere Verarbeitung der Granulate ist die Partikelgröße am Ende des Granulierprozesses entscheidend. In diesem Bereich war die Übereinstimmung der in-line und off-line

gemessenen x_{90} und x_{50} Werte gegeben. Für kleinere Partikel (x_{10}) wurde keine Übereinstimmung gefunden. Abweichungen zum Beispiel durch Variation der Trocknungstemperatur oder Trocknungszeit während der für diese Arbeit durchgeführten Wirbelschichtgranulierprozesse konnten mit Hilfe des SFT-Sensors dargestellt werden. Eine Echtzeitfreigabe anhand der in-line Partikelgrößenmessung mit dem SFT-Sensor wäre durchaus möglich wenn weitere Untersuchungen zum Einfluss von Prozessparametern auf die Messergebnisse vorgenommen werden. Für andere Testsysteme (Formulierungen bzw. Wirbelschichtgranulatoren) müssen Untersuchungen zur Ermittlung der Messposition im Granulator und der Sondeneinstellung (Einbringungstiefe und Rotationswinkel) individuell durchgeführt werden. Anschließend hat eine Validierung im Vergleich zur off-line Referenzmessung zu erfolgen.

Zur in-line Messung der Granulatfeuchte wurde ein Mikrowellenresonanzsensor (MRT) im Produktbehälter des Wirbelschichtgranulators installiert. Die Kalibrierung erfolgte gegen die Standard-off-line Methode zur Bestimmung des Trocknungsverlustes. Dabei wurde ein Regressionskoeffizient von 0,903 über den Gesamtgranulierprozess ermittelt. Während des In-line Monitorings der für diese Arbeit durchgeführten Wirbelschichtgranulationsprozesse konnten Abweichungen der in-line Methode von der off-line Referenzmethode identifiziert werden. Diese Abweichungen resultierten aus Unterschieden im Granulationsprozess der Chargen zur Kalibrierung der in-line Messsonde im Vergleich zu den später kontrollierten Testchargen. Trotz dieser Auffälligkeiten war es möglich, die Verläufe der Granulatfeuchte bei unterschiedlichen Granulierprozessen nachzuverfolgen. Jedoch ist eine Endpunkt-Bestimmung der Granulatfeuchte mit Hilfe der MRT-Sonde als Ersatz für die off-line Messung nicht möglich. Sensoren zur Messung an Hand von zwei bzw. vier Messfrequenzen zur Erhöhung der Messgenauigkeit wurden bereits in der Literatur untersucht ^{146;147}.

Neben der Installation und Validierung der in-line Sensoren zum Monitoring der kritischen Qualitätsmerkmale Partikelgröße und Granulatfeuchte wurde die Stabilität des Wirkstoffes EE in Abhängigkeit der Prozessvariablen untersucht. Als Resultat sollte ein effektiver und schonender Herstellungsprozess im Hinblick auf den oxidativen EE-Abbau erzielt werden. Folgende Schwerpunkte wurden berücksichtigt:

- Einfluss der Granulatfeuchte und der thermischen Belastung während des Trocknungsprozesses durch Variation der Trocknungszeit

- Einfluss der thermischen Belastung während des Trocknungsprozesses durch Variation der Trocknungstemperatur
- Einfluss des Füllstoffes: Kontakt des Wirkstoffes mit dem Füllmittel (Lactose oder MCC) durch Untersuchung von binären Mischungen und unterschiedlicher Sprühsequenzen während der Granulation.

Alle Untersuchungen wurden unter Einbeziehung der in-line Messsonden zur Darstellung der Einflüsse auf die kritischen Qualitätsmerkmale Partikelgrößenverteilung im Granulat (SFT-Sensor) und Granulatfeuchte (MRT-Sensor) durchgeführt.

Zur Untersuchung der Stabilität von EE wurden dessen Hauptabbauprodukte (6-alpha-hydroxy-EE, 6-beta-hydroxy-EE, 9(11)-dehydro-EE, 6-oxo-EE²⁹⁻³¹) quantifiziert und verglichen.

Um den Einfluss der Trocknungszeit zu untersuchen, wurden drei Chargen der Modell-Formulierung auf MCC-Basis hergestellt und bewusst bis zu 30 Minuten getrocknet. Nach 0 min, 10 min und 30 min Trocknungszeit wurden Proben gezogen, eingelagert und der Gehalt der EE-Abbauprodukte bestimmt. Anhand der Ergebnisse konnten Rückschlüsse auf die Stabilität von EE in Abhängigkeit von der Temperatur und der Granulatfeuchte gezogen werden. Durch Untersuchung der Abbauprodukte zum Startpunkt der Stabilitätsprüfung sollten thermische Einflüsse aufgrund der langen Trocknungszeit nachweisbar sein. Einflüsse unterschiedlicher Granulatfeuchte resultierend aus unterschiedlichen Trocknungszeiten sollten nach geschlossener Lagerung in Glasvials sichtbar sein. Der Gehalt der Abbauprodukte in den Startproben wies jedoch keine signifikanten Unterschiede auf. Das bedeutet, dass eine lange Trocknungszeit keinen Einfluss auf die Stabilität nimmt. Nach der Lagerung über 12 Wochen bei 40 °C/75 % r.F. in geschlossenen Vials hatten die Proben mit einer hohen Ausgangsfeuchte von LOD = 8,35 % (0 min Trocknungszeit) insgesamt signifikant erhöhte Gehalte aller Abbauprodukte im Vergleich zu Proben mit einer geringen Ausgangsfeuchte von LOD = 3,43 % (30 min Trocknungszeit). Damit wurde bestätigt, dass die Granulatfeuchte den Abbau von EE beschleunigt.

Der Einfluss des thermischen Stresses aufgrund der Trocknungstemperatur auf die Stabilität von EE wurde durch Variation der Zulufttemperatur während des Trocknungsschrittes von 50 °C, 70 °C oder 90 °C untersucht. Die Temperatur von 70 °C ist die Standard-Prozesseinstellung. Je Temperatureinstellung wurden drei Chargen der Modellformulierung hergestellt. Alle Granulate wurden bis zu einem Feuchtegehalt von LOD = 6-7 % getrocknet,

der mittels MRT-in-line Messung bestimmt wurde. Die entstandenen Granulate wurden tablettiert und die Stabilität von EE untersucht. Signifikant erhöhte Gehalte von EE-Abbauprodukten konnten in Proben, die bei 90 °C getrocknet wurden, nach 8 Wochen Lagerung bei 40 °C/75 % r.F. ermittelt werden. Dies bestätigt die Hypothese, dass thermischer Stress während der Granulierung die Stabilität von EE beeinflusst.

In der untersuchten Modellformulierung wurde Lactose durch MCC als Hauptfüllstoff ersetzt. Um Aussagen zum Einfluss der Füllstoffe auf die Stabilität von EE machen zu können, wurden zunächst binäre Mischungen aus MCC (Vivapur 101) bzw. verschiedenen Lactose-Qualitäten mit EE im Granulator hergestellt. Dazu wurde EE in ethanolischer Lösung jeweils auf die sich im Wirbelbett befindlichen Füllstoffe gesprüht. Proben dieser binären Mischungen wurden sowohl offen als auch verschlossen in Glasvials gelagert und auf den Gehalt an EE-Abbauprodukten untersucht. In den offen gelagerten Proben der binären Mischung mit MCC wurden im Vergleich zu den Lactosemischungen signifikant erhöhte Gehalte an EE-Abbauprodukten ermittelt. Dies kann auf die in der Literatur beschriebenen Aufnahme und Speicherung von Wassermolekülen in der molekularen Struktur der MCC^{57;134} und den damit verbundenen beschleunigten Abbau von EE zurückgeführt werden. Die aus den geschlossen gelagerten Proben ermittelten Gehalte an EE-Abbauprodukten waren vergleichbar gering in den Proben aus MCC und den verschiedenen Lactose-Typen. Der Vergleich zwischen geschlossener und offener Lagerung hat gezeigt, dass der Kontakt von EE mit MCC in Anwesenheit von Wasser zur Zersetzung von EE führt.

Im nächsten Schritt wurde der Einfluss der Teilchengröße von MCC (Kontaktfläche) auf die Stabilität von EE untersucht. Zu diesem Zweck wurden binäre Mischungen von MCC-Typen verschiedener Partikelgröße (Vivapur 105, Vivapur 101, Vivapur 12) mit EE im Wirbelschichtgranulator hergestellt. Um den Einfluss der Luftfeuchte während der Lagerung zu minimieren, wurden Proben dieser binären Mischungen in geschlossenen Glasvials gelagert und auf EE-Abbauprodukte untersucht. Den geringsten Gehalt an EE-Abbauprodukten wiesen die Proben der binären Mischung mit MCC der größten Partikelgröße (Vivapur 12) auf. Den höchsten Anteil an Abbauprodukten zeigten die Proben der binären Mischung mit MCC der kleinsten Partikelgröße (Vivapur 105). Es konnte daraus geschlossen werden, dass die verringerte Partikelgröße und die damit verbundene vergrößerte spezifische Oberfläche in den Proben mit Vivapur 105 einen verstärkten Abbau von EE hervorgerufen haben. Das bedeutet, dass die größere Oberfläche einem vermehrten

Kontakt von EE mit den in der MCC eingeschlossenen Wassermolekülen und damit einem beschleunigten Abbau bedingt.

Da während der Sprühgranulierung EE intensiven Kontakt mit der Oberfläche der MCC bekommt, war es naheliegend, die Reihenfolge des Sprühens von wässriger Bindemittellösung und ethanolischer EE-Lösung zu variieren und somit die Kontaktzeiten des EE mit der MCC zu verändern. Zunächst wurde der Standardprozess durchgeführt, bei dem zuerst die ethanolische EE-Lösung auf die vorgewärmten Hilfsstoffe (MCC) und danach die wässrige Bindemittellösung gesprüht werden (Sequenz 1). In Sequenz 2 wurde die Bindemittellösung in zwei Teile gleicher Menge separiert. Der erste Teil wurde auf die vorgewärmten Hilfsstoffe gesprüht, im Anschluss daran wurden die ethanolische EE-Lösung und zuletzt der zweite Teil wässriger Bindemittellösung gesprüht (Sequenz 2). In Sequenz 3 wurde der Standardprozess umgekehrt und damit der Schutz für das EE besonders erhöht: im ersten Schritt wurde die wässrige Bindemittellösung auf die vorgewärmten Hilfsstoffe gesprüht, danach folgte das Aufsprühen der ethanolischen EE-Lösung. Alle hergestellten Chargen wurden in-line und off-line während des gesamten Granulierprozesses mittels SFT- und MRT-Sonde kontrolliert. Die Granulate wurden tablettiert und anschließend verblistert in PVC/Aluminium eingelagert, um die Stabilität von EE zu untersuchen. Für den Gehalt der EE-Abbauprodukte konnten im Vergleich der drei Sequenzen signifikante Unterschiede gezeigt werden. Der höchste Gehalt an EE-Abbauprodukten wurde in den Proben des Standardverfahrens (Sequenz 1) ermittelt. Sequenz 3 zeigte wie vermutet den geringsten Anteil an EE-Abbauprodukten. Die sowohl in-line als auch off-line ermittelten Daten zur Partikelgrößenverteilung ergaben, dass vor dem Sprühen der ethanolischen EE-Lösung die Partikelgröße in Sequenz 3 am größten und in Sequenz 1 am kleinsten war. Außerdem konnte sowohl in-line als auch off-line gezeigt werden, dass die Granulatfeuchte während des gesamten Granulierprozesses in Sequenz 3 am geringsten war. Es wird dementsprechend angenommen, dass sich drei Effekte überlagern: zum einen ist in Sequenz 3 die Oberfläche von MCC mit Bindemittel überzogen, bevor ein Kontakt mit EE entstehen kann. Zum zweiten war die gesamte Kontaktzeit von EE mit Wasser in Sequenz 3 insgesamt am geringsten. Zudem war die gesamte Zeit, in der EE im Wirbelschichtgranulierprozess enthalten war, in Sequenz 3 am kürzesten.

Die Gesamtauswertung aller Daten zur Stabilität von EE zeigte, dass die Entstehung von 6-oxo-EE vorwiegend thermisch bedingt ist. Die Bildung von 6-alpha-hydroxy-EE, 6-betyhydroxy-EE und 9(11)-dehydro-EE wurde vorwiegend durch die Granulatfeuchte verursacht.

Korrelationen konnten für 6-oxo-EE sowohl mit den thermischen Einflüssen als auch mit der Granulatfeuchte dargestellt werden.

Die Entwicklung eines effektiven und schonenden Granulierprozesses ist durch Änderung der Granuliersequenz möglich. Es konnte gezeigt werden, dass die in-line gemessene Partikelgrößenverteilung mittels SFT-Sensor ein geeignetes System darstellt, den Wirbelschichtgranulierprozess zu untersuchen und zu kontrollieren. Die In-line Kontrolle der Granulatfeuchte mit dem MRT-Sensor ist nur bedingt möglich. Hier kam es im Vergleich zur Off-line-Messung zu größeren Abweichungen der Feuchtwerte.

Reference List

---

1. Ebel S., Lehner M. S., Oettel M.; Ethinylestradiol; In: Blaschek W., Ebel S., Hackenthal E. et al.; Hagers Enzyklopädie der Arzneistoffe und Drogen; 6 ed; Stuttgart: Wissenschaftliche Verlagsgesellschaft mbH, 2012; p. 945-948
2. Yu L. X.; Pharmaceutical Quality by Design: Product and Process Development, Understanding and Control; Pharmaceutical Research;2008; 25(4): 781-791
3. FDA; Guidance for Industry PAT- A Framework for Innovative Pharmaceutical Development, Manufacturing and Quality Assurance; 2004
4. International Conference On Harmonisation Of Technical Requirements For Registration Of Pharmaceuticals For Human Use (ICH); Pharmaceutical Development Q8 (R2); 2009
5. International Conference On Harmonisation Of Technical Requirements For Registration Of Pharmaceuticals For Human Use (ICH); Quality Risk Management Q9; 2005
6. Lipsanen T.; Process Analytical Technology Approach on Fluid Bed Granulation and Drying- Identifying Critical Relationships and Construction the Design Space; 2008
7. FDA; Pharmaceutical cGMPS for the 21st Century - A Risk-Based Approach: Second Progress Report and Implementation Plan Introduction; U.S.Department of Health and Human Services 2009
8. International Conference On Harmonisation Of Technical Requirements For Registration Of Pharmaceuticals For Human Use (ICH); Pharmaceutical Quality Systems Q10; ICH; 2008
9. Straßberger F., Diller M.; Process Analytical Technology (PAT) im behördlichen Umfeld; 71 (9), 1540-1543; 2009, pharmind., Editio Cantor Verlag
10. Serno P., Kleinebudde P., Knop K.; Granulieren; Editio Cantor Verlag (2007)
11. Bauer K. H., Frömmering K.-H., Führer C.; Lehrbuch der pharmazeutischen Technologie; 7 ed. Stuttgart: Wissenschaftliche Verlagsgesellschaft mbH (2002)
12. Schæfer T., Wørts O.; Control of fluidized bed granulation V. Factors effecting granule growth; Arch. Pharm.Chemi. Sci. Ed.6, 1978; 69-82
13. Gao J. Z. H., Jain A., Motheram R. et al.; Fluid bed granulation of a poorly water soluble, low density, micronized drug: comparison with high shear granulation; International Journal of Pharmaceutics;2002; 237(1-2): 1-14
14. Davies W. L., Gloor W. T.; Batch Production of Pharmaceutical Granulations in a Fluidized Bed I: Effects of Process Variables on physical properties of final granulation; Journal of Pharmaceutical Sciences;1971; 60(12): 1869-1971
15. Zimmermann I.; Pharmazeutische Technologie- Industrielle Herstellung und Entwicklung von Arzneimitteln; 1 ed. Berlin Heidelberg: Springer Verlag (1998).

16. Murakami H., Yoneyama T., Nakajima K. et al.; Correlation between loose density and compactibility of granules prepared by various granulation methods; *International Journal of Pharmaceutics*;2001; 216(1-2): 159-164.
17. Faure A., York P., Rowe R. C.; Process control and scale-up of pharmaceutical wet granulation processes: a review; *European Journal of Pharmaceutics and Biopharmaceutics*;2001; 52(3): 269-277.
18. Schæfer T., Wørts O.; Control of fluidized bed granulation I. Effects of spray angle, nozzle height and starting materials on granule size and size distributions; *Arch. Pharm.Chemi. Sci. Ed.* 5;1977; 51-60
19. Schæfer T., Wørts O.; Control of fluidized bed granulation II. Estimation of droplet size of atomized binder solutions; *Arch. Pharm.Chemi. Sci. Ed.* 5;1977; 178-193
20. Schæfer T., Wørts O.; Control of fluidized bed granulation III. Effects of inlet air temperature and liquid flow rate on granule size and size distribution. Control of moisture content of granules in the drying phase; *Arch. Pharm.Chemi. Sci. Ed.* 6; 1978; 1-13
21. Schæfer T., Wørts O.; Control of fluidized bed granulation IV. Effects of binder solution and atomizing on granule size and size distribution; *Arch. Pharm.Chemi. Sci. Ed.* 6;1978; 14-25
22. Hemati M., Cherif R., Saleh K. et al.; Fluidized bed coating and granulation: influence of process-related variables and physicochemical properties on the growth kinetics; *Powder Technology*;2003; 130(1-3): 18-34
23. Abberger T.; Zur Kinetik der Wirbelschichtgranulation; *Pharmazie*;1999;(54): 611-613
24. Lourenco V., Lochmann D., Reich G. et al.; A quality by design study applied to an industrial pharmaceutical fluid bed granulation; *European Journal of Pharmaceutics and Biopharmaceutics*;2012; 81(2): 438-447
25. Herdling T., Lochmann D.; Implementierung von Process Analytical Technology (PAT) in der Solida-Produktion; *pharmind*;2010; 72(3): 402-408
26. Burggraef A., Monteyne T., Vervaet C. et al.; Process analytical tools for monitoring, understanding, and control of pharmaceutical fluidized bed granulation: A review; *European Journal of Pharmaceutics and Biopharmaceutics*;2013; 83(1): 2-15
27. Kern W., Willersinn H.; Die Katalyse der Autoxydation ungesättigter Verbindungen; *Angewandte Chemie*;1955; 67(19-20): 573-581
28. Pezzuto J.M., Park E.J.; Autoxidation and Antioxidants; In: J.Swift, *Encyclopedia of Pharmaceutical Technology*; 3 ed; Informa Healthcare USA (2006) p. 139-154
29. Li H., Song Y., Peng X.; Improved synthesis of mestranol and ethinyl estradiol (EE) related degradation products as authentic references; *Steroids*;2008; 73(5): 488-494

30. Segmuller B. E., Armstrong B. L., Dunphy R. et al.; Identification of autoxidation and photodegradation products of ethynylestradiol by on-line HPLC-NMR and HPLC-MS; *Journal of Pharmaceutical and Biomedical Analysis*;2000; 23(5): 927-937
31. Cotter M. L., Levine S. D., Mallory R. et al.; Thermal degradation of mestranol and ethinyl estradiol; *Tetrahedron Letters*;1978; 19(22): 1939-1942
32. International Conference On Harmonisation Of Technical Requirements For Registration Of Pharmaceuticals For Human Use (ICH); Impurities in new drug products Q3B(R2); 2006
33. Ekhatto I. V., Hurley T., Lovdahl M. et al.; Norethindrone acetate (NA) and ethinyl estradiol (EE) related oxidative transformation products in stability samples of formulated drug product: synthesis of authentic references; *Steroids*;2002; 67(3-4): 165-174
34. Fakhari A. R., Khorrami A. R., Shamsipur M.; Stability-indicating high-performance thin-layer chromatographic determination of levonorgestrel and ethinylestradiol in bulk drug and in low-dosage oral contraceptives; *Analytica Chimica Acta*;2006; 572(2): 237-242
35. EDQM; Ethinylestradiol; NT 2000, E 33; 2001, Ph. Eur. NT 2000
36. Sedee A., van Henegouwen G. B.; Photosensitized Decomposition of Contraceptive Steroids: A Possible Explanation for the Observed (Photo)allergy of the Oral Contraceptive Pill; *Arch Pharm Pharm Med Chem*;1985; 318(2): 111-119
37. Mazellier P., Méité L., De Laat J.; Photodegradation of the steroid hormones 17beta-estradiol (E2) and 17alpha-ethinylestradiol (EE2) in dilute aqueous solution; *Chemosphere*;2008; 73(8): 1216-1223
38. Waterman K. C., Adami R. C., Alsante K. M. et al.; Stabilization of Pharmaceuticals to Oxidative Degradation; *Pharmaceutical development and Technology*;2002; 7(1): 1-32
39. Mahajan R., Templeton A., Harman A. et al.; The Effect of Inert Atmospheric Packaging on Oxidative Degradation in Formulated Granules; *Pharmaceutical Research*;2005; 22(1): 128-140
40. Carstensen J.T.; Effect of Moisture on the Stability of Solid Dosage Forms; *Drug Development and Industrial Pharmacy*;1988; 14(14): 1927-1969
41. Ahlneck C., Zografi G.; The molecular basis of moisture effects on the physical and chemical stability of drugs in the solid state; *International Journal of Pharmaceutics*;1990; 62(2-3): 87-95
42. Waterman K. C., Adami R. C., Hong J.; Impurities in drug products; In: Ahuja S., Alsante K. M., *Handbook of isolation and characterization of impurities in pharmaceuticals*; Boston:2005) p. 75-88
43. Seugling EW; The Contribution of tableting aids to pharmaceutical development (Part I); *Pharm Technol*;1980; 4(7): 27-62

44. EDQM; European Pharmacopoeia 5.0; 01/2005:0316 Cellulose, Microcrystalline; 2013
45. Doelker E.; Comparative compaction properties of various Microcrystalline Cellulose types and Generic Products; Drug Development and Industrial Pharmacy;1993; 19(17-18): 2399-2471
46. David S. T., Augsburger L. L.; Plastic flow during compression of directly compressible fillers and its effect on tablet strength; Journal of pharmaceutical sciences;1977; 66(2): 155-159
47. Landin M., Martinez-Pacheco R., Gomez-Amoza J. L. et al.; Effect of batch variation and source of pulp on the properties of microcrystalline cellulose; International Journal of Pharmaceutics;1993; 91(2-3): 133-141
48. Landin M., Martinez-Pacheco R., Gomez-Amoza J. L. et al.; Effect of country of origin on the properties of microcrystalline cellulose; International Journal of Pharmaceutics;1993; 91(2-3): 123-131
49. Ardizzone S., Dioguardi F. S., Mussini P. R. et al.; Batch effects, water content and aqueous/organic solvent reactivity of microcrystalline cellulose samples; International Journal of Biological Macromolecules;1999; 26(4): 269-277
50. Haware R. V., Bauer-Brandl A., Tho I.; Comparative evaluation of the powder and compression properties of various grades and brands of microcrystalline cellulose by multivariate methods; Pharmaceutical Development and Technology;2010; 15(4): 394-404
51. Zografi G., Kontny M. J.; The interactions of water with cellulose- and starch-derived pharmaceutical excipients; Pharmaceutical Research;1986; 3(4): 187-194
52. Zografi G., Kontny M. J., Yang A. Y. S. et al.; Surface area and water vapor sorption of macrocrystalline cellulose; International Journal of Pharmaceutics;1984; 18(1-2): 99-116
53. Faroongsarng D., Peck G. E.; The Swelling & Water Uptake of Tablets III: Moisture Sorption Behavior of Tablet Disintegrants; Drug development and industrial Pharmacy;1994; 20(5): 779-798.
54. Dawoodbhai S., Rhodes C. T.; The effect of moisture on powder flow and on compaction and physical stability of tablets; Drug development and industrial Pharmacy;2008; 15(10): 1577-1600
55. Amidon G. E., Houghton M. E.; The Effect of Moisture on the Mechanical and Powder Flow Properties of Microcrystalline Cellulose; Pharmaceutical Research;1995; 12(6): 923-929
56. Ek R., Lennholm H., Davidson R. et al.; Pore swelling in beads made of cellulose fibres and fibre fragments; International Journal of Pharmaceutics;1995; 122(1-2): 49-56

57. Khan F., Pilpel N., Ingham S.; The effect of moisture on the density, compaction and tensile strength of microcrystalline cellulose; Powder Technology;1988; 54(3): 161-164
58. Ritschel W. A.; Die Tablette;2013.
59. Newell H. E., Buckton G., Butler D. A. et al.; The use of inverse phase gas chromatography to study the change of surface energy of amorphous lactose as a function of relative humidity and the processes of collapse and crystallisation; International Journal of Pharmaceutics;2001; 217(1-2): 45-56
60. Thielmann F., Burnett D. J., Heng J. Y. Y.; Determination of the surface energy distributions of different processed lactose; Drug Development and Industrial Pharmacy;2013; 33(11): 1240-1253
61. Newell H. E., Buckton G., Butler D. A. et al.; The use of inverse phase gas chromatography to measure the surface energy of crystalline, amorphous and recently milled lactose; Pharmaceutical Research;2001; 18(5): 662-666
62. DFE pharma; Product Specification Pharmatose(R) 200M (EU); 2016, <http://www.dfepharm.com/en/excipients/lactose/milled-lactose/pharmatose-200m/qar-documents.aspx>
63. DFE pharma; Product Specification Pharmatose(R) 130M; 2016, <http://www.dfepharm.com/en/excipients/lactose/milled-lactose/pharmatose-130m/qar-documents.aspx>
64. DFE pharma; Product Specification Pharmatose(R) 450M; 2016, <http://www.dfepharm.com/en/excipients/lactose/milled-lactose/pharmatose-450m/qar-documents.aspx>
65. Abberger T.; The effect of powder type, free moisture and deformation behaviour of granules on the kinetics of fluid-bed granulation; European Journal of Pharmaceutics and Biopharmaceutics;2001; 52(3): 327-336
66. Kristl A., Mrahr A., Kozjek F.; Physico-chemical evaluation and statistical assessment of wet granulation; pharmind;1993; 55(3): 271-275
67. Kleinebudde P.; Theme Issue "Granulation"; European Journal of Pharmaceutics and Biopharmaceutics;2001; 52(3): 267
68. EDQM; European Pharmacopoeia 5, 2.9.12 Sieve Test; 2013
69. EDQM; European Pharmacopoeia 6.2, 2.09.35: Powder fineness; 2007
70. Ritschel W. A., Bauer-Brandl A.; Herstellung verpressbarer Tablettiermassen; Die Tablette- Handbuch der Entwicklung, Herstellung und Qualitätssicherung; Aulendorf: Editio Cantor Verlag (2002) p. 248-374
71. EDQM; European Pharmacopoeia 6.2, 2.9.38: Particle size Distribution Estimation by analytical sieving; 2013, Supplement 6.2 to Ph. Eur.

72. International Conference On Harmonisation Of Technical Requirements For Registration Of Pharmaceuticals For Human Use (ICH); Evaluation and Recommendation of Pharmacopoeial Texts for Use in the ICH Regions Q4B Annex 12: Analytical sieving General Chapter; 2010
73. Li M., Wilkinson D., Patchigolla K.; Obtaining Particle Size Distribution from Chord Length Measurements; Particle and Particle Systems Characterization;2006; 23(2): 170-174
74. Worlitschek J., Hocker T., Mazzotti M.; Restoration of PSD from Chord Length Distribution Data using the Method of Projections onto Convex Sets; Particle and Particle Systems Characterization;2005; 22(2): 81-98
75. Worlitschek J., Mazzotti M.; Choice of the Focal Point Position Using Lasentec FBRM; Particle and Particle Systems Characterization;2003; 20(1): 12-17
76. Hansuld E. M., Briens L., Sayani A. et al.; An investigation of the relationship between acoustic emissions and particle size; Powder Technology;2012; 219(0): 111-117
77. Tsujimoto H., Yokoyama T., Huang C. C. et al.; Monitoring particle fluidization in a fluidized bed granulator with an acoustic emission sensor; Powder Technology;2000; 113(1-2): 88-96
78. Halstensen M., de Bakker P., Esbensen K. H.; Acoustic chemometric monitoring of an industrial granulation production process--a PAT feasibility study; Chemometrics and Intelligent Laboratory Systems;2006; 84(1-2): 88-97
79. Poutiainen S., Matero S., Hämäläinen T. et al.; Predicting granule size distribution of a fluidized bed spray granulation process by regime based PLS modeling of acoustic emission data; Powder Technology;2012; 228(0): 149-157
80. Watano S., Miyanami K.; Image processing for on-line monitoring of granule size distribution and shape in fluidized bed granulation; Powder Technology;1995; 83(1): 55-60
81. T.Närvänen, K.Seppälä, O.Antikainen et al.; A New Rapid on-Line Imaging Method to Determine Particle Size Distribution of Granules; AAPS Pharm SciTech;2008; 9(1): 282-287.
82. Goebel S. G., Steffens K.-J.; Online-Messung der Produktfeuchte und Korngröße in der Wirbelschicht mit der Nah-Infrarot-Spektroskopie; pharmind;1998; 60: 889-895.
83. Nieuwmeyer F., Damen M., Gerich A. et al.; Granule Characterization During Fluid Bed Drying by Development of a Near Infrared Method to Determine Water Content and Median Granule Size; Pharmaceutical Research;2007; 24(10): 1854-1861
84. Rantanen J., Räsänen E., Tenhunen J. et al.; In-line moisture measurement during granulation with a four-wavelength near infrared sensor: an evaluation of particle size and binder effects; European Journal of Pharmaceutics and Biopharmaceutics;2000; 50(2): 271-276

85. Alcala, Blanco, Bautista et al.; Monitoring of wet granulation process by NIR spectroscopy: determination of moisture, particle size and density; 2008, Barcelona 2008
86. Rantanen J., Yliruusi J.; Determination of Particle Size in a Fluidized Bed Granulator With a Near Infrared Set-up; Pharmacy and Pharmacology Communications;1998; 4(2): 73-75
87. Tok A., Goh X., Ng W. et al.; Monitoring Granulation Rate Processes Using Three PAT Tools in a Pilot-Scale Fluidized Bed; AAPS Pharm SciTech;2008; 9(4): 1083-1091
88. Petrak D.; Simultaneous measurement of particle size and particle velocity by the spatial filtering technique; Particle and Particle Systems Characterization;2002; 19: 391-400
89. Petrak D., Rauh H.; Optical Probe for the In-Line Determination of Particle Shape, Size and Velocity; Particulate Science and Technology;2006; 24: 381-394
90. Petrak D., Dietrich S., Eckhardt G. et al.; In-line particle sizing for real-time process control by fibre-optical spatial filtering technique (SFT); Advanced Powder Technology;2011; 22(2): 203-208
91. Parsum Gesellschaft für Partikel-, Strömungs- und Umweltmeßtechnik mbH; Bedienungsanleitung in-line Particle Probe IPP 70; 2007
92. Silva A. F. T., Burggraeve A., Denon Q. et al.; Particle sizing measurements in pharmaceutical applications: Comparison of in-process methods versus off-line methods; European Journal of Pharmaceutics and Biopharmaceutics;2013;(0)
93. Närvänen T., Lipsanen T., Antikainen O. et al.; Gaining fluid bed process understanding by in-line particle size analysis; Journal of Pharmaceutical Sciences;2009; 98(9): 1110-1117
94. Huang J., Goolcharran C., Utz J. et al.; A PAT Approach to enhance process understanding of fluid bed granulation using in-line particle size characterization and multivariate analysis; Journal of Pharmaceutical Innovation;2010; 5(1): 58-68
95. Burggraeve A., Silva A. F. T., Van Den Kerkhof T. et al.; Development of a fluid bed granulation process control strategy based on real-time process and product measurements; Talanta;2012; 100: 293-302.
96. Burggraeve A., Van Den Kerkhof T., Hellings M. et al.; Evaluation of in-line spatial filter velocimetry as PAT monitoring tool for particle growth during fluid bed granulation; European Journal of Pharmaceutics and Biopharmaceutics;2010; 76(1): 138-146
97. Lipsanen T., Närvänen T., Raikkönen et al.; Particle size, moisture, and fluidization variations described by indirect in-line physical measurements of fluid bed granulation.; AAPS Pharm SciTech;2008; 9(4): 1070-1077

98. Närvänen T., Antikainen O., Yliruusi J.; Predicting Particle Size During Fluid Bed Granulation Using Process Measurement Data; AAPS Pharm SciTech;2009; 10(4): 1268-1275
99. Schmidt-Lehr S., Moritz H.-U., Jürgens K. C.; Online-Kontrolle der Partikelgröße während einer Wirbelschichtgranulation; pharmind;2007; 69: 478-484
100. Stöckel P., Dietrich S., Petrak D.; Inline-Partikelmessung in der Wirbelschicht; pharmind;2013; 75(11): 1824-1832
101. Burggraave A., van den Kerkhof T., Hellings M. et al.; Batch statistical process control of a fluid bed granulation process using in-line spatial filter velocimetry and product temperature measurements; European Journal of Pharmaceutical Sciences;2011; 42(5): 584-592
102. Influence of the installed in-Line Spatial Filter Velocimetry (SFV) Probe on the fluidized bed stability; 5th intern. Granulation Workshop; 2014
103. Malamataris S., Goidas P., Dimitriou A.; Moisture sorption and tensile strength of some tableted direct compression excipients; International Journal of Pharmaceutics;1991; 68(1-3): 51-60
104. Alden M., Torkington P., Strutt A. C. R.; Control and instrumentation of a fluidized-bed drier using the temperature-difference technique I. Development of a working model; Powder Technology;1988; 54(1): 15-25
105. Lipsanen T., Antikainen O., Raikkönen H. et al.; Effect of fluidisation activity on end-point detection of a fluid bed drying process; International Journal of Pharmaceutics;2008; 357(1-2): 37-43
106. Reich G.; Near-infrared spectroscopy and imaging: Basic principles and pharmaceutical applications; Advanced Drug Delivery Reviews;2005; 57(8): 1109-1143
107. Frake P., Greenhalgh D., Grierson S. M. et al.; Process control and end-point determination of a fluid bed granulation by application of near infra-red spectroscopy; International Journal of Pharmaceutics;1997; 151(1): 75-80
108. Wantano S., Takashima, H. et al.; Measurements of Moisture Content by IR Sensor in Fluidized Bed Granulation. Effects of Operating Variables on the Relationship between Granule Moisture Content and Absorbance of IR Spectra; Chemical and Pharmaceutical Bulletin;1996; 44(6): 1267-1269
109. Findlay P. W., Peck G. R., Morris K. R.; Determination of fluidized bed granulation end point using near-infrared spectroscopy and phenomenological analysis; Journal of Pharmaceutical Sciences;2005; 94(3): 604-612
110. List K., Steffens K.-J.; Überwachung und Steuerung von Granulationsprozessen mit Hilfe der Nah-Infrarot-Spektroskopie; pharmind;1996; 58(4): 347-353

111. Buschmüller C., Wiedey W., Döscher C. et al.; In-line monitoring of granule moisture and temperature throughout the entire fluidized-bed granulation process using microwave resonance technology (Part I); *pharmind*;2009; 71(8): 1403-1408
112. Buschmüller C., Wiedey W., Döscher C. et al.; In-line Monitoring of Granule Moisture and Temperature throughout the entire Fluidized-bed Granulation Process using Microwave Resonance Technology (Part II); *pharmind*;2009; 71(9): 1614-1620
113. Schlemm U., Richter H., Mellmann J.; Feuchtemessung in Weizen mit der Mikrowellen-Resonanzmethode; *Mühle und Mischfutter*;2008; 145(23): 786-789
114. Leuenberger H.; *Martin Physikalische Pharmazie*; 4 ed. Stuttgart: Wissenschaftliche Verlagsgesellschaft mbH (2002)
115. Buschmüller C.; In-line monitoring of granule moisture in fluidized bed granulators using microwave resonance technology a novel PAT tool; *Pharmazeutische Technologie und Biopharmazie der Heinrich-Heine Universität Düsseldorf*; 2009.
116. Knöchel R., Taute W., Döscher C.; Stray field ring resonators and a novel trough guide resonator for precise microwave moisture and density measurements; *Measurement Science and Technology*;2007; 18(4): 1061-1068
117. Meyer W., Schilz W.; A microwave method for density independent determination of the moisture content of solids; *Journal of Physics D: Applied Physics*;1980; 13(10): 1823
118. Buschmüller C., Wiedey W., Döscher C. et al.; In-line monitoring of granule moisture in fluidized-bed dryers using microwave resonance technology; *European Journal of Pharmaceuics and Biopharmaceutics*;2008; 69(1): 380-387
119. Corredor C. C., Bu D., Both D.; Comparison of near infrared and microwave resonance sensors for at-line moisture determination in powders and tablets; *Analytica Chimica Acta*;2011; 696(1-2): 84-93
120. Melichar M.; *Untersuchungen zur Feuchtemessung an pharmazeutischen Hilfsstoffen mit Hilfe der Mikrowellen-Resonanzspektroskopie*; *Pharmazeutische Technologie der Rheinischen Friedrich-Wilhelms-Universität Bonn*, 2007
121. Lourenco V., Herdling T., Reich G. et al.; Combining microwave resonance technology to multivariate data analysis as a novel PAT tool to improve process understanding in fluid bed granulation; *Eur J Pharm Biopharm*;2011; 78(3): 513-521
122. Roßteuscher-Carl K., Fricke S., Hacker M. C. et al.; In-line monitoring of particle size in a fluid bed granulator: Investigations concerning positioning and configuration of the sensor; *International Journal of Pharmaceutics*;2014; 466(0): 31-37
123. Roßteuscher-Carl K., Fricke S., Hacker M. C. et al.; Influence of in line monitored fluid bed granulation process parameters on the stability of Ethinylestradiol; *International Journal of Pharmaceutics*;2015; 496(2): 751-758
124. Jenapharm GmbH & Co.KG; *Entwicklungs-Prüfvorschrift 1013S_PVE_D, Prüfung auf Verwandte Substanzen*; 16-23; 2013

125. Knöchel R., Taute W., Döscher C.; inventors; Mikrowellenanordnung zur Produktfeuchtemessung, mit Temperaturkompensation; patent EP 1 331 476 B1.(26 Apr 2006)
126. Närvänen T., Lipsanen T., Antikainen O. et al.; Controlling granule size by granulation liquid feed pulsing; *International Journal of Pharmaceutics*;2008; 357(1-2): 132-138
127. Burggraef A., Van Den Kerkhof T., Hellings M. et al.; Understanding fluidized-bed granulation; *PharmTech*;2011; 35(8): 63-67
128. Di Maio F. P., Di Renzo A., Vivacqua V.; A particle segregation model for gas-fluidization of binary mixtures; *Powder Technology*;2012; 226(0): 180-188.
129. Hoffmann A. C., Romp E. J.; Segregation in a fluidised powder of a continuous size distribution; *Powder Technology*;1991; 66(2): 119-126
130. Rawle A.; *Basic Principles of Particle Size Analysis*; 2008, Malvern Instruments
131. Allinson J. G., Dansereau R. J., Sakr A.; The effects of packaging on the stability of a moisture sensitive compound; *International Journal of Pharmaceutics*;2001; 221(1-2): 49-56
132. Lange J., Wyser Y.; Recent innovations in barrier technologies for plastic packaging - a review; *Packaging Technology and Science*;2003; 16(4): 149-158
133. Nieuwmeyer F., van der Voort Maarschalk K., Vromans H.; Lactose Contaminant as Steroid Degradation Enhancer; *Pharmaceutical Research*;2008; 25(11): 2666-2673
134. Fielden K. E., Newton J. M., O'Brien P. et al.; Thermal Studies on the Interaction of Water and Microcrystalline Cellulose; *Journal of Pharmacy and Pharmacology*;1988; 40(10): 674-678
135. Dreu R., Sirca J., Pintye-Hodi K. et al.; Physicochemical properties of granulating liquids and their influence on microcrystalline cellulose pellets obtained by extrusion-spheronisation technology; *International Journal of Pharmaceutics*;2005; 291(1-2): 99-111
136. Millili G. P., Schwartz J. B.; The Strength of Microcrystalline Cellulose Pellets: The Effect of Granulating with Water/Ethanol Mixtures; *Drug Development and Industrial Pharmacy*;1990; 16(8): 1411-1426
137. Millili G. P., Wigent R. J., Schwartz J. B.; Differences in the mechanical strength of dried microcrystalline cellulose pellets are not due to significant changes in the degree of hydrogen bonding; *Pharmaceutical Development and Technology*;1996; 1(3): 239-249
138. Watanabe A., Morita S., Ozaki Y.; A study on water adsorption onto microcrystalline cellulose by NIR with two- Dimensional Correlation Spectroscopy and Principal Component Analysis; *Applied spectroscopy*;2006; 60(9): 1054-1061
139. da Silva C. A. M., Taranto O. P.; Real-Time Monitoring of Gas-Solid Fluidized-Bed Granulation and Coating Process: Evolution of Particle Size, Fluidization Regime

- Transitions, and Psychometric Parameters; Drying Technology;2015; 33(15-16): 1929-1948
140. Wormsbecker M., Adams A., Pugsley T. et al.; Segregation by size difference in a conical fluidized bed of pharmaceutical granulate; Powder Technology;2005; 153(1): 72-80
  141. Huilin L., Yurong H., Gidaspow D. et al.; Size segregation of binary mixture of solids in bubbling fluidized beds; Powder Technology;2003; 134(1-2): 86-97
  142. Schaafsma S. H., Marx T., Hoffmann A. C.; Investigation of the particle flowpattern and segregation in tapered fluidized bed granulators; Chemical Engineering Science;2006; 61(14): 4467-4475
  143. Wu S. Y., Baeyens J.; Segregation by size difference in gas fluidized beds; Powder Technology;1998; 98(2): 139-150
  144. Peters J., Bartscher K., Döscher C. et al.; In-line moisture monitoring in fluidized bed granulation using a novel multi-resonance microwave sensor; Talanta;2017; 170(Supplement C): 369-376
  145. Waterman K. C., Adami R. C.; Accelerated aging: Prediction of chemical stability of pharmaceuticals; International Journal of Pharmaceutics;2005; 293(1): 101-125
  146. Peters J., Bartscher K., Döscher C. et al.; Use of a novel multi-frequency microwave sensor for inline moisture monitoring in fluidized ged granulation; 2015, AAPS Annual Meeting Orlando 25th to 29th October, 2015
  147. Kollar B., Wiedey W., Bartscher K. et al.; Mikrowellenresonanz-Sensoren; TechnoPharm;2013; 3(6): 317-321

Appendix

List of Abbreviations

Curriculum Vitae

List of Publications

Declaration of Authorship

Acknowledgements

List of Abbreviations

API	Active pharmaceutical ingredient
CQA	Critical quality attribute
cGMP	Current Good Manufacturing Practice
EE	Ethinylestradiol
EMA	European medicines agency
FBRM	Focussed beam reflectance measurement
FDA	Food and Drug Administration
DH	dehydro
DS	Drug substance
ICH	International Conference on Harmonisation
JPH	Jenapharm GmbH & Co.KG
LOD	Loss on drying
LOD/IR	Loss on drying measured by infra-red balance
MRT	Microwave resonance technology
MCC	Microcrystalline Cellulose
MWR	Microwave resonance (technology)
NIR	Near infrared
NIRS	Near infrared spectroscopy
PAT	Process analytic technology
Ph. Eur.	European Pharmacopoeia
PSD	Particle size distribution

PTFE	Polytetrafluorethylene
SEM	Scanning electron microscopy
SFT	Spatial filtering technology

Curriculum Vitae

Name: Katrin Roßteuscher-Carl (née Roßteuscher)
Date of birth: June 22, 1981
Place of birth: Suhl
Nationality: German
Marital status: Married

Professional training and carrier:

01/2012 – today   **Pharmaceutical Scientist**, Aeropharm GmbH, Rudolstadt
06/2009 - today   **PhD candidate**, Institute of Pharmacy, Pharmaceutical
Technology, Universität Leipzig
06/2006 – 12/2011   **Scientific assistant**, Jenapharm GmbH & Co. KG, Jena
05/2006   **Licensure as Pharmacist**
06/2005 – 05/2006   Pharmaceutical Traineeship, public pharmacy
Apotheke am Nollendorfer Hof, Jena
11/2004 – 05/2005   Pharmaceutical Traineeship, pharmaceutical industry,
Boehringer Ingelheim Pharma GmbH & Co. KG, Ingelheim
Diploma thesis (grade 2.0), Institute of Pharmacy,
Pharmaceutical Technology, Friedrich-Schiller- Universität
Jena
*Title: „Entwicklung und Optimierung von analytischen und
technologischen Verfahren zur Prüfung von Dosierventilen“*
10/2000 – 10/2004   Pharmaceutical studies, Friedrich-Schiller-University Jena

Education:

09/1992 – 06/2000   **High School**, Hennebergisches Gymnasium “Georg Ernst”
Schleusingen
General Qualification for university entrance (final grade: 1.6)
09/1988 – 08/1992   Elementary School, Staatliche Grundschule “Gerhart
Hauptmann”, Schleusingen

List of Publications

Publications (peer-reviewed papers)

In-line monitoring of particle size in a fluid bed granulator: Investigations concerning positioning and configuration of the sensor

Roßteuscher-Carl, K.; Fricke, S.; Hacker, M. C.; Schulz-Siegmund, M.; International Journal of Pharmaceutics **2014**, 466, 31-37

Influence of in line monitored fluid bed granulation process parameters on the stability of Ethinylestradiol

Roßteuscher-Carl, K.; Fricke, S.; Hacker, M. C.; Schulz-Siegmund, M.; International Journal of Pharmaceutics **2015**, 496, 751-758

Conference Abstracts (poster presentations)

Optimization of API-stability during fluid bed granulation process by PAT

Roßteuscher, K.; Ladwig, R.; Hacker, M. C.; Fricke, S.; Schulz-Siegmund, M.;
8th World Meeting on Pharmaceutics, Biopharmaceutics and Pharmaceutical Technology,
Istanbul, Turkey 2012

Investigation for API-stability as a function of the drying phase in the fluid bed granulation process

Roßteuscher, K.; Ladwig, R.; Hacker, M. C.; Fricke, S.; Schulz-Siegmund, M.;
10th Leipzig Research Festival for Life Sciences, Leipzig, Germany 2011

In-line monitoring of particle size in a fluid bed granulator: positioning and configuration of a sensor

Roßteuscher, K.; Ladwig, R.; Hacker, M. C.; Fricke, S.; Schulz-Siegmund, M.;
QbD/PAT Conference, Heidelberg, Germany, 2011

Scientific Presentation (lectures)

Installation Parsum-Sonde zur In-line- Partikelgrößenbestimmung im Wirbelschichtgranulator GPCG 3.1

Roßteuscher, K.
Mitteldeutsches Technologentreffen, Leipzig, Germany, 2009

Declaration of Authorship

Hiermit erkläre ich, dass ich die vorliegende Dissertation mit dem Thema „Development of a PAT monitored fluid bed granulation process using the example of a low dose steroid hormone“ eigenständig verfasst und alle verwendeten Quellen im Literaturverzeichnis angegeben habe. Ich bestätige, dass ich die Kapitel 1, 2, 5, 6, 7 und 8 in alleiniger Urheberschaft verfasst habe.

Zitate aus der Literatur sind als solche gekennzeichnet. Abbildungen und Tabellen sind von mir selbst erstellt worden oder mit einem entsprechenden Literaturverweis versehen.

Ich versichere, dass

- die vorliegende Arbeit ohne unzulässige Hilfe und ohne Benutzung anderer als der angegebenen Hilfsmittel angefertigt wurde und dass die aus fremden Quellen direkt oder indirekt übernommenen Gedanken in der Arbeit als solche kenntlich gemacht worden sind;
- keine weiteren Personen als die genannten Coautoren und die in der Danksagung erwähnten Personen in dem jeweils genannten Umfang an der Auswahl und Auswertung des Materials sowie bei der Herstellung des Manuskripts beteiligt waren;
- keine Hilfe eines Promotionsberaters in Anspruch genommen wurde und dass Dritte weder unmittelbar noch mittelbar geldwerte Leistungen für Arbeiten erhalten haben, die im Zusammenhang mit dem Inhalt der vorgelegten Dissertation stehen;
- die vorgelegte Arbeit in gleicher oder in ähnlicher Form keiner anderen wissenschaftlichen Einrichtung zum Zwecke einer Promotion oder eines anderen Prüfungsverfahrens vorgelegt und auch veröffentlicht wurde;
- bisher keine erfolglosen Promotionsversuche stattgefunden haben;
- die Art und der Umfang der Coautoren an der wissenschaftlichen Leistung der vorgelegten Publikationen vollständig angegeben sind.

Jena, den 17.07.2018

Katrin Roßteuscher-Carl

Nachweis über Anteile der Co-Autoren, Katrin Roßteuscher-Carl

Development of a PAT monitored fluid bed granulation process using the example of a low dose steroid hormone

---

Nachweis über Anteile der Co-Autoren:

Titel: In-line monitoring of particle size in a fluid bed granulator: investigations concerning positioning and configuration of the sensor

Journal: International Journal of Pharmaceutics

Autoren: Katrin Roßteuscher-Carl, Sabine Fricke, Michael C. Hacker, Michaela Schulz-Siegmund

---

Anteil Katrin Roßteuscher-Carl:

- Konzeption
- Installation der SFT-Sonde am Wirbelschichtgranulator
- Durchführung der Wirbelversuche mit Microcristalliner Cellulose und Lactose
- Herstellung Testcharge im Wirbelschichtgranulator
- Erstellung der off-line Partikelgrößenprofile mittels Laserdiffraktometrie
- Analyse und Verarbeitung der Daten
- Kritische Diskussion der Ergebnisse
- Verfassen der Publikation

Anteil Sabine Fricke:

- Projektidee
- Organisation der experimentellen und analytischen Infrastruktur
- Beratung bei der Durchführung der Versuche
- Kritische Diskussion der Ergebnisse

Anteil Michael C. Hacker:

- Analyse und statistische Verarbeitung der Daten
- Kritische Diskussion der Ergebnisse
- Verfassen der Publikation

Anteil Michaela Schulz-Siegmund:

- Kritische Diskussion der Ergebnisse
- Verfassen der Publikation

09.07.2018
Katrin Roßteuscher-Carl

Michaela Schulz-Siegmund

Nachweis über Anteile der Co-Autoren, Katrin Roßteuscher-Carl

Development of a PAT monitored fluid bed granulation process using the example of a low dose steroid hormone

---

Nachweis über Anteile der Co-Autoren:

Titel: Influence of in line monitored fluid bed granulation process parameters on the stability of Ethinylestradiol

Journal: International Journal of Pharmaceutics

Autoren: Katrin Roßteuscher-Carl, Sabine Fricke, Michael C. Hacker, Michaela Schulz-Siegmund

---

Anteil Katrin Roßteuscher-Carl:

- Konzeption
- Installation der SFT-Sonde und MRT-Sonde am Wirbelschichtgranulator
- Herstellung der Testchargen im Wirbelschichtgranulator
- Messung von off-line Partikelgrößen und Granulatfeuchte
- Einlagerung der Granulatproben und Tabletten für Stabilitätsuntersuchungen
- Bestimmung der Abbauprodukte von EE mittels HPLC
- Analyse und Verarbeitung der Daten
- Kritische Diskussion der Ergebnisse
- Verfassen der Publikation

Anteil Sabine Fricke:

- Projektidee
- Organisation der experimentellen und analytischen Infrastruktur
- Beratung bei der Durchführung der Versuche
- Kritische Diskussion der Ergebnisse

Anteil Michael C. Hacker:

- Analyse und statistische Verarbeitung der Daten
- Kritische Diskussion der Ergebnisse
- Verfassen der Publikation

Anteil Michaela Schulz-Siegmund:

- Kritische Diskussion der Ergebnisse
- Verfassen der Publikation

09.07.2018
Katrin Roßteuscher-Carl

Michaela Schulz-Siegmund

Acknowledgements

Frau Prof. Dr. Schulz-Siegmund danke ich für Annahme und Betreuung meiner Arbeit sowie die herzliche Aufnahme in die Arbeitsgruppe wann immer ich vor Ort in Leipzig war, um am Lehrstuhlseminar teilzunehmen, Ergebnisse zu besprechen oder Versuche im Labor durchzuführen. Bedanken möchte ich mich auch für die vielen kritischen Diskussionen, die die Sicht auf die Untersuchungen und Ergebnisse geschärft haben.

Frau Dr. Fricke danke ich herzlich für die Konzeption des Themas meiner Arbeit, für die Ermöglichung der Arbeit überhaupt und für die vielen Gespräche und Ideen. Ohne Ihre Unterstützung und pragmatischen Vorschläge hätte ich oft den roten Faden verloren.

Herrn PD Dr. Michael Hacker danke ich für die Unterstützung bei der statistischen Auswertung der Daten und der kritischen Diskussion der Ergebnisse und beim Verfassen der Publikationen.

Der Jenapharm GmbH & Co. KG möchte ich für die finanzielle Unterstützung der Arbeit danken.

Großer Dank gilt meinen ehemaligen Kollegen der ehemaligen Abteilung EPG der Jenapharm GmbH & Co. KG:

Ralf Ladwig danke ich für die vielen konstruktiven Diskussionen zur Planung und Auswertung der Versuche und für die Einweisung in statistische Versuchsplanung

Ich danke Anke Herling und Frau Babock für die vielen Stunden der Unterstützung am Wirbelschichtgranulator und an der Tablettenpresse, für die Vor und Nachbereitung der Versuche und vieler Arbeiten im Labor wie Untersuchung der Partikelgröße am Laserdiffraktometer und Bestimmung der Granulatfeuchte

Kathrin Hennig danke ich für die persönliche Einweisung in die Durchführung von Untersuchungen an der HPLC

Petra Zielke und Kathrin Hennig danke ich für das Verblistern der Tablettenkerne

Weiterhin möchte ich Janina Telle danken, die mich im Rahmen ihrer Bachelorarbeit zum Thema „Einfluss der Parameter Sprühregime und Zulufttemperatur während der Trocknung auf die Eigenschaften von Wirbelschichtgranulaten und Tabletten“ (Hochschule Anhalt (FH),

Fachbereich 7- Angewandte Biowissenschaften und Prozesstechnik) in der Durchführung der Versuche unterstützt hat. Es hat sehr viel Spaß gemacht, ihre Arbeit zu begleiten.

Der Firma Parsum danke ich für die beratende Unterstützung.

Manuela Pfeifer danke ich für die Unterstützung zur Weiterführung der Arbeit gerade in den letzten Monaten vor meinem Ausscheiden aus der Abteilung EPG.

Bedanken möchte ich mich bei Frau Tarrach und Alexander Buske aus der ehemaligen Abteilung EPA der Jenapharm GmbH & Co. KG für die Unterstützung bei der Erstellung der HPLC-Methode zur Messung der Abbauprodukte von EE, bei der Einlagerung der Proben in die Klimakammern und dem Messen der Proben an der HPLC-Anlage.

Großer Dank gilt Tina Loth (Institut für Pharmazie, Pharmazeutische Technologie, Universität Leipzig) für REM-Aufnahmen zur Untersuchung der Struktur unterschiedlicher MCC-Qualitäten.

Ein besonderes Dankeschön gilt all meinen ehemaligen Kolleginnen und Kollegen der Abteilung EPG für die tolle Arbeitsatmosphäre und Eure stete Unterstützung in allen Fragestellungen. Besonders möchte ich Anke, Kathrin und Petra, Frau Schmidt, Kirsten und Ralf für die vielen lustigen und schönen Mittagspausen danken. Ich habe die Zeit in der Abteilung sehr genossen und viel von Euch gelernt.

Meinen Eltern kann ich nicht genug danken dafür dass Ihr immer für meine Familie und mich da seid.

Unendlicher Dank gilt meinem lieben Mann Micha und meinen beiden Kindern Martha und Yann für das immer währende Verständnis und die Unterstützung in all den Jahren, für die Zeit, die Ihr mir gelassen habt und für die Motivation, die Ihr mir täglich aufs Neue schenkt. Danke für alles!